



Carbae™ 105 and Carbae™ 108 are state-of-the-art carbon fiber packings that control your maintenance costs, without compromising performance. Carbae™ 105 is made from a 95% carbon assay, aerospace-grade fiber, coated with PTFE throughout. Carbae™ 108 uses the same fiber but is coated with a unique graphite dispersion.

Both Carbae™ 105 and Carbae™ 108 offer a low coefficient of friction and high thermal conductivity, so your process runs cooler and the packing lasts longer. For unparalleled economy and performance, choose the Carbae™ family of packing.



## Specifications

105	108
<b>Materials of Construction</b> 95% carbon assay fiber; PTFE coating	95% carbon assay fiber; graphite dispersion
<b>Temperature</b> -328°F (-200°C) to +600°F (+316°C) atmosphere To +1200°F (+650°C) steam	-328°F (-200°C) to +850°F (+455°C) atmosphere To +1200°F (+650°C) steam
<b>pH Range</b> 0-14 (except strong oxidizers)	0-14 (except strong oxidizers)
<b>Shaft Speed</b> To 3,000 fpm (15 m/sec)	To 4,000 fpm (20 m/sec)
<b>Pressure*</b> To 500 psi (35 bar) Rotary/Centrifugal	To 500 psi (35 bar) Rotary/Centrifugal; To 2,500 psi (172 bar) Valves

\*There are no known pressure limits that have been determined when Carbae™ 108 is combined as end ring material with die-formed GRAPH-LOCK™ center rings in valve installations.

Carbae™ 108 can be certified to contain less than 200 ppm leachable chlorides on request.

## Value & Benefits

- Excellent cost/use ratio
- Ideal for most industrial equipment
- Compatible with a wide variety of chemicals
- Easy to install and remove

## Ideal for

- Power generation
- Chemical/petrochemical
- Pulp & paper
- Primary metals
- General industrial use

# Garlock

SEALING TECHNOLOGIES®

an EnPro Industries company

# Ordering Information

Size (Inches)	Standard Pkg/Min Order	<i>Carbae 105</i>		<i>Carbae 108</i>	
		Order Code	Yield ft/lb	Order Code	Yield ft/lb
1/8	1 lb. spool	40405-1008	74.1	40408-1008	125
	2 lb. spool	40405-1208		40408-1208	
	5 lb. spool	40405-2008		40408-2008	
3/16	1 lb. spool	40405-1012	31.9	40408-1012	55.6
	2 lb. spool	40405-1212		40408-1212	
	5 lb. spool	40405-2012		40408-2012	
1/4	2 lb. spool	40405-1216	23.3	40408-1216	29.0
	5 lb. spool	40405-2016		40408-2016	
5/16	2 lb. spool	40405-1220	15.9	40408-1220	19.8
	5 lb. spool	40405-2020		40408-2020	
3/8	5 lb. spool	40405-2024	11.5	40408-2024	13.8
	10 lb. spool	40405-3024		40408-3024	
7/16	5 lb. spool	40405-2028	8.3	40408-2028	10.1
	10 lb. spool	40405-3028		40408-3028	
1/2	5 lb. spool	40405-2032	6.5	40408-2032	8.4
	10 lb. spool	40405-3032		40408-3032	
9/16	5 lb. spool	40405-2036	5.4	40408-2036	6.9
	10 lb. spool	40405-3036		40408-3036	
5/8	5 lb. spool	40405-2040	4.4	40408-2040	5.5
	10 lb. spool	40405-3040		40408-3040	
3/4	5 lb. spool	40405-2048	3.3	40408-2048	3.8
	10 lb. spool	40405-3048		40408-3048	
7/8	10 lb. spool	40405-3056	2.3	40408-3056	2.9
1	10 lb. spool	40405-3064	1.6	40408-3064	2.5

## AUTHORIZED REPRESENTATIVE

### WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing.

While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues. Subject to change without notice.

GARLOCK is a registered trademark for packings, seals, gaskets, and other products of Garlock.

© Garlock Inc 2007. All rights reserved worldwide.

**Garlock**  
SEALING TECHNOLOGIES®

an EnPro Industries company

**Garlock Sealing Technologies**  
1666 Division Street  
Palmyra, New York 14522 USA  
1-315-597-4811  
1-800-448-6688  
Fax: 1-800-543-0598  
1-315-597-3039

[www.garlock.com](http://www.garlock.com)

Other Garlock facilities are located in:

**Columbia, SC, USA**  
Phone 1.803.783.1880  
Fax 1.803.783.4279

**Houston, TX, USA**  
Phone 1.281.459.7200  
Fax 1.281.458.0502

**Sydney, Australia**  
Phone 61.2.9793.2511  
Fax 61.2.9793.2544

**São Paulo, Brazil**  
Phone 55.11.4352.6161  
Fax 55.11.4352.8181

**Sherbrooke, Canada**  
Phone 1.819.563.8080  
Fax 1.819-563.5620

**W. Yorkshire, England**  
Phone 44.1422.313600  
Fax 44.1422.313601

**Saint-Étienne, France**  
Phone 33.4.7743.5100  
Fax 33.4.7743.5151

**Neuss, Germany**  
Phone 49.2131.3490  
Fax 49.2131.349.222

**Mexico City, Mexico**  
Phone 52.555.567.7011  
Fax 52.555.368.0418

**Singapore**  
Phone 65.6285.9322  
Fax 65.6284.5843

**Shanghai, China**  
Phone 86.021.62789702  
Fax 86.021.62787826

**Dubai, UAE**  
Phone 971.4.8833652  
Fax 971.4.8833682