

Thomson SS-78

Abrasion-resistant slurry service, rotating equipment, and valve stem compression packing



FEATURES / BENEFITS

- High strength, high pressure capability - longer life.
- Chemical compatibility - reduces inventory costs.
- Non-asbestos - reduces handling cost.
- Excellent thermal stability.

TYPICAL APPLICATIONS

- Highly abrasive media, high pressure applications, slurries, mining tailings pumps, brines, effluent treatment.
- Compatible with mild acids, mild caustics, oils, low pressure steam, waste water, pulp and paper applications.
- Worn equipment with damaged sleeves, sever radial run out or bent shaft conditions - very resistant to extrusion.
- Very high strength and durable Aramid filament fibers.

SPECIFICATIONS

Construction:

Aramid filament fiber/PTFE dispersion. Square interbraid.

Temperatures:

-200°F (-128°C) to +550°F (+288°C)

Pressure:

To 500+ psi (34 bar). For higher pressures e.g. reciprocating pumps, please contact A.R. Thomson Group.

Speed:

2000 fpm (10 m/s)

pH range:

3–11

See reverse for ordering information.

ORDERING INFORMATION - SS-78

Specify Thomson style, size and quantity (lbs) required.

Size	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
Approx. (ft/lb)	23.1	12.8	9.1	7.3	6.2	4.8	4.2	2.9	2.1	1.5
Std pkg (lbs)	2/5	1/2/5	2/5/10/25	5	5/10	5	5/10/50	10/25/50	10	10

Also available in metric sizes, die formed pre-packaged sets, and specialty cut lengths.
Contact A.R. Thomson Group for any special requirements.

SHAFT SPEED CONVERSION CALCULATIONS

Feet per minute (fpm)	Meter per second (m/s)
Shaft / sleeve diameter (in) x RPM x 0.262 = fpm	Shaft / sleeve diameter (in) x RPM x 0.0013299 = m/s
Shaft / sleeve diameter (mm) x RPM x 0.0103 = fpm	Shaft / sleeve diameter (mm) x RPM x 0.0000524 = m/s

AUTHORIZED DISTRIBUTOR

Limitation of liability: actual performance may vary and is determined by factors unique to a given application. It is recommended that care be taken in the selection and application of materials for hazardous services and controlled testing be undertaken to determine suitability for a specific application. A.R. Thomson Group does not make or imply any warranty of suitability for a particular purpose and is not liable for any damages arising from the use of the information in this sheet.



Locations across Canada to serve you. For your nearest branch, please visit www.arthomson.com
Copyright © A.R. Thomson Group - All rights reserved.