

Garlock Style 2400

Style 2400 is a quality, general service compressed non-asbestos gasketing material which is grey in color. The combination of a nitrile (NBR) rubber binder with aramid and mineral fibers provides good performance at a competitive price.



Specifications*

Temperature, min.	-40°F (-40°C)
Cont. operating temp.	+400°F (+205°C)
Pressure, max.	1,000 psi (69 bar)
P x T, max.**	
1/32" (0.8mm) 1/16" (1.6mm)	350,000 (12,000)
1/8" (3.2mm)	250,000 (8,600)

* When approaching maximum pressure or continuous operating temperature, or 50% of Maximum PxT, consult Garlock Applications Engineering. Pressure and PxT max ratings based on standard ANSI flanges at our preferred torque values.

** P x T = psig x °F (bar x °C)

Value & Benefits

- Unique blend of organic and inorganic fibers
- Oil and fuel resistant binder
- Improved compressibility and thermal stability
- Good performance in low pressure saturated steam
- Longer life

Ideal for Industries

- General service
- Water municipalities
- Water treatment

Media

- Water
- Aliphatic hydrocarbons
- Oils
- Gasoline
- Saturated steam

Physical Properties

ASTM Test Method	Typical Physical Properties
F37B	Sealability Milliliters/Hour Leakage, ASTM Fuel A (isooctane): 1.0 Gasket Load, 500 psi (3.5 N/mm ²) Internal Pressure, 9.8 psig (0.7 bar) Nitrogen: 1.5 Gasket Load, 3000 psi (20.7 N/mm ²) Internal Pressure, 30 psig (2 bar)
F36	Recovery, % 50
F36	Compressibility, % Range 10-20
F38	Creep Relaxation, % 20 22 hrs. @ 212°F (100°C)

ASTM Test Method	Typical Physical Properties
F146	Fluid Resistance After Five Hours Immersion ASTM #1 Oil @ 300°F (150°C) Thickness Increase Range, %: 0-10 Weight Increase Max., %: 15 ASTM IRM #903 Oil @ 300°F (150°C) Thickness Increase Range, %: 0-15 Tensile Loss Max., %: 35 ASTM Fuel A @ 70-85°F (20-30°C) Thickness Increase Range, %: 0-10 Weight Increase Max., %: 10 ASTM Fuel B @ 70-85°F (20-30°C) Thickness Increase Range, %: 0-10 Weight Increase Max., %: 15
F152	Tensile Strength 1750 Across Grain, psi (N/mm ²): (12)

Sizes

60" x 63" sheet size

1/32", 1/16", 1/8" thicknesses

NOTE: This is a general guide and should not be the sole means of selecting or rejecting this material. Properties based on 1/32" (0.8mm) sheet thickness. Typical physical properties are derived from averages of actual test results. These values do not constitute specification limits.

AUTHORIZED DISTRIBUTOR



Garlock Sealing Technologies
 1666 Division Street
 Palmyra, New York 14522 USA
 Phone: 1-315-597-4811
 Toll Free: 1-800-448-6688
 Fax: 1-315-597-3290
 Toll Free Fax: 1-800-543-0598



ISO 9001:2000
 Cert. #001762

WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing.

While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues. Subject to change without notice.

GARLOCK is a registered trademark for packings, seals, gaskets, and other products of Garlock.

© Garlock Inc 2004. All rights reserved worldwide.

Other Garlock facilities are located in:

Columbia, SC, USA
 Phone 1-803-783-1880
 Fax 1-803-783-4279

São Paulo, Brazil
 Phone 55-11-4127-9935
 Fax 55-11-4343-5871

W. Yorkshire, England
 Phone 44-1422-313600
 Fax 44-1422-313601

Mexico City, Mexico
 Phone 52-555-567-7011
 Fax 52-555-368-0418

Houston, TX, USA
 Phone 1-281-459-7200
 Fax 1-281-458-0502

Brantford, Canada
 Phone 1-519-753-8671
 Fax 1-519-758-2265

Saint-Étienne, France
 Phone 33-4-7743-5100
 Fax 33-4-7743-5151

Singapore
 Phone 65-6285-9322
 Fax 65-6284-5843

Sydney, Australia
 Phone 61-2-9793-2511
 Fax 61-2-9793-2544

Sherbrooke, Canada
 Phone 1-819-563-8080
 Fax 1-819-563-5620

Neuss, Germany
 Phone 49-2131-3490
 Fax 49-2131-349-222

Dubai, UAE
 Phone 971-4-8833652
 Fax 971-4-8833682