

Data

Chemical	Test Temp. °F	Natural Rubber	SBR Rubber	Butyl	EP Rubber	Nitrile	Herchlor Hydrin	Neoprene	CPE Rubber	Hypalon	Urethane	Silicone	Fluoro-Silicone	Fluoro-elastomer	Polyacrylate
		ACETALDEHYDE	70°	C	U	A	A	U	A	C	-	C	U	A	U
ACETALDEHYDE AMMONIA		B	B	A	-	B	-	-	A	B	-	-	-	-	-
PARA-ACETALDEHYDE	70°	C	-	A	-	U	-	-	-	-	-	-	-	U	-
ACETAMIDE		C	C	A	A	A	-	B	-	B	U	B	A	B	U
ACETATE C-8	70°	U	U	B	-	U	-	-	B	U	-	-	-	U	-
ACETIC ACID, GLACIAL	70°	U	U	B	B	U	U	C	A	C	U	B	C	U	U
ACETIC ACID, 30%	150°	C	C	A	A	C	C	B	A	B	C	A	B	C	U
ACETIC ACID AMINE		C	C	A	A	A	-	B	-	B	U	B	A	B	U
ACETIC ALDEHYDE	70°	C	U	A	A	U	A	C	-	C	U	A	U	U	U
ACETIC ANHYDRIDE		B	B	A	A	C	U	B	A	A	U	C	U	U	U
ACETIC ESTER	70°	U	U	B	B	U	-	C	B	U	-	B	U	U	-
ACETIC ETHER	70°	U	U	B	B	U	-	C	B	U	-	B	U	U	-
ACETIC OXIDE	70°	B	B	A	A	C	U	B	A	A	U	C	U	U	U
ACETOACETIC ESTER	70°	C	C	B	B	U	-	C	A	U	-	B	U	U	-
ACETONE	70°	B	B	A	A	U	U	B	A	B	U	B	U	U	U
ACETONE CYANOHYDRIN	70°	C	C	A	-	U	-	-	A	C	-	-	-	U	-
ACETOPHENONE		C	U	A	A	U	U	U	-	U	U	-	U	U	U
ACETYLACETONE		C	U	B	-	U	-	-	B	U	-	-	-	U	-
ACETYLBENZENE		C	U	A	A	U	U	U	-	U	U	-	U	U	U
ACETYLCHLORIDE	70°	U	U	U	-	U	-	-	A	U	-	-	-	B	-
ACETYLENE	70°	B	B	A	A	A	-	B	-	B	-	B	-	A	-
ACETYLENE DICHLORIDE	70°	U	U	U	U	U	U	U	-	U	U	C	C	A	-
ACETYLENE TETRACHLORIDE	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
ACETYL OXIDE		B	B	A	A	C	U	B	A	A	U	C	U	U	U
ACRALDEHYDE		B	C	A	A	B	U	B	A	B	U	U	U	A	U
ACROLEIN		B	C	A	A	B	U	A	A	B	U	U	U	A	U
ACRYLALDEHYDE		B	C	A	A	B	U	A	A	B	U	U	U	A	U
ACRYLONITRILE	70°	U	U	C	C	U	-	C	A	C	-	U	U	U	-
ADIPIC ACID		-	-	-	-	A	-	-	-	-	-	-	A	-	-
ALCOHOL C-8	70°	B	B	A	A	B	-	A	A	A	U	B	B	A	U
ALCOHOL C-11	70°	A	A	A	-	A	-	-	-	A	-	-	-	B	-
ALCOHOL C-12	70°	A	A	A	-	A	-	-	-	A	-	-	-	B	-
ALDEHYDE C-7	70°	U	U	A	-	U	-	-	C	U	-	-	-	-	-
ALDEHYDE C-10	70°	U	U	A	-	U	-	-	-	U	-	-	-	U	-
ALDEHYDE AMMONIA		B	B	A	-	B	-	-	A	B	-	-	-	-	-
ALKANE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
ALKAZENE		U	U	U	U	C	C	U	-	U	C	-	B	A	-
ALLOMALEIC ACID		A	A	U	-	A	-	B	-	B	-	B	A	A	U
ALLYL ALCOHOL		A	A	A	-	A	-	-	A	A	-	-	-	A	-
ALLYL ALDEHYDE		B	C	A	A	B	U	A	A	B	U	U	U	A	U
ALLYL BROMIDE	70°	U	U	U	-	U	-	-	B	U	-	-	-	B	-

Data

ALLYL CHLORIDE	70°	U	U	C	U	U	-	U	B	U	-	-	-	B	-
ALUMS - NH <sub>3</sub> - Cr or K	150°	A	B	A	A	A	-	A	A	A	-	A	A	A	-
ALUMINUM ACETATE	70°	A	A	A	A	A	A	A	A	A	-	B	A	A	A
ALUMINUM CHLORIDE	70°	A	A	A	A	A	A	A	A	A	-	B	A	A	A
ALUMINUM DIFORMATE	70°	U	U	B	-	U	-	-	-	U	-	-	-	C	-
ALUMINUM FLUORIDE	150°	B	A	A	A	A	A	A	-	A	-	B	A	A	-
ALUMINUM FORMATE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
ALUMINUM HYDROXIDE	150°	A	B	A	A	B	-	A	A	B	-	-	-	C	-
ALUMINUM NITRATE	70°	A	A	A	A	A	A	A	-	A	-	-	-	-	-
ALUMINUM ORTHOPHOSPHATE	150°	A	A	A	A	-	-	A	-	A	-	A	-	A	-
ALUMINUM PHOSPHATE	150°	A	A	A	A	-	-	A	-	A	-	A	-	A	-
ALUMINUM SULFATE	150°	A	B	A	A	A	-	A	A	A	-	A	A	A	U
ALUMINUM TRIFORMATE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
ALUMINUM TRIHYDRATE	150°	A	B	A	A	B	-	A	A	B	-	-	-	C	-
AMINO BENZENE	70°	U	U	A	A	U	U	C	B	C	-	C	C	C	U
1-AMINO BUTANE	70°	B	B	A	A	B	-	U	-	C	U	B	U	U	U
AMINODIMETHYL BENZENE	70°	U	U	U	U	C	-	U	-	U	-	U	U	U	-
AMINOETHANE	70°	C	C	B	-	C	-	-	A	C	-	-	-	-	-
1-AMINO ETHANOL	70°	B	B	A	-	B	-	-	-	A	B	-	-	-	-
2-AMINO ETHANOL	70°	B	B	A	B	B	B	B	A	B	C	B	U	U	U
AMINOETHYLETHANOLAMINE	70°	B	B	A	-	B	-	-	-	B	-	-	-	-	-
1-AMINOPENTANE	70°	B	B	A	-	B	-	-	B	C	-	-	-	-	-
2-AMINOPROPANE	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-
1-AMINO-2-PROPANOL	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-
AMINOXYLENE	70°	U	U	U	U	C	-	U	-	U	-	U	U	U	-
AMMONIA-AQUA	150°	B	B	A	A	B	B	B	A	A	A	A	B	A	-
AMMONIA-ANHYDROUS	70°	A	-	A	A	A	-	A	-	B	-	C	U	U	-
AMMONIA GAS (COLD)	70°	A	A	A	A	A	-	A	-	A	-	A	A	-	-
AMMONIA GAS (HOT)	150°	C	C	B	B	C	-	B	-	B	-	A	U	U	-
AMMONIUM CARBONATE	70°	A	A	A	A	U	B	A	-	-	-	-	-	-	-
AMMONIUM CHLORIDE	150°	A	A	A	A	A	A	A	A	A	A	B	A	A	A
AMMONIUM CUPRIC SULFATE	150°	C	A	A	-	A	-	-	-	A	-	-	-	A	-
AMMONIUM HYDROXIDE	150°	B	B	A	A	B	B	B	A	A	A	A	B	A	-
AMMONIUM HYPOSULFITE	150°	A	A	A	-	A	-	-	A	A	-	-	-	A	-
AMMONIUM NITRATE	70°	A	A	A	A	A	A	A	-	A	U	-	-	-	A
AMMONIUM NITRITE	150°	A	A	A	A	A	-	A	-	A	-	B	-	-	-
AMMONIUM PERSULFATE	150°	A	U	A	A	U	-	A	-	A	U	-	-	-	U
AMMONIUM PHOSPHATE	150°	A	A	A	A	A	-	A	A	A	-	A	-	-	-
AMMONIUM SESQUICARBONATE	70°	A	A	A	A	U	B	A	-	-	-	-	-	-	-
AMMONIUM SULFATE	150°	A	A	A	A	A	-	A	A	A	-	-	-	-	U
AMMONIUM SULFIDE	150°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
AMMONIUM SULFITE	150°	A	A	A	-	A	-	-	A	A	-	-	-	A	-
AMMONIUM THIOSULFATE	70°	A	A	A	-	A	-	-	A	A	-	-	-	A	-
AMYL ACETATE	70°	U	U	A	A	U	U	U	C	U	U	U	U	U	U
AMYL ALCOHOL	70°	A	A	A	A	A	A	A	A	A	U	C	B	B	U
AMYLAMINE	70°	B	B	A	-	B	-	-	B	C	-	-	-	-	-
AMYL BORATE		U	U	U	U	A	-	A	-	A	-	-	-	A	-
AMYL CARBINOL	70°	A	A	B	C	A	-	B	A	B	U	B	A	A	U
AMYL CHLORIDE	70°	U	U	U	U	U	-	U	C	U	-	-	-	B	-
AMYL CHLORONAPHTHALENE		U	U	U	U	U	-	U	-	U	U	U	A	A	B
AMYL HYDRATE	70°	A	A	A	A	A	A	A	A	A	U	C	B	B	U
AMYL HYDRIDE	70°	U	U	U	-	A	-	-	-	C	-	-	-	A	-

Data

AMYL NAPHTHALENE		U	U	U	U	U	-	U	-	U	U	U	A	A	B
AMYL OLEATE	70°	U	U	U	U	U	-	U	-	U	-	-	-	B	-
AMYL PHENOL	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
AMYL PHTHALATE	70°	U	U	A	-	U	-	-	-	U	-	-	-	C	-
ANETHOLE	70°	U	U	U	-	U	-	-	A	U	-	-	-	B	-
ANGLESITE	150°	A	A	A	-	A	-	A	A	A	-	-	-	A	-
ANILINE	70°	U	U	A	A	U	U	C	B	C	-	C	C	C	U
ANILINE CHLORIDE		B	C	B	B	B	-	U	-	U	U	U	B	B	U
ANILINE DYES		B	B	B	B	U	-	B	-	B	U	-	B	B	U
ANILINE HYDROCHLORIDE		B	C	B	B	B	-	U	-	U	U	U	B	B	U
ANILINE OIL	70°	U	U	A	A	U	U	C	B	C	-	C	C	C	U
ANILINE SALT		B	C	B	B	B	-	U	-	U	U	U	B	B	U
ANISE CAMPHOR	70°	U	U	U	-	U	-	-	A	U	-	-	-	B	-
ANIMAL FATS		U	U	B	B	A	A	B	-	B	A	B	A	A	A
ANSUL ETHER-121		U	U	C	C	C	-	U	-	U	B	U	C	U	U
ANTIMONY PENTACHLORIDE	70°	U	U	U	-	U	-	-	-	U	-	-	-	-	-
ANTIMONY PERCHLORIDE	70°	U	U	U	-	U	-	-	-	U	-	-	-	-	-
ANT OIL, ARTIFICIAL	70°	C	C	B	B	U	U	B	A	B	-	C	-	U	-
AQUA AMMONIA	150°	B	B	A	A	B	B	B	A	A	A	A	B	A	-
AQUA REGIA		U	U	U	U	-	-	U	B	C	-	-	C	B	-
AROMATIC SPIRITS	70°	U	U	U	-	C	-	-	-	U	-	-	-	A	-
AROMATIC TAR	70°	U	U	U	-	C	-	-	-	U	-	-	-	A	-
ARQUADS	70°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
ARSENIC ACID	70°	B	A	A	A	A	A	A	A	A	C	A	A	A	C
ARSENIC CHLORIDE	70°	U	U	U	-	U	-	-	-	U	-	-	-	U	-
ARSENIC TRICHLORIDE	70°	U	U	U	-	U	-	-	-	U	-	-	-	U	-
ARTIFICIAL GOLD	150°	A	A	A	-	A	-	-	-	A	-	-	-	-	-
ASKAREL (DIELECTRICS)		U	U	U	U	B	-	U	-	U	U	U	B	A	U
ASPHALT	175°	U	U	U	U	B	A	B	-	C	B	U	B	A	B
ASPHALTUM	175°	U	U	U	U	B	A	B	-	C	B	U	B	A	B
ASTM#1 OIL	70°	U	U	U	U	A	-	B	A	B	A	-	-	A	-
ASTM#2 OIL	70°	U	U	U	U	A	-	B	A	C	A	-	-	A	-
ASTM#3 OIL	70°	U	U	U	U	A	-	B	A	C	A	-	-	A	-
BARIUM CARBONATE	150°	A	A	A	A	A	-	A	-	A	-	-	-	A	-
BARIUM CHLORIDE	150°	A	A	A	A	A	A	A	A	A	A	A	A	A	A
BARIUM HYDROXIDE	150°	A	A	A	A	A	A	A	A	A	A	A	A	A	U
BARIUM MONOSULFIDE	150°	A	B	A	A	A	A	A	-	A	A	A	A	A	U
BARIUM SULFATE	150°	A	A	A	A	A	A	A	-	A	A	A	A	A	-
BARIUM SULFIDE	150°	A	B	A	A	A	A	A	-	A	A	A	A	A	U
BEER		A	A	A	A	A	A	A	-	A	-	A	A	A	U
BEET SUGAR LIQUORS		A	A	A	A	A	-	A	-	A	-	A	A	A	U
BENZAL CHLORIDE	70°	-	-	B	-	U	-	-	U	-	-	-	-	-	-
BENZALDEHYDE		U	U	A	A	U	U	U	C	U	U	U	U	U	U
BENZENE	70°	U	U	U	U	U	U	C	U	U	-	U	B	B	U
BENZENE DIBROMIDE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
BENZENEMONOSULFONIC ACID		-	-	-	-	-	-	A	-	A	-	-	B	A	-
BENZENESULFONIC ACID		-	-	-	-	-	-	A	-	A	-	-	B	A	-
BENZINE	70°	U	U	U	U	A	-	C	A	U	-	-	-	A	-
BENZOIC ACID		U	U	B	-	-	-	-	A	B	-	B	B	A	-
BENZOIC ALDEHYDE	70°	U	U	A	A	U	U	U	C	U	U	U	U	U	U
BENZYL ACETATE	70°	U	U	B	-	U	-	-	B	-	-	-	-	U	-
BENZYL ALCOHOL	70°	C	C	B	B	U	U	B	A	B	-	-	B	A	-

Data

BENZYL BENZOATE		-	-	B	B	-	-	-	-	-	-	-	A	A	-
BENZYL CHLORIDE	70°	-	-	B	B	U	-	U	B	-	-	-	A	A	-
BENZYL DICHLORIDE	70°	-	-	B	-	U	-	-	U	-	-	-	-	-	-
BETULA OIL		-	-	B	B	-	-	U	-	-	-	-	-	-	-
BICARBURETTED HYDROGEN		-	-	-	-	A	-	-	-	-	-	-	A	A	-
BICHLOROACETIC ACID	70°	B	U	C	-	U	-	-	-	U	-	-	-	U	-
BICHROMATE OF SODA	150°	-	-	A	-	-	-	-	A	C	-	-	-	-	-
BIMETHYL		U	U	U	U	A	-	B	-	B	B	U	A	A	A
BINITROBENZENE	70°	U	U	C	-	U	-	-	-	U	-	-	-	A	-
BLACK ASH	150°	A	B	A	A	A	A	A	-	A	A	A	A	A	U
BLACK LIQUOR	150°	B	B	B	B	B	-	B	-	B	-	-	-	-	-
BLAST FURNACE GAS		C	C	C	C	B	-	B	-	C	-	B	B	A	-
BLEACH	70°	U	U	B	B	U	B	C	-	B	U	B	B	A	U
BLEACH SOLUTIONS	70°	U	U	B	B	-	-	C	-	A	-	B	B	A	-
BLUE COPPERAS	150°	C	A	A	A	A	-	A	-	A	A	A	A	A	U
BLUE SALT	150°	B	B	A	A	A	-	A	-	A	A	A	A	A	U
BLUE STONE	150°	C	A	A	A	A	-	A	-	A	A	A	A	A	U
BLUE VITRIOL	150°	C	A	A	A	A	-	A	-	A	A	A	A	A	U
BOLETIC ACID		A	A	U	-	A	-	B	-	B	-	B	A	A	U
BORACIC ACID		A	A	A	A	A	A	A	-	A	A	A	A	A	U
BORAX		B	B	A	A	B	-	A	-	A	A	B	B	A	B
BORAX DECAHYDRATE		B	B	A	A	B	-	A	-	A	A	B	B	A	B
BORAX DEHYDRATE		B	B	A	A	B	-	A	-	A	A	B	B	A	B
BORAX DEHYDRATED		B	B	A	A	B	-	A	-	A	A	B	B	A	B
BORDEAU MIXTURE		B	B	A	A	B	-	A	-	A	-	B	B	A	-
BORIC ACID		A	A	A	A	A	A	A	-	A	A	A	A	A	U
BRIMSTONE	250°	U	U	A	A	U	C	A	-	A	U	A	A	A	U
BRINE	150°	A	A	A	A	A	-	A	-	A	-	-	-	A	-
BROMINE-ANHYDROUS	70°	U	U	U	U	U	-	U	-	U	U	C	B	A	-
BROMINE TRIFLUORIDE		U	U	U	U	U	U	U	-	U	U	U	U	U	U
BROMINE WATER		-	-	-	-	-	-	B	-	A	-	-	B	A	-
BROMOALLYLENE	70°	U	U	U	-	U	-	-	B	U	-	-	-	B	-
BROMOBENZENE	70°	U	U	U	U	U	U	U	U	U	U	U	A	A	U
1-BROMO BUTANE	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
BROMOCHLOROMETHANE	70°	U	U	B	B	U	-	U	C	U	-	-	-	U	-
BROMOMETHANE		-	-	-	-	B	-	U	-	U	-	-	A	A	-
3-BROMOPROPENE	70°	U	U	U	-	U	-	-	B	U	-	-	-	B	-
BROMOTOLUENE	70°	U	U	U	-	U	-	-	U	U	-	-	-	B	-
BROMOTRIFLUOROMETHANE	70°	A	A	A	A	A	-	A	-	A	A	U	-	A	-
BUBULUM OIL		U	U	B	B	A	-	-	-	-	-	B	A	A	A
BUNKER OIL	70°	U	U	U	U	A	-	B	-	A	B	B	A	A	A
BUTADIENE		U	U	C	C	C	U	B	-	B	U	-	B	B	-
BUTALDEHYDE	70°	C	-	A	-	U	-	-	B	-	-	-	-	U	-
BUTANAL	70°	C	-	A	-	U	-	-	B	-	-	-	-	U	-
BUTANE		U	U	U	U	A	A	B	-	A	A	-	A	A	A
1.4 BUTANEDICARBOXYLIC ACID		-	-	-	-	A	-	-	-	-	-	-	A	-	-
BUTANOIC ACID	70°	C	U	C	-	C	-	C	A	B	-	-	-	-	-
BUTANOL	70°	A	A	A	A	A	-	A	A	A	U	B	A	A	U
2-BUTENAL	70°	U	U	A	-	U	-	-	-	U	-	-	-	U	-
BUTENE-1	70°	U	U	U	U	B	-	C	-	C	-	-	B	A	-
CIS-BUTENE-2	70°	U	U	U	U	B	-	C	-	C	-	-	B	A	-
TRANS-BUTENE-2	70°	U	U	U	U	B	-	C	-	C	-	-	B	A	-

Data

CIS-BUTENEDIOIC ACID	70°	C	C	C	C	U	-	-	-	C	-	-	-	A	-
TRANS-BUTENEDIOIC ACID		A	A	U	-	A	-	B	-	B	-	B	A	A	U
BUTRALDEHYDE	70°	C	-	A	-	U	-	-	B	-	-	-	-	U	-
BUTRIC ALDEHYDE	70°	C	-	A	-	U	-	-	B	-	-	-	-	U	-
BUTTER		U	U	B	A	A	A	B	-	B	A	A	A	A	A
BUTTER OF ZINC	150°	A	A	A	A	A	-	A	-	A	-	-	A	A	U
BUTYL ACETATE		U	U	B	B	U	U	U	B	U	U	U	U	U	U
BUTYL ACETOACETATE	70°	U	U	C	-	U	-	-	-	U	-	-	-	U	-
BUTYL ACETYL RICINOLEATE		-	-	A	A	-	-	B	-	B	-	-	-	B	A
BUTYL ACRYLATE	70°	U	U	U	U	U	-	-	B	U	-	-	-	U	-
BUTYL ALCOHOL	70°	A	A	A	A	A	-	A	A	A	U	B	A	A	U
TERT-BUTYL ALCOHOL		B	B	B	B	B	-	B	-	B	U	B	B	A	U
BUTYL ALDEHYDE	70°	C	-	A	-	U	-	-	B	-	-	-	-	U	-
BUTYLAMINE	70°	B	B	A	A	B	-	U	-	C	U	B	U	U	U
BUTYLBENZENE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
BUTYL BENZYL PHTHALATE	70°	U	U	A	-	U	-	-	-	U	-	-	-	C	-
BUTYL BENZOATE		U	U	U	-	U	-	-	-	U	-	-	-	B	-
BUTYL BROMIDE	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
BUTYL BUTANOATE	70°	U	U	C	-	U	-	-	-	U	-	-	-	U	-
BUTYL BUTYRATE	70°	U	U	C	-	U	-	-	-	U	-	-	-	U	-
BUTYL CARBITOL	70°	-	-	A	A	A	-	B	A	B	-	-	-	A	-
PARA-TERT-BUTYLCATECHOL		U	C	B	B	U	-	B	-	B	U	-	A	A	U
BUTYL CELLOSOLVE	70°	U	U	A	A	A	-	B	A	B	-	-	U	U	-
BUTYL CHLORIDE	70°	U	U	C	-	U	-	-	U	U	-	-	-	B	-
4. TERT-BUTYL-1, 2-DIHYDROXYBENZENE		U	C	B	B	U	-	B	-	B	U	-	A	A	U
BUTYLENE	70°	U	U	U	U	B	-	C	-	C	-	-	B	A	-
BUTYL ETHER	70°	U	U	C	C	U	-	U	-	U	B	-	C	C	U
BUTYL ETHYL ACETALDEHYDE	70°	U	U	A	-	U	-	-	-	U	-	-	-	U	-
BUTYL ETHYL ETHER	70°	U	U	B	-	U	-	B	-	U	-	-	-	C	-
BUTYL HYDRIDE		U	U	U	U	A	A	B	-	A	A	-	A	A	A
TERT-BUTYL MERCAPTAN		U	U	U	U	U	-	U	-	U	U	-	-	A	-
BUTYL OCTADECANOATE		U	U	B	B	B	-	U	-	U	-	-	B	A	-
BUTYL OLEATE		U	U	B	B	-	-	U	-	U	-	-	B	A	-
BUTYL PHTHALATE	70°	U	U	A	A	U	B	U	C	U	C	B	B	B	-
BUTYL STEARATE		U	U	B	B	B	-	U	-	U	-	-	B	A	-
BUTYL TITANATE		B	B	B	A	B	-	A	-	A	-	-	A	A	-
BUTYRALDEHYDE	70°	U	U	B	B	U	-	C	-	U	-	C	U	U	U
BUTYRIC ACID	70°	C	U	C	-	C	-	C	A	B	-	-	-	-	-
BUTYRIC ALCOHOL	70°	A	A	A	A	A	-	A	A	A	U	B	A	A	U
BUTYRIC ANH+A289YDRIDE	70°	C	U	C	-	C	-	-	-	B	-	-	-	-	-
BUTYRONE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
CADMIUM ACETATE	70°	A	B	A	A	B	-	B	A	B	-	-	U	U	-
CAKE ALUM	150°	A	B	A	A	A	-	A	A	A	-	A	A	A	U
CALCIUM ACETATE	70°	A	B	A	A	B	-	B	A	B	-	-	U	U	-
CALCIUM ALUMINATE	70°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
CALCIUM BICHROMATE	150°	-	-	A	-	-	-	-	-	C	-	-	-	-	-
CALCIUM BISULFITE	150°	A	B	A	A	A	-	A	-	A	A	A	A	A	-
CALCIUM CARBONATE	150°	A	A	A	A	A	-	A	-	A	-	-	-	A	-
CALCIUM CHLORIDE	150°	A	A	A	A	A	A	A	-	A	A	A	A	A	A
CALCIUM DIACETATE	70°	A	B	A	A	B	-	B	A	B	-	-	U	U	-
CALCIUM DICHROMATE	150°	-	-	A	-	-	-	-	-	C	-	-	-	-	-
CALCIUM HYDROGEN SULFITE	150°	A	B	A	A	A	-	A	-	A	A	A	A	A	-

Data

CALCIUM HYDROSULFIDE	70°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
CALCIUM HYDRATE	70°	A	A	A	A	A	A	A	A	A	A	A	A	A	U
CALCIUM HYDROXIDE	70°	A	A	A	A	A	A	A	A	A	A	A	A	A	U
CALCIUM HYPOCHLORITE	70°	B	B	B	B	B	B	B	B	B	-	B	A	A	U
CALCIUM NITRATE	150°	A	A	A	A	A	A	A	A	A	A	B	A	A	A
CALCIUM OXYCHLORIDE	70°	B	B	B	B	B	B	B	B	B	-	B	A	A	U
CALCIUM SILICATE	150°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
CALCIUM SULFATE	150°	A	A	A	A	A	-	A	-	A	-	-	-	A	-
CALCIUM SULFHYDRATE	70°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
CALCIUM SULFIDE	150°	B	B	A	A	B	B	A	A	A	A	B	A	A	U
CALCIUM SULFITE	150°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
CANE SUGAR LIQUORS		A	A	A	A	A	A	A	-	A	U	A	A	A	U
CAPRALDEHYDE	70°	U	U	A	-	U	-	-	-	U	-	-	-	U	-
CAPRIC ALDEHYDE	70°	U	U	A	-	U	-	-	-	U	-	-	-	U	-
CAPRILIC ACID	70°	C	U	C	-	C	-	-	A	B	-	-	-	-	-
CAPROIC ALDEHYDE	70°	U	U	B	A	U	-	A	-	-	B	B	-	U	-
CAPROYL ALCOHOL	70°	A	A	B	C	A	-	B	A	B	U	B	A	A	U
CAPRYLIC ACID	70°	C	U	C	-	C	-	-	A	B	-	-	-	-	-
CAPRYLYL ACETATE	70°	U	U	B	-	U	-	-	B	U	-	-	-	U	-
CARBAMIDE		-	-	A	-	C	-	A	-	-	-	-	-	-	-
CARBAMATE		U	U	B	B	C	-	B	-	B	U	-	A	A	U
CARBAZOTIC ACID		B	B	B	B	B	-	A	-	B	B	U	B	A	-
CARBINOLS	70°	A	A	A	-	A	-	-	-	A	-	-	-	U	-
CARBITOL	70°	B	B	B	B	B	-	B	A	B	U	B	B	B	U
CARBITOL ACETATE	70°	U	U	C	-	U	-	-	-	U	-	-	-	U	-
CARBOLIC ACID		U	U	B	B	U	-	C	A	C	U	U	B	A	-
CARBON BISULFIDE	70°	U	U	U	U	C	U	U	C	U	-	U	C	A	-
CARBON DIOXIDE	70°	B	B	B	B	A	A	B	-	A	A	A	A	A	B
CARBON DISULFIDE	70°	U	U	U	U	C	U	U	C	U	-	-	C	A	-
CARBONIC ACID	70°	A	A	A	A	A	A	A	-	A	A	A	A	A	A
CARBONIC ANHYDRIDE	70°	B	B	B	B	A	A	B	-	A	A	A	A	A	B
CARBON MONOXIDE	70°	B	B	A	A	A	A	A	-	A	A	A	B	A	-
CARBON MONOXIDE	150°	C	C	C	C	C	-	C	-	B	-	-	B	A	-
CARBON TETRABROMIDE		U	U	U	U	U	-	-	-	-	-	-	B	A	-
CARBON TETRACHLORIDE	70°	U	U	U	U	C	B	U	C	U	C	U	A	A	-
CASINGHEAD GASOLINE	70°	U	U	U	-	A	-	-	-	-	-	-	-	A	-
CASTOR OIL	70°	C	B	B	B	A	A	A	A	A	A	A	A	A	A
CAUSTIC LIME	70°	A	A	A	A	A	A	A	A	A	A	A	A	A	U
CAUSTIC POTASH	150°	B	B	A	A	B	B	B	A	B	B	C	B	B	U
CAUSTIC SODA	150°	B	B	A	A	B	B	B	A	B	B	C	B	B	U
CELLOSIZE	70°	U	U	A	-	U	-	-	-	U	-	-	-	-	-
CELLOSOLVE	70°	U	U	B	B	B	-	C	-	C	-	-	-	C	-
CELLOSOLVE ACETATE	70°	U	U	B	B	U	-	U	-	U	U	-	U	U	-
CELLULUBE		ALL CELLULUBES NOW FYR GUARD & FYR C													
CETYLIC ACID	70°	U	C	A	B	A	B	B	-	B	A	-	A	A	-
CHINA-WOOD OIL	100°	U	U	C	U	A	-	B	-	B	B	U	B	A	-
CHINESE BEAN OIL		U	U	B	B	A	A	B	-	B	B	A	A	A	A
CHLORACETIC ACID	70°	C	U	C	B	U	-	C	A	U	U	U	C	U	-
CHLORACETONE	70°	C	U	B	A	U	-	B	U	C	-	-	U	U	-
CHLORAZOTIC ACID	70°	U	U	U	U	-	-	U	B	C	-	-	C	B	-
CHLORBENZOL	70°	U	U	U	U	U	U	U	U	U	C	U	B	A	U
CHLORINATED ACETONE	70°	C	U	B	A	U	-	B	U	C	-	-	U	U	-

Data

CHLORINATED LIME	70°	B	B	B	B	B	B	B	B	B	-	B	A	A	U
CHLORINATED NAPHTHALENE		U	U	U	U	U	-	U	-	-	-	U	B	A	-
CHLORINATED SOLVENTS	70°	U	U	U	U	U	-	U	-	U	-	U	U	A	U
CHLORINATED TAR CAMPHOR		U	U	U	U	U	-	U	-	-	-	U	B	A	-
CHLORINE(DRY)	70°	U	U	C	U	U	B	C	-	C	C	-	A	A	-
CHLORINE(WET)	70°	U	U	C	U	U	B	U	-	U	U	-	B	A	-
CHLORINE DIOXIDE	70°	-	-	C	C	U	-	U	-	C	-	-	B	A	-
CHLORINE TRIFLUORIDE	70°	U	U	U	U	U	U	U	-	U	U	U	B	U	-
CHLOROACETIC ACID	70°	C	U	C	B	U	-	C	A	U	U	U	C	U	-
CHLOROACETONE	70°	C	U	B	A	U	-	B	U	C	-	-	U	U	-
CHLOROAZOTIC ACID	70°	U	U	U	U	-	-	U	B	C	-	-	C	B	-
CHLOROBENZENE	70°	U	U	U	U	U	U	U	U	U	C	U	B	A	U
CHLOROBENZOL	70°	U	U	U	U	U	U	U	U	U	C	U	B	A	U
CHLOROBROMOMETHANE		U	U	B	B	U	-	U	C	U	-	-	-	U	-
CHLOROBUTADIENE		U	U	U	U	U	-	U	-	-	-	-	B	A	-
1-CHLOROBUTANE	70°	U	U	C	-	U	-	-	U	U	-	-	-	B	-
CHLORODODECANE		U	U	U	U	U	-	U	-	-	-	-	A	A	-
CHLOROETHANE		U	U	A	A	A	B	B	-	C	B	U	A	A	C
CHLOROETHENE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
2-CHLOROETHYL ALCOHOL		B	B	-	-	U	-	B	-	B	-	C	B	A	-
CHLOROETHYLENE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
CHLOROETHYLBENZENE	70°	U	U	U	U	C	C	U	U	U	C	-	B	A	-
CHLOROFORM	70°	U	U	U	U	U	-	U	U	U	-	U	B	A	-
CHLOROMETHANE		U	U	C	C	U	-	U	-	U	-	U	B	A	U
3-CHLORO-2-METHYL-1-PROPENE	70°	U	U	C	-	U	-	-	-	U	-	-	-	C	-
0-CHLORONAPHTHALENE		U	U	U	U	U	-	U	-	-	-	U	B	A	-
1-CHLORO-1-NITROETHANE		U	U	U	U	U	-	U	-	U	U	U	-	C	U
CHLORONITROUS ACID		U	U	U	U	-	-	U	B	C	-	-	C	B	-
CHLOROPENTAFLUOROETHANE		A	A	A	A	A	-	A	-	A	-	-	-	B	-
1-CHLOROPENTANE	70°	U	U	U	-	U	-	-	C	U	-	-	-	B	-
CHLOROPHENOL	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
CHLOROPRENE	70°	U	U	U	U	U	-	U	-	-	-	-	B	A	-
CHLOROPROPANE	70°	U	U	C	-	U	-	-	-	U	-	-	-	B	-
1-CHLORO-2-PROPANONE	70°	C	U	B	A	U	-	B	U	C	-	-	U	U	-
3-CHLOROPROPENE	70°	U	U	C	U	U	-	U	B	U	-	-	-	B	-
ALPHA-CHLOROPROPYLENE	70°	U	U	C	U	U	-	U	B	U	-	-	-	B	-
CHLOROPROPYLENE OXIDE	70°	U	U	B	B	-	-	-	-	-	-	-	U	U	-
CHLOROSULFONIC ACID	70°	U	U	U	U	U	-	U	-	U	U	-	C	C	U
CHLOROTHENE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
CHLOROTHENE-NU	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
CHLOROTOLUENE	70°	U	U	U	U	U	-	U	U	U	U	-	B	A	-
CHLOROTRIFLUOROMETHANE		A	A	A	A	A	A	A	-	A	-	-	-	A	-
CHROME PLATING SOLUTIONS	70°	U	U	U	U	U	-	U	-	C	U	B	B	A	-
CHROMIC ACID	100°	U	U	C	C	U	-	U	A	B	U	C	C	A	-
CHROMIC ANHYDRIDE	100°	U	U	C	C	U	-	U	A	B	U	C	C	A	-
CHROMIUM TRIOXIDE	100°	U	U	C	C	U	-	U	A	B	U	C	C	A	-
CIDER VINEGAR		B	B	A	A	B	-	A	-	A	-	A	-	A	U
CINENE		-	-	-	-	B	-	-	-	-	-	-	C	A	-
CINNAMENE	70°	U	U	U	U	U	-	U	-	U	-	U	C	B	-
CITRIC ACID	150°	A	A	A	A	A	A	A	-	A	A	A	A	A	-
COAL OIL	70°	U	U	U	U	A	A	B	A	C	B	U	A	A	A
COAL TAR	70°	U	U	U	-	C	-	-	-	U	-	-	-	A	-

Data

COAL TAR NAPHTHA	70°	U	U	U	-	C	-	-	-	U	-	-	-	A	-
COBALT CHLORIDE		A	A	A	A	A	-	A	-	-	U	A	A	-	U
COBALTOUS CHLORIDE		A	A	A	A	A	-	A	-	-	U	A	A	-	U
COCOANUT OIL		U	U	A	A	A	-	B	-	B	A	A	A	-	A
COCONUT BUTTER		U	U	A	A	A	-	B	-	B	A	A	A	-	A
COCONUT OIL		U	U	A	A	A	-	B	-	B	A	A	A	-	A
COCONUT PALM OIL		U	U	A	A	A	-	B	-	B	A	A	A	-	A
COD-LIVER OIL	70°	U	U	A	A	A	-	B	-	B	A	B	A	A	A
COKE OVEN GAS	70°	U	U	C	-	C	-	C	-	A	-	B	B	A	-
COLAMINE	70°	B	B	A	B	B	B	B	A	B	C	B	U	U	U
COLZA OIL		U	U	A	A	B	A	B	-	B	B	U	A	A	B
COPPER ACETATE	70°	-	-	A	A	B	-	B	-	B	-	-	-	-	-
COPPERAS	150°	A	A	A	A	A	A	A	A	A	-	B	A	A	A
COPPER CARBONATE	70°	C	A	A	-	A	-	-	-	A	-	-	-	A	-
COPPER CHLORIDE	150°	C	A	A	A	A	-	A	-	A	A	A	A	A	A
COPPER CYANIDE	70°	A	A	A	A	A	-	A	-	A	A	A	A	A	A
COPPER HYDRATE	70°	C	B	A	-	B	-	-	-	B	-	-	-	C	-
COPPER HYDROXIDE	70°	C	B	A	-	B	-	-	-	B	-	-	-	C	-
COPPER NITRATE	150°	C	A	A	A	A	-	A	-	A	-	-	-	A	-
COPPER NITRITE	70°	C	A	A	-	A	-	-	-	A	-	-	-	A	-
COPPER NITRITE, BASIC	70°	C	A	A	-	A	-	-	-	A	-	-	-	A	-
COPPER SULFATE	150°	C	A	A	A	A	-	A	-	A	A	A	A	A	U
COPPER SULFIDE	70°	C	A	A	-	A	-	-	-	A	-	-	-	A	-
CORN OIL		U	U	B	B	A	A	B	-	B	A	A	A	A	A
CORN SYRUP		A	A	A	A	A	A	A	-	A	A	A	A	A	-
COTTONSEED OIL		U	U	C	A	A	A	B	-	B	A	A	A	A	A
CREOSOTE, COAL TAR	70°	U	U	U	U	B	U	C	-	C	B	U	A	A	A
CREOSOTE OIL	70°	U	U	U	U	B	U	C	-	C	B	U	A	A	A
CRESOL	70°	U	U	C	C	C	-	C	-	C	U	C	B	A	-
CRESYLIC ACID	70°	U	U	C	C	C	-	C	-	C	U	C	B	A	-
CROTONALDEHYDE	70°	U	U	A	-	U	-	-	-	U	-	-	-	U	-
CROTONIC ACID		U	U	B	B	-	-	U	-	-	-	-	U	B	U
CROTONIC ALDEHYDE	70°	U	U	A	-	U	-	-	-	U	-	-	-	U	-
CRUDE OIL	70°	U	U	U	-	A	-	-	-	U	-	-	-	A	-
CRYSTALS OF VENUS	70°	-	-	A	A	B	-	B	-	B	-	-	-	-	-
CUMENE	70°	U	U	U	-	U	-	-	-	U	-	-	B	A	-
CUPRIC ACETATE	70°	-	-	A	A	B	-	B	-	B	-	-	-	-	-
CUPRIC CARBONATE	70°	C	A	A	-	A	-	-	-	A	-	-	-	A	-
CUPRIC CHLORIDE	150°	C	A	A	A	A	-	A	-	A	A	A	A	A	A
CUPRIC CYANIDE	70°	A	A	A	A	A	-	A	-	A	A	A	A	A	A
CUPRIC NITRATE	150°	C	A	A	A	A	-	A	-	A	-	-	-	A	-
CUPRIC NITRITE	70°	C	A	A	-	A	-	-	-	A	-	-	-	A	-
CUPRIC SULFATE	150°	C	A	A	A	A	-	A	-	A	A	A	A	A	U
CYCLOHEXANE	70°	U	U	U	U	A	-	U	A	U	B	U	A	A	B
CYCLOHEXANOL	70°	C	U	U	U	B	-	A	A	C	-	-	A	A	-
CYCLOHEXANONE	70°	U	U	C	C	U	U	U	C	U	-	-	U	U	-
CYCLOPENTANE	70°	U	U	U	-	U	-	-	B	U	-	-	-	A	-
CYCLOPENTANE METHYL	70°	U	U	U	-	B	-	-	-	U	-	-	-	A	-
CYCLOPENTANOL	70°	U	U	U	-	B	-	-	A	U	-	-	-	B	-
CYCLOPENTANONE	70°	U	U	U	-	U	-	-	C	U	-	-	-	-	-
CYCLOPENTYL ALCOHOL	70°	U	U	U	-	B	-	-	A	U	-	-	-	B	-
CYMENE	70°	U	U	U	-	U	-	U	U	U	-	-	B	A	-



Data

CYMOL	70°	U	U	U	-	U	-	U	U	U	-	-	B	A	-
D.D.T.IN KEROSENE	70°	U	U	U	U	A	-	B	-	U	-	-	-	A	-
DECAHYDRONAPHTHLENE	70°	U	U	C	-	U	-	U	C	U	-	-	-	A	-
DECALIN	70°	U	U	C	-	U	-	U	C	U	-	-	A	A	-
DECANAL	70°	U	U	A	-	U	-	-	-	U	-	-	-	U	-
DECANE	70°	U	U	-	-	B	-	U	-	U	B	B	A	A	A
DECANOL	70°	A	A	A	-	A	-	-	A	A	-	-	-	B	-
DECYL ALCOHOL	70°	A	A	A	-	A	-	-	A	A	-	-	-	B	-
DECYL ALDEHYDE	70°	U	U	A	-	U	-	-	-	U	-	-	-	U	-
DECYL BUTYL PHTHALATE	70°	U	U	A	-	U	-	-	-	U	-	-	-	C	-
DECYL CARBINOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	B	-
DECYL HYDRIDE	70°	U	U	-	-	B	-	U	-	U	B	B	A	A	A
DENATURED ALCOHOL	70°	A	A	A	A	A	A	A	-	A	C	A	A	A	U
DETERGENT ALKYLATE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
DETERGENT SOLUTIONS		B	B	A	A	A	A	A	-	A	U	A	A	A	U
DEVELOPING FLUIDS		A	B	B	B	A	-	A	-	A	-	A	A	A	-
DIACETIC ESTER	70°	C	C	B	B	U	-	C	A	U	-	B	U	U	-
DIACETONE	70°	U	B	A	A	B	-	B	A	-	B	-	U	U	U
DIACETONE ALCOHOL	70°	U	B	A	A	B	-	B	A	-	B	-	U	U	U
DIACETYLMETHANE		C	U	B	-	U	-	-	B	U	-	-	-	U	-
DIAMINE		-	-	A	A	B	-	B	-	B	U	C	-	-	-
DIAMYLAMINE	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-
DIAMYLENE	70°	U	U	U	-	C	-	-	-	U	-	-	-	A	-
DIAMYL NAPHTHALENE	70°	U	U	A	-	U	-	-	-	U	-	-	-	C	-
DIAMYL PHENOL	70°	U	U	U	-	U	-	-	A	U	-	-	-	A	-
DIBENZYL ETHER	70°	U	U	B	B	U	U	U	-	U	B	-	-	U	-
DIBENZYL SEBECATE	70°	-	-	B	B	-	-	U	-	-	B	C	C	B	-
DIBROMOBENZENE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
DIBROMOMETHANE	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
DIBROMOTETRAFLUOROETHANE		U	C	U	U	B	-	A	-	A	-	-	-	B	-
DIBUTYL AMINE	70°	B	B	A	A	B	-	U	-	C	-	C	U	U	-
DIBUTYL ETHER	70°	U	U	C	C	U	-	U	-	U	B	U	C	C	U
DIBUTYL PHTHALATE	70°	U	U	A	A	U	B	U	C	U	C	B	B	B	-
DIBUTYL SEBECATE	70°	U	U	B	B	U	-	U	-	U	U	B	B	B	U
DICALCIUM PHOSPHATE	70°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
DICHLOROACETIC ACID	70°	B	U	C	-	U	-	-	-	U	-	-	-	U	-
O-DICHLOROBENZENE	70°	U	U	U	U	U	-	U	-	U	U	U	B	A	-
1,2-DICHLOROBENZENE	70°	U	U	U	U	U	-	U	-	U	U	U	B	A	-
PARA-DICHLOROBENZOL	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
DICHLOROBUTANE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
DICHLORODIETHYL SULFIDE		A	-	A	A	-	-	A	-	A	-	A	-	-	-
DICHLORODIFLUOROMETHANE	70°	B	A	B	B	A	A	A	-	A	B	U	C	C	-
SYM-DICHLOROETHANE	70°	U	U	U	U	U	U	U	C	U	U	C	C	A	-
SYM-DICHLOROETHYLENE	70°	U	U	U	U	U	U	U	C	U	U	C	C	A	-
DICHLOROETHYLEETHER	70°	U	U	U	U	U	-	-	-	U	-	-	-	-	-
DICHLOROFLUOROMETHANE		U	-	U	U	U	B	B	-	U	-	U	-	U	-
DICHLOROHEXANE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
DICHLORO ISOPROPYL ETHER		U	U	C	C	U	-	U	-	U	B	U	C	C	B
DICHLOROMETHANE	70°	U	U	U	U	U	-	U	C	U	U	-	B	A	-
DICHLOROPENTANE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
DICHLOROPROPANE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
DICHLOROTETRAFLUOROETHANE		A	A	A	A	A	A	A	-	A	A	U	B	B	-

Data

DICYCLOHEXYLAMINE		U	U	-	-	C	-	-	-	-	-	-	-	-	-	-	-	-	-
DIDODECYL ETHER		U	U	B	-	U	-	-	-	U	-	-	-	-	-	-	-	-	-
DIESEL OIL	150°	U	U	U	U	A	A	B	-	B	B	U	A	A	A				
DIETHANOLAMINE	70°	B	B	A	-	B	-	-	A	C	-	-	-	-	-	-	-	-	-
DIETHYLACETALDEHYDE	70°	U	U	A	-	U	-	-	-	U	-	-	-	U	-				
DIETHYLAMINE	70°	B	A	B	B	B	-	B	B	C	C	B	U	U	U				
DIETHYL CARBINOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	A	-				
DIETHYLENE DIOXIDE	70°	U	U	B	B	U	-	U	-	U	-	-	-	C	U				
DIETHYLENE GLYCOL	150°	A	A	A	A	A	A	A	A	A	U	B	A	A	U				
DIETHYLENE GLYCOL MONOBUTYL ETHER		-	-	A	A	A	-	B	A	B	-	-	-	A	-				
DIETHYLENE GLYCOL MONOMETHYL ETHER		U	U	C	-	U	-	-	-	U	-	-	-	-	-				
DIETHYLENE TRIAMINE	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-				
DIETHYL ETHER	70°	U	U	C	C	C	B	U	-	U	B	U	U	U	U				
DI (2-ETHYLHEXYL) PHTHALATE		U	U	B	B	C	B	U	C	U	-	C	B	B	-				
DI (2-ETHYLHEXYL) SEBACATE		U	U	B	B	U	C	U	-	U	B	C	C	B	U				
DIETHYL KETONE	70°	U	U	B	-	U	-	-	C	U	-	-	-	U	-				
DIETHYL OXALATE	70°	A	A	A	A	U	U	U	A	U	A	-	-	A	-				
DIETHYL OXIDE	70°	U	U	C	C	C	B	U	-	U	B	U	U	U	U				
DIETHYL PHTHALATE	70°	U	U	A	-	U	-	U	B	U	-	-	-	C	-				
DIETHYL SEBACATE	70°	U	U	A	-	U	-	U	B	U	-	-	-	C	-				
DIETHYL SULFATE	70°	U	U	C	-	U	-	-	A	U	-	-	-	B	-				
DIETHYL TRIAMINE	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-				
PARA-DIHYDROXYBENZENE	70°	B	B	-	-	C	-	-	-	-	-	-	B	U	-				
DIHYDROXY DIETHYL ETHER	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-				
DIHYDROXY ETHYLAMINE	70°	B	B	A	-	B	-	-	A	C	-	-	-	-	-				
DIHYDROXY SUCCINIC ACID	150°	A	B	B	B	A	B	B	-	A	A	A	A	A	-				
DIISOBUTYLENE	70°	U	U	U	-	B	-	C	-	C	-	U	C	A	-				
DIISOBUTYLKETONE	70°	U	U	B	B	U	-	-	-	U	-	-	-	U	-				
DIISODECYL ADIPATE	70°	U	U	A	-	U	-	-	-	U	-	-	-	C	-				
DIISODECYL PHTHALATE	70°	U	U	A	-	U	-	-	-	U	-	-	-	C	-				
DIISOOCTYL ADIPATE	70°	U	U	A	-	U	-	-	-	U	-	-	-	C	-				
DIISOOCTYL PHTHALATE	70°	U	U	A	-	U	-	-	-	U	-	-	-	C	-				
DIISOPROPANOL AMINE	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-				
DIISOPROPYL AMINE	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-				
DIISOPROPYL BENZENE	70°	U	U	U	U	U	-	U	-	U	-	-	B	A	-				
DII+A511SOPROPYL ETHER	70°	U	U	C	U	B	-	B	-	B	B	-	-	U	U				
DIISOPROPYLIDENE ACETONE	70°	-	-	B	B	-	-	-	-	-	-	-	-	-	-				
DIISOPROPYL KETONE	70°	U	U	A	A	U	-	U	-	U	-	-	U	U	-				
DILAURYL ETHER	70°	U	U	B	-	U	-	-	-	U	-	-	-	-	-				
1,2-DIMETHOXYETHANE		U	U	C	C	C	-	U	-	U	B	U	C	U	U				
DIMETHYL		U	U	U	U	A	-	B	-	B	B	U	A	A	A				
DIMETHYL AMINE	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-				
DIMETHYL ANILINE	70°	U	U	U	U	C	-	U	-	U	-	U	U	U	-				
DIMETHYLBENZENE	70°	U	U	U	U	U	U	U	U	U	U	U	B	A	-				
1,2-DIMETHYLBENZENE		U	U	U	U	U	U	U	U	U	U	U	B	A	-				
1,3-DIMETHYLBENZENE		U	U	U	U	U	U	U	U	U	U	U	B	A	-				
1,4-DIMETHYLBENZENE		U	U	U	U	U	U	U	U	U	U	U	B	A	-				
2,2-DIMETHYLBUTANE		U	U	U	-	A	-	-	B	U	-	-	-	A	-				
DIMETHYL CARBINOL	70°	A	A	A	A	A	A	A	A	A	U	A	A	A	U				
DIMETHYL ETHER	70°	U	U	C	-	B	-	-	-	U	-	-	-	-	-				
DIMETHYL FORMAMIDE		-	-	-	-	B	-	C	-	C	-	B	-	U	-				
2,6-DIMETHYL-4-HEPTANONE	70°	U	U	B	B	U	-	-	-	U	-	-	-	U	-				

Data

DIMETHYL KETONE	70°	B	B	A	A	U	U	B	A	B	U	B	U	U	U
DIMETHYL METHANE		U	U	U	U	A	A	A	-	A	B	U	B	A	A
2,4-DIMETHYL PENTANONE-3		U	U	A	A	U	-	U	-	U	-	-	U	U	-
DIMETHYL PHENOL	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
DIMETHYL PHTHALATE	70°	U	U	B	B	U	-	U	A	U	-	-	B	B	-
DIMETHYL SULFATE	70°	U	U	C	-	U	-	-	A	U	-	-	-	B	-
DIMETHYL SULFIDE	70°	U	U	C	-	U	-	-	B	U	-	-	-	-	-
DINITROBENZENE	70°	U	U	C	-	U	-	-	-	U	-	-	-	A	-
DINITROBENZOL	70°	U	U	C	-	U	-	-	-	U	-	-	-	A	-
DINITROTOLUENE	70°	U	U	U	U	U	-	U	-	U	-	-	-	C	-
DINITROTOLUOL	70°	U	U	U	U	U	-	U	-	U	-	-	-	C	-
DIOCTYL ADIPATE	70°	U	U	A	-	U	-	-	C	U	-	-	-	C	-
DIOCTYL AMINE	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-
DIOCTYL PHTHALATE		U	U	B	B	C	B	U	C	U	-	C	B	B	-
DIOCTYL SEBACATE		U	U	B	B	U	C	U	-	U	B	C	C	B	U
DIOXANE		U	U	B	B	U	-	U	-	U	-	-	C	U	-
DIOXOLANE		U	U	C	B	U	-	-	-	U	-	-	-	-	-
DIPENTENE		-	-	-	-	B	-	-	-	-	-	-	C	A	-
DIPENTYLAMINE	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-
DIPHENYL		U	U	U	U	U	-	U	-	U	-	-	B	A	-
DIPHENYL ETHER		-	-	-	A	-	-	-	-	-	-	C	B	A	-
DIPHENYL OXIDE		-	-	-	A	-	-	-	-	-	-	C	B	A	-
DIPHENYL PHTHALATE	70°	U	U	A	-	U	-	-	-	U	-	-	-	C	-
DIPROPYLAMINE	70°	B	B	A	-	B	-	-	B	C	-	-	-	-	-
DIPROPYLENE GLYCOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
DIPROPYL KETONE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
DIPROPYLMETHANE	70°	U	U	U	-	A	-	-	A	U	-	-	-	A	-
DISODIUM PHOSPHATE	70°	A	A	A	A	A	-	B	A	A	A	U	A	A	A
DIVINYL BENZENE	70°	U	U	U	-	U	-	-	U	U	-	-	-	A	-
DIVINYL ETHER	70°	U	U	B	-	U	-	-	-	U	-	-	-	-	-
DIVINYL OXIDE	70°	U	U	B	-	U	-	-	-	U	-	-	-	-	-
D.M.P.	70°	U	U	U	-	U	-	-	-	U	-	-	-	U	-
N-DODECANOL		A	A	A	-	A	-	-	-	A	-	-	-	B	-
DODECYL ALCOHOL		A	A	A	-	A	-	-	-	A	-	-	-	B	-
DODECYL BENZENE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
DODECYL TOLUENE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
DOW-PER	70°	U	U	U	U	C	B	U	C	U	U	B	B	A	-
DOWTHERM A		U	U	U	U	U	U	U	C	U	B	B	A	A	-
DOWTHERM E		U	U	U	U	U	U	U	C	U	B	B	A	A	-
DOWTHERM S.R.T.	70°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
EARTH PITCH	175°	U	U	U	U	B	A	B	-	C	B	U	B	A	B
ENANTHALDEHYDE	70°	U	U	A	-	U	-	-	C	U	-	-	-	-	-
EPICHLOROHYDRIN		U	U	B	B	-	-	-	-	-	-	-	U	U	-
EPOXYETHANE		-	-	C	C	U	-	U	-	U	-	C	U	U	-
EPSOM SALTS	150°	B	B	A	A	A	A	A	A	A	-	A	A	A	U
ETHANAMIDE		C	C	A	A	A	-	B	-	B	U	B	A	B	U
ETHANE		U	U	U	U	A	-	B	-	B	B	U	A	A	A
ETHANETHIOL		U	U	U	U	U	U	U	-	-	-	-	-	A	-
ETHANOIC ACID - 30%	150°	C	C	A	A	C	C	B	A	B	C	A	B	C	U
ETHANOL	70°	A	A	A	A	A	A	A	-	A	B	A	A	A	U
ETHANOLAMINE	70°	B	B	A	B	B	B	B	A	B	C	B	U	U	U
ETHENE		-	-	-	-	A	-	-	-	-	-	-	A	A	-

Data

ETHER	70°	U	U	C	C	C	B	U	-	U	B	U	U	U	U
ETHINE	70°	B	B	A	A	A	-	B	-	B	-	B	-	A	-
ETHYL ACETATE	70°	U	U	B	B	U	-	C	B	U	-	B	U	U	-
ETHYLACETIC ACID	70°	C	U	C	-	C	-	C	A	B	-	-	-	-	-
ETHYL ACETOACETATE	70°	C	C	B	B	U	-	C	A	U	-	B	U	U	-
ETHYLACETONE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
ETHYL ACRYLATE	70°	U	U	B	B	U	U	-	B	U	-	B	U	U	-
ETHYL ALCOHOL	70°	A	A	A	A	A	A	A	-	A	B	A	A	A	-
ETHYL ALDEHYDE	70°	C	U	A	A	U	A	C	-	C	U	A	U	U	U
ETHYL ALUMINUM DICHLORIDE	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
ETHYLAMINE	70°	C	C	B	-	C	-	-	A	C	-	-	-	-	-
ETHYLBENZENE	70°	U	U	U	U	U	U	C	U	U	-	A	A	-	-
ETHYL BUTANOL	70°	A	A	B	C	A	-	B	A	B	U	B	A	A	U
ETHYLBUTRALDEHYDE	70°	U	U	A	-	U	-	-	-	U	-	-	-	U	-
ETHYL BUTYL ACETATE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
ETHYL BUTYL ALCOHOL	70°	A	A	B	C	A	-	B	A	B	U	B	A	A	U
ETHYL BUTYL AMINE	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-
ETHYL BUTYL ETHER		U	U	B	-	U	-	B	-	U	-	-	-	C	-
ETHYL BUTYL KETONE	70°	U	U	B	-	U	-	-	C	U	-	-	-	U	-
ETHYL BUTYRALDEHYDE	70°	U	U	A	-	U	-	-	-	U	-	-	-	U	-
ETHYL CELLOSOLVE	70°	-	-	B	B	-	-	-	-	-	-	-	U	U	-
ETHYL CELLULOSE		B	B	B	B	B	-	B	-	B	B	C	U	U	U
ETHYL CHLORIDE		U	U	A	A	A	B	B	-	C	B	U	A	A	C
ETHYL CHLOROCARBONATE		U	U	-	-	-	-	C	-	C	-	-	B	A	-
ETHYL CHLOROFORMATE		U	U	-	-	-	-	C	-	C	-	-	B	A	-
ETHYL DICHLORIDE	70°	U	U	U	-	U	-	-	B	U	-	-	-	B	-
ETHYLDIMETHYLMETHANE	70°	U	U	U	-	A	-	-	-	U	-	-	-	A	-
ETHYLENE		-	-	-	-	A	-	-	-	-	-	-	A	A	-
ETHYLENE ALCOHOL	150°	A	A	A	A	A	A	A	A	A	B	A	A	A	U
ETHYLENE BROMIDE	70°	U	U	U	U	U	-	U	C	U	-	-	-	B	-
ETHYLENE CHLORIDE		U	U	U	U	U	U	C	U	U	C	C	A	-	-
ETHYLENE CHLOROHYDRIN		B	B	-	-	U	-	B	-	B	-	C	B	A	-
ETHYLENE DIAMINE	70°	B	B	A	A	A	A	A	B	B	-	A	U	U	-
ETHYLENE DIBR+A595OMIDE	70°	U	U	U	U	U	-	U	C	U	-	-	-	B	-
ETHYLENE DICHLORIDE	70°	U	U	U	U	U	U	C	U	U	C	C	A	-	-
ETHYLENE GLYCOL	150°	A	A	A	A	A	A	A	A	A	B	A	A	A	U
ETHYLENE GLYCOL DIMETHYLETHER		U	U	C	C	C	-	U	-	U	B	U	C	U	U
ETHYLENE GLYCOL MONOBUTYL ETH+A611ER	70°	U	U	A	A	A	-	B	A	B	-	-	U	U	-
ETHYLENE GLYCOL MONOMETHYL ETHER		U	U	B	B	B	-	B	-	C	-	-	-	U	-
ETHYLENE OXIDE		-	-	C	C	U	-	U	-	U	-	C	U	U	-
ETHYLENE TRICHLORIDE		U	U	U	U	U	U	U	U	U	U	U	U	A	-
ETHYL ETHER	70°	U	U	C	C	C	B	U	-	U	B	U	U	U	U
ETHYL FORMATE	70°	U	U	B	B	U	U	B	A	U	-	-	A	A	-
2-ETHYLHEXALDEHYDE		U	U	A	-	U	-	-	-	U	-	-	-	U	-
ETHYL HEXANOL	70°	B	B	A	A	B	-	A	A	A	U	B	B	A	U
ETHYL HEXOIC ACID	70°	C	U	C	-	C	-	C	A	B	-	-	-	-	-
ETHYLHEXYL ACETATE	70°	U	U	B	-	U	-	-	B	U	-	-	-	U	-
ETHYL HEXYL ALCOHOL	70°	B	B	A	A	B	-	A	A	A	U	B	B	A	U
ETHYL HYDRIDE		U	U	U	U	A	-	B	-	B	B	U	A	A	A
ETHYL HYDROXIDE		U	U	U	U	A	-	B	-	B	B	U	A	A	A
ETHYL IODIDE	70°	U	U	U	-	U	-	A	A	A	-	-	-	B	-
ETHYL ISOBUTYL ETHER	70°	U	U	B	-	U	-	-	-	U	-	-	-	-	-

Data

ETHYL MERCAPTAN		U	U	U	U	U	U	U	-	-	-	-	-	A	-
ETHYL METHYL KETONE	70°	U	U	B	B	U	U	U	U	U	U	U	U	U	U
7-ETHYL-2-METHYL-4-UNDECANOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	C	-
ETHYL OXALATE	70°	A	A	A	A	U	U	U	A	U	A	-	-	A	-
ETHYL OXIDE	70°	U	U	C	C	C	B	U	-	U	B	U	U	U	U
ETHYL PENTACHLOROBENZENE		U	U	U	U	C	C	U	-	U	C	-	B	A	-
ETHYL PHTHALATE	70°	U	U	A	-	U	-	U	B	U	-	-	-	C	-
ETHYL PROPIONYL	70°	U	U	B	-	U	-	-	C	U	-	-	-	U	-
ETHYL PROPYL ETHER	70°	U	U	B	-	U	-	-	-	U	-	-	-	-	-
ETHYL PROPYL KETONE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
ETHYL SILICATE	70°	C	C	A	-	A	-	A	A	-	-	-	-	-	-
ETHYL SULFATE	70°	U	U	C	-	U	-	-	A	U	-	-	-	B	-
ETHYL SULFHYDRATE		U	U	U	U	U	U	U	-	-	-	-	-	A	-
ETHYNE	70°	B	B	A	A	A	-	B	-	B	-	B	-	A	-
ESSENCE OF MIRBANE		U	U	U	U	U	U	U	C	U	U	U	U	B	U
ESSENCE OF MYRBANE		U	U	U	U	U	U	U	C	U	U	U	U	B	U
EX-TRI	70°	U	U	U	U	U	U	U	U	U	U	U	U	A	-
FATTY ACIDS	70°	C	C	U	U	B	-	B	-	B	-	C	-	A	-
FERMENTATION ALCOHOL		U	U	U	U	A	-	B	-	B	B	U	A	A	A
FERRIC BROMIDE	150°	A	A	A	A	A	-	A	-	A	-	-	-	A	-
FERRIC CHLORIDE	150°	A	A	A	A	A	A	A	A	A	A	A	-	A	-
FERRIC NITRATE		A	A	A	A	A	A	A	-	A	-	C	A	A	A
FERRIC PERCHLORIDE	150°	A	A	A	A	A	A	A	A	A	A	A	-	A	-
FERRIC SULFATE	150°	A	A	A	A	A	A	A	A	A	-	B	A	A	A
FERRIC TRIBROMIDE	150°	A	A	A	A	A	-	A	-	A	-	-	-	A	-
FERRIC TRICHLORIDE	150°	A	A	A	A	A	A	A	A	A	A	A	-	A	-
FERROUS ACETATE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
FERROUS CHLORIDE	150°	A	A	A	A	A	A	A	A	A	A	A	-	A	-
FERROUS HYDROXIDE	70°	U	B	A	-	B	-	-	-	B	-	-	-	U	-
FERROUS SULFATE	150°	A	A	A	A	A	A	A	A	A	-	B	A	A	A
FERROUS SULFIDE	150°	A	A	A	A	A	-	-	-	A	-	-	-	A	-
FILTER ALUM	150°	A	B	A	A	A	-	A	A	A	-	A	A	A	U
FISH OILS		U	U	A	A	A	-	B	-	B	A	B	A	A	A
FLAXSEED OIL		U	U	B	B	A	-	B	A	B	B	-	A	A	A
FLOWERS OF SULFUR	250°	U	U	A	A	U	C	A	-	A	U	A	A	A	U
FLUOBORIC ACID	150°	A	B	A	A	-	A	A	A	-	-	-	-	-	-
FLUORINATED CYCLIC ETHERS		-	-	A	A	-	-	-	-	-	-	-	-	-	-
FLUORINE (GAS)	70°	U	U	U	U	U	-	U	-	U	-	-	-	U	-
FLUORINE (LIQUID)		-	-	C	C	-	-	-	-	-	-	-	-	B	-
FLUOROBENZENE		U	U	U	U	U	-	U	-	U	-	U	B	A	-
FLUOROBORIC ACID	150°	A	B	A	A	A	-	A	A	A	-	-	-	-	-
FLUOROCARBON OILS		-	U	A	A	A	-	A	-	A	-	-	B	B	-
FLUOROLUBE		-	U	A	A	A	-	A	-	A	-	-	B	B	-
FLUROSILICIC ACID	150°	A	B	A	A	A	-	B	B	A	-	U	-	A	-
FLUOSILICIC ACID	150°	A	B	A	A	A	-	B	B	A	-	U	-	A	-
FORMALDEHYDE	70°	B	B	A	A	A	B	B	A	A	U	-	-	A	-
FORMALIN	70°	B	B	A	A	A	B	B	A	A	U	-	-	A	-
FORMIC ACID	70°	B	B	A	A	B	B	B	A	A	U	B	C	C	-
FORMIC ALDEHYDE	70°	B	B	A	A	A	B	B	A	A	U	-	-	A	-
FORMONITRILE		B	B	B	A	B	-	B	-	A	-	-	B	A	U
FREON 11		U	U	U	U	A	-	C	-	U	U	U	B	A	-
FREON 12		B	A	B	B	A	A	A	-	A	B	U	C	C	-

Data

FREON 13		A A A A	A A A - A -	- - A -
FREON 13-B1		A A A A	A - A - A A	U - A -
FREON 21		U U U U	U B B - U -	U - U -
FREON 22		B B A A	U A A - A U	U U U -
FREON 31		B B A A	U - A - B -	- - U -
FREON 32		A A A A	A - A - A -	- - C -
FREON 112		U U U U	B - B - B -	- - A -
FREON 113		C B U U	A A A - A B	U U B -
FREON 114		A A A A	A A A - A A	U B B -
FREON 114-B2		U C U U	B - A - A -	- - B -
FREON 115		A A A A	A - A - A -	- - B -
FREON 142-B		A A A A	A - A - A -	- - U -
FREON 152-A		A A A A	A - A - C -	- - U -
FREON 218		A A A A	A - A - A -	- - A -
FREON 502		A A - -	B - A - - -	- - B -
FREON C-316		A A A A	A - A - A -	- - - -
FREON C-318		A A A A	A - A - A -	- - A -
FREON BF SOLVENT		U U U U	B - B - B -	- - A -
FREON MF SOLVENT		U U U U	A - C - U U	U B A -
FREON TA SOLVENT		A A A A	A - A - A A	A - C -
FREON TC SOLVENT		U B A B	A - A - A A	U - A -
FREON TF SOLVENT		C B U U	A A A - A B	U U B -
FREON TMC SOLVENT		B C B B	B - B - B B	C - A -
FREON T-P35 SOLVENT		A A A A	A - A - A A	A - A -
FREON T-WD602 SOLVENT		C B A B	B - B - B A	U - A -
FUEL OIL		U U U U	A A B - B B	U A A A
FUEL A (ASTM)		U U U U	A - B - - -	- - A -
FUEL B (ASTM)		U U U U	A - C - - -	- - A -
FUMARIC ACID		A A U -	A - B - B -	B A A U
FURAN		U U C C	U - U A U -	- - - -
FURF+A714URALDEHYDE		C C B B	U U B A B -	C - U -
FURFURAL	70°	C C B B	U U B A B -	C - U -
FURFURAN		U U C C	U - U A U -	- - - -
FURFURYL ALCOHOL	70°	- - C -	- - - A - -	- - B -
FURYL CARBINOL	70°	- - C -	- - - A - -	- - B -
GALLIC ACID	70°	A B B B	B - C A B U	- A A U
GALLOTANNIC ACID	150°	A C B A	B - A - A A	B A A U
GASOLINE	70°	U U U U	A A B B C A	U A A -
GAULTHERIA OIL		- - B B	- - U - - -	- - - -
GELATIN		A A A A	A A A - A A	A A A U
GENETRON 11		U U U U	A - C - U U	U B A -
GENETRON 12		B A B B	A A A - A B	U C C -
GENETRON 13		A A A A	A A A - A -	- - A -
GENETRON 113		C B U U	A A A - A B	U U B -
GENETRON 114		A A A A	A A A - A A	U B B -
GDME		U U C C	C - U - U B	U C U U
GLAUBERS SALT		- U B B	- - - - - -	- A A U
GLUCONIC ACID	70°	U U C -	C - - A B -	- - - -
GLUCOSE		A A A A	A A A - A A	A A A -
GLUE		A A A A	A A A - A A	A A A -
GLYCERINE	70°	A A A A	A A A A A A	A A A U
GLYCERYL TRIACETATE		B C A A	B - B - B U	- U U U

Data

GLYCOL	150°	A	A	A	A	A	A	A	A	A	B	A	A	A	U
GLYCOL CHLOROHYDRIN		B	B	-	-	U	-	B	-	B	-	C	B	A	-
GLYCOL DIMETHYL ETHER		U	U	C	C	C	-	U	-	U	B	U	C	U	U
GLYCOGENIC ACID	70°	U	U	C	-	C	-	-	A	B	-	-	-	-	-
GLYCONIC ACID	70°	U	U	C	-	C	-	-	A	B	-	-	-	-	-
GLYME		U	U	C	C	C	-	U	-	U	B	U	C	U	U
GRAIN ALCOHOL	70°	A	A	A	A	A	A	A	-	A	B	A	A	A	U
GRAY ACETATE	70°	A	B	A	A	B	-	B	A	B	-	-	U	U	-
GREASE		U	U	U	-	A	-	-	-	U	-	-	-	A	-
GREEN COPPERAS	150°	A	A	A	A	A	A	A	A	A	-	B	A	A	A
GREEN SULFATE LIQUOR	150°	B	B	B	A	B	A	B	-	B	A	A	A	A	A
GREEN SULFITE LIQUOR	70°	B	B	B	B	B	B	B	-	B	-	U	B	A	U
GREEN VITRIOL	150°	A	A	A	A	A	A	A	A	A	-	B	A	A	A
HA+A771LOWAX OIL		U	U	U	U	U	-	U	-	U	-	U	A	A	-
HARTSHORN		A	A	A	A	U	B	A	-	-	-	-	-	-	-
HENDECANOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	B	-
HEPAR CALCIS	150°	B	B	A	A	B	B	A	A	A	A	B	A	A	U
HEPTALDEHYDE	70°	U	U	A	-	U	-	-	C	U	-	-	-	-	-
HEPTANAL	70°	U	U	A	-	U	-	-	C	U	-	-	-	-	-
HEPTANE	70°	U	U	U	-	A	-	-	A	U	-	-	-	A	-
HEPTANE CARBOXYLIC ACID	70°	U	U	C	-	C	-	-	A	B	-	-	-	-	-
HEPTANOL-2	70°	A	A	A	-	A	-	-	-	A	-	-	-	U	-
2-HEPTANONE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
3-HEPTANONE	70°	U	U	B	-	U	-	-	C	U	-	-	-	U	-
4-HEPTANONE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
HEPTYL CARBINOL	70°	B	B	A	A	B	-	A	A	A	U	B	B	A	U
HEXADECANOIC ACID	70°	U	C	A	B	A	B	B	-	B	A	-	A	A	-
HEXAHYDROBENZENE	70°	U	U	U	U	A	-	U	A	U	B	U	A	A	B
HEXAHYDROPHENOL	70°	C	U	U	U	B	-	A	A	C	-	-	A	A	-
HEXAHYDROPYRIDINE		U	U	U	U	U	-	U	-	U	-	-	U	U	-
HEXAHYDROTOLUENE	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
HEXALDEHYDE	70°	U	U	B	A	U	-	A	-	-	B	B	-	U	-
HEXAMETHYLENE	70°	U	U	U	U	A	-	U	A	U	B	U	A	A	B
HEXANAPHTHENE	70°	U	U	U	U	A	-	U	A	U	B	U	A	A	B
HEXANE	70°	U	U	U	U	A	A	B	A	C	B	U	A	A	A
HEXANEDIOIC ACID	70°	-	-	-	-	A	-	-	-	-	-	-	A	-	-
HEXANOL	70°	A	A	B	C	A	-	B	A	B	U	B	A	A	U
HEXANONE-3		U	U	B	-	U	-	-	-	U	-	-	-	U	-
1-HEXENE		U	U	U	U	B	-	B	A	B	A	U	A	A	A
HEXYL ALCOHOL	70°	A	A	B	C	A	-	B	A	B	U	B	A	A	U
HEXYL ALCOHOL, PSEUDO	70°	A	A	B	C	A	-	B	A	B	U	B	A	A	U
HEXYLAMINE	70°	B	B	A	-	B	-	-	B	C	-	-	-	-	-
HEXYLENE	70°	U	U	U	U	B	-	B	A	B	A	U	A	A	A
HEXYLENE GLYCOL	70°	A	A	A	-	A	-	-	A	A	-	-	-	A	-
HEXYL METHYL KETONE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
HI-TRI	70°	U	U	U	U	U	U	U	U	U	U	U	U	A	-
HOOF OIL		U	U	B	B	A	-	-	-	-	-	B	A	A	A
HYDRARGYRUM		A	A	A	A	A	A	A	-	A	A	-	-	A	-
HYDRAULIC OIL (PETROLEUM)		U	U	U	U	A	A	B	A	B	A	B	A	A	A
HYDRAZINE		-	-	A	A	B	-	B	-	B	U	C	-	-	-
HYDRAZINE, ANHYDROUS		-	-	A	A	B	-	B	-	B	U	C	-	-	-
HYDRAZINE, BASE		-	-	A	A	B	-	B	-	B	U	C	-	-	-

Data

HYDROBROMIC ACID	150°	A	U	A	A	U	-	C	B	A	U	U	C	A	U
HYDROCHLORIC ACID 37%	70°	B	C	B	B	C	U	C	B	A	U	B	B	A	U
HYDROCHLORIC ACID 37%	125°	B	U	C	C	U	U	U	B	U	U	U	U	A	U
HYDROCYANIC ACID		B	B	B	A	B	-	B	-	A	-	-	B	A	U
HYDROFLUORIC ACID (CONC.)	70°	U	U	B	B	U	-	C	B	A	U	U	U	A	U
HYDROFLUORIC ACID (CONC.)	125°	U	U	U	U	U	-	U	-	C	U	U	U	B	U
HYDROFLUORIC ACID, ANHYDROUS		U	U	B	B	-	-	-	-	A	-	U	-	-	-
HYDROFLUOSILICIC ACID	150°	A	B	A	A	A	-	B	B	A	-	U	-	A	-
HYDROFLUOSILICIC ACID	150°	A	B	A	A	A	-	B	B	A	-	U	-	A	-
HYDROGEN BROMIDE		A	U	A	A	U	-	C	B	A	U	U	C	A	U
HYDROGEN CARBOXYLIC ACID	70°	B	B	A	A	B	B	B	A	A	U	B	C	C	-
HYDROGEN CYANIDE		B	B	B	A	B	-	B	-	A	-	-	B	A	U
HYDROGEN DIOXIDE (10%)	70°	U	U	C	-	U	-	U	A	C	-	-	-	A	-
HYDROGEN DIOXIDE (OVER 10%)	70°	U	U	U	-	U	-	-	-	U	-	A	B	A	-
HYDROGEN FLUORIDE	125°	U	U	U	U	U	-	U	-	C	U	U	U	B	U
HYDROGEN GAS		B	B	A	A	A	-	A	-	A	A	C	C	A	B
HYDROGEN PEROXIDE (10%)		U	U	C	-	U	-	U	A	C	-	-	-	A	-
HYDROGEN PEROXIDE (90%)		U	U	U	-	U	-	-	-	U	-	A	B	A	-
HYDROGEN SULFIDE (WET)	70°	U	U	A	A	U	B	A	-	B	-	C	C	U	U
HYDROGEN SULFIDE (WET)	150°	U	U	A	A	U	B	B	-	C	-	C	C	U	U
HYDROQUINONE		B	B	-	-	C	-	-	-	-	-	-	B	U	-
HYDROXY BENZENE	150°	U	U	B	B	U	-	C	A	C	U	U	B	A	-
ORTHO-HYDROXYBENZOIC ACID		A	B	A	A	A	-	-	-	-	-	-	A	A	-
1-HYDROXY-2,4-DIAMYL BENZENE	70°	U	U	U	-	U	-	-	A	U	-	-	-	A	-
2-HYDROXYETHYLAMINE	70°	B	B	A	B	B	B	B	A	B	C	B	U	U	U
HYDROXYETHYL-ETHYLENEDIAMINE	70°	B	B	A	-	B	-	-	-	B	-	-	-	-	-
ALPHA-HYDROXYISOBUTYRONITRILE	70°	C	C	A	-	U	-	-	A	C	-	-	-	U	-
4, HYDROXY-2-KETO-4-METHYLPENTANE	70°	U	B	A	A	B	-	B	A	-	B	-	U	U	U
HYDROXYMETHYLBENZENE	70°	U	U	C	C	C	-	C	-	C	U	C	B	A	-
4, HYDROXY-4-METHYLPENTANONE-2		U	B	A	A	B	-	B	A	-	B	-	U	U	U
HYDROXY-1,2,3-PROPANE TRICARBOXYLIC ACID	150°	A	A	A	A	A	A	A	-	A	A	A	A	A	-
ALPHA-HYDROXYPROPIONIC ACID	70°	B	B	A	A	B	-	B	-	A	-	A	A	A	-
2-HYDROXYPROPYLAMINE	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-
HYDROXYSUCCINIC ACID	150°	A	B	U	U	A	-	B	-	B	-	B	A	A	U
HYPNONE		C	U	A	A	U	U	U	-	U	U	-	U	U	U
HYPOCHLOROUS ACID		B	B	B	B	U	B	-	-	-	-	-	-	A	-
IODINE		-	-	-	-	-	-	-	A	A	-	-	-	-	-
IODINE PENTAFLUORIDE		U	U	U	U	U	U	U	-	U	U	U	U	U	U
IDOETHANE	70°	U	U	U	-	U	-	A	A	A	-	-	-	B	-
IODOFORM		-	-	A	A	-	-	-	-	-	-	-	-	-	-
IRON ACETATE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
IRON BROMIDE	150°	A	A	A	A	A	-	A	-	A	-	-	-	A	-
IRON CHLORIDE	150°	A	A	A	A	A	A	A	A	A	A	A	-	A	-
IRON DICHLORIDE	150°	A	A	A	A	A	A	A	A	A	A	A	-	A	-
IRON HYDROXIDE	70°	U	B	A	-	B	-	-	-	B	-	-	-	U	-
IRON NITRATE		A	A	A	A	A	A	A	-	A	-	C	A	A	A
IRON PERCHLORIDE	150°	A	A	A	A	A	A	A	A	A	A	A	-	A	-
IRON PROTOCHLORIDE	150°	A	A	A	A	A	A	A	A	A	A	A	-	A	-
IRON SULFATE	150°	A	A	A	A	A	A	A	A	A	-	B	A	A	A
IRON SULFIDE	150°	A	A	A	A	A	-	-	-	A	-	-	-	A	-
IRON TRICHLORIDE	150°	A	A	A	A	A	A	A	A	A	A	A	-	A	-
IRON VITRIOL	150°	A	A	A	A	A	A	A	A	A	-	B	A	A	A



Data

ISOAMYL ACETATE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
ISOAMYL ALCOHOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
ISOAMYL BROMIDE	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
ISOAMYL BUTYRATE	70°	U	U	C	-	U	-	-	-	U	-	-	-	U	-
ISOAMYL CHLORIDE	70°	U	U	C	-	U	-	-	-	U	-	-	-	B	-
ISOAMYL ETHER	70°	U	U	B	-	U	-	-	-	U	-	-	-	-	-
ISOAMYL PHTHALATE	70°	U	U	A	-	U	-	-	-	U	-	-	-	C	-
ISOBUTANE	70°	U	U	U	-	A	-	-	-	U	-	-	-	A	-
ISOBUTANOL	70°	A	A	A	A	A	-	A	-	A	U	A	B	A	U
ISOBUTENE	70°	U	U	U	U	B	-	C	-	C	-	-	B	A	-
ISOBUTYL ACETATE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
ISOBUTYL ALCOHOL	70°	A	A	A	A	A	-	A	-	A	U	A	B	A	U
ISOBUTYL ALDEHYDE	70°	C	-	A	-	U	-	-	-	-	-	-	-	U	-
ISOBUTYL AMINE	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-
ISOBUTYL BROMIDE	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
ISOBUTYL CARBINOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
ISOBUTYL CHLORIDE	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
ISOBUTYLENE	70°	U	U	U	U	B	-	C	-	C	-	-	B	A	-
ISOBUTYL ETHER	70°	U	U	B	-	U	-	-	-	U	-	-	-	-	-
ISOBUTYRALDEHYDE	70°	C	-	A	-	U	-	-	-	-	-	-	-	U	-
ISOOCTANE	70°	U	U	U	U	A	A	C	A	B	B	U	A	A	A
ISOPENTANE	70°	U	U	U	-	A	-	-	-	U	-	-	-	A	-
ISOPHORONE		-	-	A	A	U	-	-	-	-	B	-	-	U	-
ISOPROPANOL	70°	A	A	A	A	A	A	A	A	A	U	A	A	A	U
ISOPROPANOLAMINE	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-
ISOPROPYL ACETATE	70°	U	U	B	A	U	-	U	-	U	A	-	-	U	U
ISOPROPYL ALCOHOL	70°	A	A	A	A	A	A	A	A	A	U	A	A	A	U
ISOPROPYL AMINE	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-
ISOPROPYL BENZENE	70°	U	U	U	-	U	-	-	-	U	-	-	B	A	-
ISOPROPYL CHLORIDE	70°	U	U	U	U	U	-	-	-	U	-	-	B	A	-
ISOPROPYL ETHER	70°	U	U	C	U	B	-	B	-	B	B	-	-	U	U
ISOPROPYLIDENEACETONE	70°	U	U	B	B	U	-	U	C	U	-	U	U	U	-
ISOPROPYL TOLUENE	70°	U	U	U	-	U	-	U	U	U	-	-	B	A	-
JET FUELS	70°	U	U	U	-	A	-	B	-	U	-	-	-	A	-
KEROSENE		U	U	U	U	A	A	B	A	C	B	U	A	A	A
KETOHEXAMETHYLENE	70°	U	U	C	C	U	U	U	C	U	-	-	U	U	-
KP-140		B	B	A	A	U	-	U	-	U	U	-	B	A	-
LACQUERS		U	U	U	U	U	U	U	U	U	U	U	U	U	U
LACQUER SOLVENTS		U	U	U	U	U	U	U	U	U	U	U	U	U	U
LACTIC ACID		B	B	A	A	B	-	B	-	A	-	A	A	A	-
LARD	150°	U	U	U	U	A	A	C	A	C	A	B	A	A	A
LAUGHING GAS	70°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
LAURYL ALCOHOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	B	-
LAVENDER FLOWER OIL		U	U	U	U	B	-	C	-	-	-	-	B	A	B
LAVENDER OIL		U	U	U	U	B	-	C	-	-	-	-	B	A	B
LEAD ACETATE	70°	A	C	A	A	B	B	B	A	B	U	U	U	U	U
LEAD NITRATE		A	A	A	A	A	-	A	-	A	-	B	A	-	-
LEAD SULFAMATE		B	B	A	A	B	-	A	-	A	-	B	A	A	U
LEAD SULFATE	150°	A	A	A	-	A	-	A	A	A	-	-	-	A	-
LICHENIC ACID		A	A	U	-	A	-	B	-	B	-	B	A	A	U
LIME ACETATE	70°	A	B	A	A	B	-	B	A	B	-	-	U	U	-
LIME BLEACH	70°	B	B	B	B	B	B	B	B	B	-	B	A	A	U

Data

LIME HYDRATE	70°	A	A	A	A	A	A	A	A	A	A	A	A	U	
LIME NITRATE	150°	A	A	A	A	A	A	A	A	A	B	A	A	A	
LIME SALTPETER	150°	A	A	A	A	A	A	A	A	A	B	A	A	A	
LIME SULFUR		U	U	A	A	U	-	A	-	A	-	A	A	A	U
LIME, SULFURATED	150°	B	B	A	A	B	B	A	A	A	B	A	A	U	
LIMONENE		-	-	-	-	B	-	-	-	-	-	C	A	-	
LINDOL		U	U	A	A	U	U	C	A	C	C	C	C	B	-
LINOLEIC ACID		-	-	U	U	B	-	U	-	-	-	B	-	B	-
LINOLIC ACID		-	-	U	U	B	-	U	-	-	-	B	-	B	-
LINSEED OIL		U	U	B	B	A	-	B	A	B	B	-	A	A	A
LIQUIFIED PETROLEUM GAS		U	U	U	U	A	A	B	-	B	A	C	B	A	C
LIQUID PITCH OIL	70°	U	U	U	U	B	U	C	-	C	B	U	A	A	A
LIQUID ROSIN	70°	U	U	U	U	A	-	-	-	U	-	-	-	A	-
LUBRICATING OIL (PETROLEUM)		U	U	U	U	A	A	B	A	B	A	B	A	A	A
LYE		B	B	A	A	B	B	B	A	B	B	C	B	B	U
MAC	70°	U	U	C	-	U	-	-	-	U	-	-	-	C	-
MAGNESIUM ACETATE		U	U	B	-	U	-	-	A	U	-	-	-	U	-
MAGNESIUM CHLORIDE	150°	A	A	A	A	A	A	A	A	A	A	A	A	-	
MAGNESIUM HYDRATE	150°	A	B	B	A	B	A	A	A	A	-	B	A	U	
MAGNESIUM HYDROXIDE	150°	A	B	B	A	B	A	A	A	A	-	B	A	U	
MAGNESIUM SULFATE	150°	B	B	A	A	A	A	A	A	A	-	A	A	U	
MAIZE OIL		U	U	B	B	A	A	B	-	B	A	A	A	A	A
MALEIC ACID	70°	C	C	C	C	U	-	-	-	C	-	-	-	A	-
MALEIC ANHYDRIDE	70°	B	B	C	C	-	-	-	-	-	-	-	-	A	-
MALEINIC ACID	70°	C	C	C	C	U	-	-	-	C	-	-	-	A	-
MALIC ACID	150°	A	B	U	U	A	-	B	-	B	-	B	A	A	U
MALIC ACID, COMMON	150°	A	B	U	U	A	-	B	-	B	-	B	A	A	U
MANGANESE SULFATE	150°	C	A	A	-	A	-	-	-	A	-	-	-	A	-
MANGANESE SULFIDE	150°	C	A	A	-	A	-	-	-	A	-	-	-	A	-
MANGANOUS SULFITE	150°	C	A	A	-	A	-	-	-	A	-	-	-	A	-
MANGANOUS SULFATE	150°	C	A	A	-	A	-	-	-	A	-	-	-	A	-
MANGANOUS SULFIDE	150°	C	A	A	-	A	-	-	-	A	-	-	-	A	-
MANGANESE SULFITE	150°	C	A	A	-	A	-	-	-	A	-	-	-	A	-
MARSH GAS		U	U	U	U	A	A	B	-	B	B	U	B	A	A
MEA		B	B	A	B	B	B	B	A	B	C	B	U	U	U
MEK	70°	U	U	B	B	U	U	U	U	U	U	U	U	U	U
MERCURIC CHLORIDE		A	A	A	A	A	A	B	-	A	-	-	A	A	-
MERCURY		A	A	A	A	A	A	A	-	A	A	-	-	A	-
MERCURY BICHLORIDE		A	A	A	A	A	A	B	-	A	-	-	A	A	-
MERCURY CHLORIDE		A	A	A	A	A	A	B	-	A	-	-	A	A	-
MESITYL OXIDE	70°	U	U	B	B	U	-	U	C	U	-	U	U	U	-
METACETONE	70°	U	U	B	-	U	-	-	C	U	-	-	-	U	-
METHANAL	70°	B	B	A	A	A	B	B	A	A	U	-	-	A	-
METHALLYL ACETATE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
METHALLYL ALCOHOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	U	-
BETA-METHALLYL CHLORIDE	70°	U	U	C	-	U	-	-	-	U	-	-	-	C	-
METHANE		U	U	U	U	A	A	B	-	B	B	U	B	A	A
METHANECARBOXYLIC ACID	150°	C	C	A	A	C	C	B	A	B	C	A	B	C	U
METHANETHIOMETHANE	70°	U	U	C	-	U	-	-	B	U	-	-	-	-	-
METHANOIC ACID	70°	B	B	A	A	B	B	B	A	A	U	B	C	C	-
METHANOL	70°	A	A	A	A	A	B	A	A	A	U	A	A	C	U
PARA-METHOXYPROPENYLBENZENE	70°	U	U	U	-	U	-	-	A	U	-	-	-	B	-

Data

METHYL ACETATE		U	U	B	B	U	U	U	A	U	-	-	U	U	-
METHYL ACETOACETATE	70°	U	U	B	-	U	-	-	A	U	-	-	-	U	-
METHYL ACETONE	70°	C	U	B	-	U	-	-	A	U	-	-	-	U	-
BETA-METHYL ACROLEIN	70°	U	U	A	-	U	-	-	-	U	-	-	-	U	-
METHYL ACRYLATE		U	U	B	B	U	-	U	-	-	-	-	U	U	U
METHYLACRYLIC ACID		U	U	B	B	-	-	U	-	-	-	-	U	B	U
METHYL ALCOHOL	70°	A	A	A	A	A	B	A	A	A	U	A	A	C	U
METHYLALLYL ACETATE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
METHYLALLYL ALCOHOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	U	-
BETA-METHYLALLYL CHLORIDE	70°	U	U	C	-	U	-	-	-	U	-	-	-	C	-
METHYL AMYL A954ALCOHOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	U	-
METHYL-N-AMYL CARBINOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	U	-
METHYL-N-AMYL KETONE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
METHYL BENZENE	70°	U	U	U	U	U	U	U	U	U	C	U	B	A	-
METHYL BROMIDE		-	-	-	-	B	-	U	-	U	-	-	A	A	-
2-METHYLBUTANE	70°	U	U	U	-	A	-	-	-	U	-	-	-	A	-
METHYL BUTANOL	70°	A	A	A	A	A	A	A	A	A	U	C	B	B	U
METHYL BUTANONE	70°	U	U	B	-	U	-	U	-	U	-	-	-	U	-
METHYL BUTYL KETONE	70°	U	U	A	A	U	-	U	-	U	-	B	U	U	-
METHYL CARBITOL	70°	U	U	C	-	U	-	-	-	U	-	-	-	-	-
METHYL CELLOSOLVE	70°	U	U	B	B	B	-	B	-	C	-	-	-	U	-
METHYL CHLORIDE	70°	U	U	C	C	U	-	U	-	U	-	U	B	A	U
METHYL CHLOROFORM	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
METHYL CYCLOHEXANE	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
METHYL CYCLOPENTANE		U	U	U	U	-	-	C	-	-	-	-	B	A	-
METHYLENE BROMIDE	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
METHYLENE CHLORIDE	70°	U	U	U	U	U	-	U	C	U	U	-	B	A	-
METHYLENE CHLOROBROMIDE	70°	U	U	B	B	U	-	U	C	U	-	-	-	U	-
METHYL ETHER	70°	U	U	C	-	B	-	-	-	U	-	-	-	-	-
METHYL ETHYL KETONE	70°	U	U	B	B	U	U	U	U	U	U	U	U	U	U
METHYL FORMATE		U	U	B	B	U	U	B	-	B	-	B	-	-	-
METHYL HEXANOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	C	-
METHYL HEXANONE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
METHYL HEXYL KETONE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
METHYL HYDRIDE		U	U	U	U	A	A	B	-	B	B	U	B	A	A
METHYL ISOBUTENYL KETONE	70°	U	U	B	B	U	-	U	C	U	-	U	U	U	-
METHYL ISOBUTYL CARBINOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	U	-
METHYL ISOBUTYL KETONE	70°	U	U	B	C	U	U	U	-	U	-	C	U	U	U
METHYL ISOPROPYL KETONE	70°	U	U	B	-	U	-	U	-	U	-	-	-	U	-
METHYL METHACRYLATE		U	U	U	U	U	U	U	C	-	-	C	U	U	U
METHYLLACTONITRILE	70°	C	C	A	-	U	-	-	A	C	-	-	-	U	-
METHYLMETHANE		U	U	U	U	A	-	B	-	B	B	U	A	A	A
METHYL OLEATE		U	U	B	B	U	-	U	-	-	-	-	B	A	-
METHYL OXIDE	70°	U	U	C	-	B	-	-	-	U	-	-	-	-	-
4-METHYL-2,4-PENTANEDIOL	70°	A	A	A	-	A	-	-	A	A	-	-	-	A	-
4-METHYL-3-PENTEN-2-ONE	70°	U	U	B	B	U	-	U	C	U	-	U	U	U	-
METHYL PHENOL	70°	U	U	C	C	C	-	C	-	C	U	C	B	A	-
2-METHYLPROPANE	70°	U	U	U	-	A	-	-	-	U	-	-	-	A	-
2-METHYLPROPANOL	70°	A	A	A	A	A	-	A	-	A	U	A	B	A	U
2-METHYL-2-PROPANOL		B	B	B	B	B	-	B	-	B	U	B	B	A	U
METHYLPROPYLBENZENE	70°	U	U	U	-	U	-	U	U	U	-	-	B	A	-
METHYLPROPYL CARBINOL	70°	B	B	A	-	B	-	-	-	B	-	-	-	C	-

Data

METHYL PROPYL ETHER	70°	U	U	B	-	U	-	-	-	U	-	-	-	-	-
METHYL PROPYL KETONE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
METHYL SALICYLATE		-	-	B	B	-	U	-	-	-	-	-	-	-	-
METHYL SULFATE	70°	U	U	C	-	U	-	-	A	U	-	-	-	B	-
METHYL SULFIDE	70°	U	U	C	-	U	-	-	B	U	-	-	-	-	-
MIBK		U	U	B	C	U	U	U	-	U	-	C	U	U	U
MILK		A	A	A	A	A	-	A	-	A	U	A	A	A	U
MILK ACID		B	B	A	A	B	-	B	-	A	-	A	A	A	-
MINERAL OIL		U	U	U	U	A	A	B	A	B	A	B	A	A	A
MINERAL OIL, WHITE		U	U	U	U	A	A	B	A	B	A	B	A	A	A
MINERAL PITCH	175°	U	U	U	U	B	A	B	-	C	B	U	B	A	B
MINERAL SPIRITS	70°	U	U	U	-	A	-	-	-	U	-	-	-	A	-
MIPA	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-
MONOBUTYL ETHER	70°	U	U	C	C	U	-	U	-	U	B	-	C	C	U
MONOCHLOROACETIC ACID	70°	C	U	C	B	U	-	C	A	U	U	U	C	U	-
MONOCHLOROACETONE	70°	C	U	B	A	U	-	B	U	C	-	-	U	U	-
MONOCHLOROBENZENE	70°	U	U	U	U	U	U	U	U	U	C	U	B	A	U
MONOCHLORODIFLUOROMETHANE	70°	B	B	A	A	U	A	A	-	A	U	U	U	U	-
MONOETHANOLAMINE	70°	B	B	A	B	B	B	B	A	B	C	B	U	U	U
MONOETHYLAMINE	70°	C	C	B	-	C	-	-	A	C	-	-	-	-	-
MONOISOPROPANOLAMINE	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-
MONOMETHYLANILINE		U	U	-	-	U	-	U	-	U	-	-	-	B	-
MONOVINYL ACETYLENE		B	B	A	A	A	-	B	-	B	-	B	-	A	-
MORRHUA OIL	70°	U	U	A	A	A	-	B	-	B	A	B	A	A	A
MOSAIC GOLD	150°	A	A	A	-	A	-	-	-	A	-	-	-	-	-
MURIATIC ACID	125°	B	U	C	C	U	U	U	B	U	U	U	U	A	U
MUSTARD GAS		A	-	A	A	-	-	A	-	A	-	A	-	-	-
MYRISTYL ALCOHOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	C	-
NAPHTHA	70°	U	U	U	U	B	A	C	A	U	C	U	B	A	B
NAPHTHALENE	70°	U	U	C	U	U	-	U	-	U	B	U	A	A	-
NAPHTHENIC ACID	70°	U	U	U	U	B	-	-	A	-	-	-	A	A	-
NAPHTHLIN	70°	U	U	C	U	U	-	U	-	U	B	U	A	A	-
NATURAL GAS	70°	C	C	U	U	A	A	A	-	A	B	A	C	A	B
NEATSFOOT OIL		U	U	B	B	A	-	-	-	-	-	B	A	A	A
NEOHXANE	70°	U	U	U	-	A	-	-	B	U	-	-	-	A	-
NEU-TRI	70°	U	U	U	U	U	U	U	U	U	U	U	U	A	-
NEVILLE ACID		U	U	B	B	C	-	C	-	-	-	-	B	A	-
NICKEL ACETATE		A	-	A	A	B	-	B	-	-	-	-	U	U	-
NICKEL CHLORIDE	150°	A	A	A	A	A	-	A	-	A	-	A	A	A	-
NICKEL NITRATE	150°	A	A	A	A	A	-	A	-	A	-	-	-	A	-
NICKELOUS CHLORIDE	150°	A	A	A	A	A	-	A	-	A	-	A	A	A	-
NICKELOUS NITRATE	150°	A	A	A	A	A	-	A	-	A	-	-	-	A	-
NICKEL SALTS, SINGLE	150°	B	B	A	A	A	-	A	-	A	A	A	A	A	U
NICKEL SULFATE	150°	B	B	A	A	A	-	A	-	A	A	A	A	A	U
NITER	150°	A	A	A	A	A	A	A	A	A	A	A	A	A	A
NITER CAKE	150°	A	A	A	A	A	-	A	-	A	-	A	A	A	U
NITRE	150°	A	A	A	A	A	A	A	A	A	A	A	A	A	A
NITRE CAKE	150°	A	A	A	A	A	-	A	-	A	-	A	A	A	U
NITRIC ACID-RED FUMING	70°	U	U	U	U	U	U	U	U	U	U	U	U	C	U
NITRIC ACID (CONC.) 30-70%	70°	U	U	C	C	U	U	U	U	C	U	U	U	B	U
NITRIC ACID 20%	150°	U	U	B	U	U	U	U	U	C	U	U	U	B	U
NITRIC ACID 10%	175°	U	U	B	U	U	U	C	U	C	U	U	U	B	U

Data

NITROBENZENE		U	U	U	U	U	U	U	C	U	U	U	U	B	U
NITROBENZINE		-	-	C	C	-	-	U	-	U	-	-	A	A	-
NITROCALCITE	150°	A	A	A	A	A	A	A	A	A	A	B	A	A	A
NITROETHANE		B	B	B	B	U	-	C	A	C	-	U	U	U	U
NITROGEN		A	A	A	A	A	A	A	A	A	A	A	A	A	A
NITROGEN DIOXIDE		U	U	C	C	U	-	U	-	U	-	C	U	U	-
NITROGEN MONOXIDE	70°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
NITROGEN TETROXIDE		U	U	C	C	U	-	U	-	U	-	C	U	U	-
NITROHYDROCHLORIC ACID		U	U	U	U	-	-	U	B	C	-	-	C	B	-
NITROMETHANE		B	B	B	B	U	-	C	-	C	-	U	U	U	U
NITROMURIATIC ACID		U	U	U	U	-	-	U	B	C	-	-	C	B	-
NITROUS OXIDE	70°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
NITROXANTHIC ACID		B	B	B	B	B	-	A	-	B	B	U	B	A	-
NONANOIC ACID	70°	U	U	A	-	A	-	-	-	U	-	-	-	-	-
NONENES	70°	U	U	U	-	A	-	-	-	U	-	-	-	A	-
NONOIC ACID	70°	U	U	A	-	A	-	-	-	U	-	-	-	-	-
NONYL ALCOHOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	B	-
NONYLENES	70°	U	U	U	-	A	-	-	-	U	-	-	-	A	-
NONYLIC ACID	70°	U	U	U	-	A	-	-	-	U	-	-	-	-	-
NORGE NITER	150°	A	A	A	A	A	A	A	A	A	A	B	A	A	A
NORWAY SALTPETER	70°	A	A	A	A	A	A	A	-	A	U	-	-	-	A
NORWEGIAN SALTPETER	150°	A	A	A	A	A	A	A	A	A	A	B	A	A	A
OCTACHLOROTOLUENE		U	U	U	U	U	-	U	-	U	U	U	B	A	U
OCTADECANE		U	U	U	U	A	-	B	-	B	A	U	A	A	B
OCTADECANOIC ACID	70°	U	U	B	B	B	B	B	-	U	A	A	-	-	-
CIS-9-OCTADECANOIC ACID	70°	U	U	B	B	B	-	B	A	B	A	U	A	A	A
OCTAFLUOROCYCLOBUTANE		A	A	A	A	A	-	A	-	A	-	-	-	A	-
OCTANAL	70°	U	U	A	-	U	-	-	-	U	-	-	-	U	-
N-OCTANE	70°	U	U	U	U	A	-	-	A	-	-	U	B	A	-
OCTANOIC ACID	70°	C	U	C	-	C	-	-	A	B	-	-	-	-	-
OCTANOL	70°	B	B	A	A	B	-	A	A	A	U	B	B	A	U
2-OCTANONE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
OCTIC ACID	70°	C	U	C	-	C	-	-	A	B	-	-	-	-	-
OCTYL ACETATE	70°	U	U	B	-	U	-	-	B	U	-	-	-	U	-
OCTYL ALCOHOL	70°	B	B	A	A	B	-	A	A	A	U	B	B	A	U
OCTYL ALDEHYDE	70°	U	U	A	-	U	-	-	-	U	-	-	-	U	-
OCTYL AMINE	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-
OCTYL CARBINOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	B	-
OCTYLENE GLYCOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
OCTYLIC ACID	70°	C	U	C	-	C	-	-	A	B	-	-	-	-	-
OCTYL PHOSPHATE		U	U	A	A	U	-	U	-	U	-	C	B	B	U
OENANTHAL	70°	U	U	A	-	U	-	-	C	U	-	-	-	-	-
OIL OF MIRBANE		U	U	U	U	U	U	U	C	U	U	U	U	B	U
OIL, OLIVE	70°	U	U	B	B	A	B	B	-	B	A	U	-	A	A
OIL, PETROLEUM	70°	U	U	U	U	A	A	B	A	B	A	B	A	A	A
OLEIC ACID	70°	U	U	B	B	B	-	B	A	B	A	U	A	A	A
OLEUM (FUMING SULFURIC ACID)	70°	U	U	U	U	U	U	U	U	U	U	U	U	U	U
ORTHOARSENIC ACID	70°	B	A	A	A	A	A	A	A	C	A	A	A	C	
ORTHOBORIC ACID		A	A	A	A	A	A	A	-	A	A	A	A	A	U
ORTHODICHLOROBENZENE	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
ORTHODICHLOROBENZOL	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
ORTHOXYLENE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-

Data

OXALIC ACID		B	B	A	A	B	C	B	-	B	U	B	A	A	-
OXIRANE		-	-	C	C	U	-	U	-	U	-	C	U	U	-
OXYGEN COLD (NOT LIQUID)	70°	B	B	A	A	C	B	B	A	B	A	A	A	A	A
OXYGEN	200° - 400	U	U	U	U	U	U	U	U	U	U	U	U	U	-
OXYMETHYLENE	70°	B	B	A	A	A	B	B	A	A	U	-	-	A	-
OZONE		U	U	B	A	U	A	B	A	A	A	A	U	A	B
PAINT THINNER - DUCO		U	U	U	U	-	-	-	-	-	-	-	B	B	-
PALMITIC ACID	70°	U	C	A	B	A	B	B	-	B	A	-	A	A	-
PAPER MAKERS ALUM	150°	A	B	A	A	A	-	A	A	A	-	A	A	A	U
PARAFFIN	150°	U	U	U	-	A	-	-	-	U	-	-	-	A	-
PARALDEHYDE	70°	C	-	A	-	U	-	-	-	-	-	-	-	U	-
PATENT ALUM	150°	A	B	A	A	A	-	A	A	A	-	A	A	A	U
PEARL ALUM	150°	A	B	A	A	A	-	A	A	A	-	A	A	A	U
PEARL ASH	150°	A	A	A	A	A	-	A	A	A	-	-	-	A	-
PEANUT OIL	70°	U	U	C	C	A	A	B	-	B	B	A	A	A	A
PELARGONIC ACID	70°	U	U	A	-	A	-	-	-	U	-	-	-	-	-
PENTACHLOROETHANE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
PENTALIN	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
PENTAMETHYLENE	70°	U	U	U	-	U	-	-	B	U	-	-	-	A	-
PENTAMETHYLENE AMINE		U	U	U	U	U	-	U	-	U	-	-	U	U	-
PENTANE	70°	U	U	U	-	A	-	-	-	C	-	-	-	A	-
PENTANOL	70°	A	A	A	A	A	A	A	A	A	U	C	B	B	U
3-PENTANOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
2-PENTANONE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
3-PENTANONE	70°	U	U	B	-	U	-	-	C	U	-	-	-	U	-
PENTASOL	70°	A	A	A	A	A	A	A	A	A	U	C	B	B	U
PENTYLAMINE	70°	B	B	A	-	B	-	-	B	C	-	-	-	-	-
PENTANEDIONE-2,4		C	U	B	-	U	-	-	B	U	-	-	-	U	-
PERCHLOR	70°	U	U	U	U	C	B	U	C	U	U	B	B	A	-
PERCHLORIC ACID 10-20%		-	-	B	B	-	C	A	-	A	-	U	A	A	-
PERCHLOROETHYLENE	70°	U	U	U	U	C	B	U	C	U	U	B	B	A	-
PERCHLOROMETHANE	70°	U	U	U	U	C	B	U	C	U	C	U	A	A	-
PETROLATUM, LIQUID		U	U	U	U	A	A	B	A	B	A	B	A	A	A
PETROLEUM	<250°	U	U	U	U	A	A	B	-	B	B	B	B	A	A
PETROLEUM	>250°	U	U	U	U	C	B	U	-	U	U	U	U	B	C
PETROLEUM ETHER	70°	U	U	U	U	A	-	C	A	U	-	-	-	A	-
PETROLEUM PITCH	175°	U	U	U	U	B	A	B	-	C	B	U	B	A	B
PHENETOLE		U	U	U	U	U	-	U	-	U	-	-	-	-	-
PHENOL	125°	U	U	B	B	U	-	C	A	C	U	U	B	A	-
PHENOL SULFONIC ACID	70°	U	U	C	-	U	-	-	-	U	-	-	-	U	-
PHENYLAMINE	70°	U	U	A	A	U	U	C	B	C	-	C	C	C	U
PHENYL BENZENE		U	U	U	U	U	-	U	-	U	-	-	B	A	-
PHENYL BROMIDE	70°	U	U	U	U	U	U	U	U	U	U	U	A	A	U
1-PHENYLBUTANE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
PHENYL CHLORIDE	70°	U	U	U	U	U	U	U	U	U	C	U	B	A	U
PHENYL ETHANE	70°	U	U	U	U	U	U	U	C	U	U	-	A	A	-
PHENYL ETHER		-	-	-	A	-	-	-	-	-	-	C	B	A	-
PHENYL ETHYLENE	70°	U	U	U	U	U	-	U	-	U	-	U	C	B	-
PHENYL ETHYL ETHER		U	U	U	U	U	-	U	-	U	-	-	-	-	-
PHENYL FLUORIDE		U	U	U	U	U	-	U	-	U	-	U	B	A	-
PHENYL HYDRAZINE		A	B	C	C	U	-	C	-	C	-	-	-	A	-
PHENYL METHYL KETONE		C	U	A	A	U	U	U	-	U	U	-	U	U	U

Data

PHENYLSULFONIC ACID		-	-	-	-	-	-	A	-	A	-	-	B	A	-
PHORONE		-	-	B	B	-	-	-	-	-	-	-	-	-	-
PHOSPHORIC ACID - 20%	150°	A	C	A	A	B	-	B	B	A	A	-	B	A	-
PHOSPHORIC ACID - 45%	100°	U	U	B	B	U	-	B	B	B	A	U	B	A	-
PHOSPHORUS CHLORIDE		U	U	A	A	U	-	U	-	U	-	-	A	A	-
PHOSPHORUS TRICHLORIDE		U	U	A	A	U	-	U	-	U	-	-	A	A	-
PICKLE ALUM	150°	A	B	A	A	A	-	A	A	A	-	A	A	A	U
PICKLING SOLUTION		-	-	C	C	-	U	-	-	C	-	-	-	B	U
PICRIC ACID		B	B	B	B	B	-	A	-	B	B	U	B	A	-
PIMELIC KETONE	70°	U	U	C	C	U	U	C	U	-	-	U	U	-	-
PINENE	70°	U	U	U	U	B	-	C	-	C	B	U	B	A	-
PINE OIL	70°	U	U	U	U	B	-	U	-	U	-	-	A	A	-
PIPERIDINE		U	U	U	U	U	-	U	-	U	-	-	U	U	-
PLATING SOLUTION - CHROME		U	U	A	A	-	-	-	-	C	-	U	-	A	-
PLATING SOLUTION - OTHERS		-	-	A	A	A	-	-	-	A	-	U	-	A	-
POLYETHER GLYCOL	150°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
POLYETHYLENE GLYCOL	150°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
POLYGLYCOL	150°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
POLYOXYETHYLENE	150°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
POLYPROPYLENE GLYCOL	150°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
POLYVINYL ACETATE EMULSION		-	-	A	A	-	-	B	-	B	-	-	-	-	-
POTASH	150°	A	A	A	A	A	-	A	A	A	-	-	-	A	-
POTASH MURIATE	150°	A	A	A	A	A	A	A	A	A	A	A	A	A	A
POTASSIUM ACETATE	70°	A	C	A	A	B	B	B	-	B	U	U	U	U	U
POTASSIUM ACID SULFATE	150°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
POTASSIUM ACID SULFITE	150°	A	A	A	-	A	-	-	-	A	A	-	-	A	-
POTASSIUM BICHROMATE	150°	B	B	A	A	A	-	A	A	A	A	A	A	A	A
POTASSIUM BISULFATE	150°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
POTASSIUM BISULFITE	150°	A	A	A	-	A	-	-	-	A	A	-	-	A	-
POTASSIUM CARBONATE	150°	A	A	A	A	A	-	A	A	A	-	-	-	A	-
POTASSIUM CHLORIDE	150°	A	A	A	A	A	A	A	A	A	A	A	A	A	A
POTASSIUM CHROMATE	150°	-	-	A	-	-	-	-	-	A	C	-	-	-	-
POTASSIUM CHROMATE, NEUTRAL	150°	-	-	A	-	-	-	-	-	A	C	-	-	-	-
POTASSIUM CHROMATE, RED	150°	B	B	A	A	A	-	A	A	A	A	A	A	A	A
POTASSIUM CHROMATE, YELLOW	150°	-	-	A	-	-	-	-	-	A	C	-	-	-	-
POTASSIUM COPPER CYANIDE		A	A	A	A	A	-	A	-	A	A	A	A	A	A
POTASSIUM CUPROCYANIDE		A	A	A	A	A	-	A	-	A	A	A	A	A	A
POTASSIUM CYANIDE		A	A	A	A	A	A	A	-	A	A	A	A	A	A
POTASSIUM DICHROMATE	150°	B	B	A	A	A	-	A	A	A	A	A	A	A	A
POTASSIUM HYDRATE	150°	B	B	A	A	B	B	B	A	B	B	C	B	B	U
POTASSIUM HYDROGEN SULFATE	150°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
POTASSIUM HYDROXIDE	150°	B	B	A	A	B	B	B	A	B	B	C	B	B	U
POTASSIUM MURIATE	150°	A	A	A	A	A	A	A	A	A	A	A	A	A	A
POTASSIUM NITRATE	150°	A	A	A	A	A	A	A	A	A	A	A	A	A	A
POTASSIUM SILICATE	150°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
POTASSIUM SULFATE	150°	B	B	A	A	A	A	A	-	A	A	A	A	A	U
POTASSIUM SULFIDE	150°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
POTASSIUM SULFITE	150°	A	A	A	A	A	-	A	-	A	-	-	-	A	-
PRODUCER GAS		U	U	U	U	A	-	B	-	B	A	B	B	A	B
PROPANE		U	U	U	U	A	A	A	-	A	B	U	B	A	A
PROPANEDIOL	70°	A	A	A	A	A	-	-	-	A	A	-	-	-	A
2-PROPANOL	70°	A	A	A	A	A	A	A	A	A	U	A	A	A	U

Data

2-PROPENAL		B	C	A	A	B	U	A	A	B	U	U	U	A	U
PROPENE		U	U	U	U	U	-	U	-	U	-	-	B	A	-
PROPENENITRILE	70°	U	U	C	C	U	-	C	A	C	-	U	U	U	-
PROPENYL ALCOHOL		A	A	A	-	A	-	-	A	A	-	-	-	A	-
PARA-PROPENYLANISOLE	70°	U	U	U	-	U	-	-	A	U	-	-	-	B	-
PROPIONALDEHYDE	70°	C	-	A	-	U	-	-	-	-	-	-	-	U	-
PROPIONE	70°	U	U	B	-	U	-	-	C	U	-	-	-	U	-
PROPYL ACETATE	70°	U	U	A	A	U	U	U	B	U	-	-	U	U	U
PROPYL ACETONE		U	U	A	A	U	-	U	-	U	-	B	U	U	-
PROPYL ALCOHOL	70°	A	A	A	A	A	A	A	A	A	U	A	A	A	U
PROPYL ALDEHYDE	70°	C	-	A	-	U	-	-	-	-	-	-	-	U	-
PROPYL CHLORIDE	70°	U	U	C	-	U	-	-	-	U	-	-	-	B	-
PROPYLENE		U	U	U	U	U	-	U	-	U	-	-	B	A	-
PROPYLENE CHLORIDE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
PROPYLENE DIAMINE	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-
PROPYLENE DICHLORIDE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
PROPYLENE GLYCOL	70°	A	A	A	A	A	-	-	A	A	-	-	-	A	-
PROPYLENE OXIDE		-	-	B	B	-	-	U	-	U	-	U	-	-	-
PROPYLFORMIC ACID	70°	C	U	C	-	C	-	C	A	B	-	-	-	-	-
PROPYL NITRATE		-	-	B	B	-	-	-	-	-	-	C	U	U	-
PRUSSIC ACID		B	B	B	A	B	-	B	-	A	-	-	B	A	U
PYRANOL		U	U	U	U	A	U	U	-	U	B	B	A	A	A
PYRIDINE		U	U	B	B	U	U	U	-	U	-	-	-	U	-
PYROLIGNEOUS ACID		-	-	B	B	-	-	B	-	B	-	-	-	-	-
PYROMUCIC ALDEHYDE	70°	C	C	B	B	U	U	B	A	B	-	C	-	U	-
PYRROLE		C	C	C	C	U	-	U	-	-	-	B	B	-	U
QUICKSILVER		A	A	A	A	A	A	A	-	A	A	-	-	A	-
RAPE OIL		U	U	A	A	B	A	B	-	B	B	U	A	A	B
RAPESEED OIL		U	U	A	A	B	A	B	-	B	B	U	A	A	B
RED OIL	70°	U	U	B	B	B	-	B	A	B	A	U	A	A	A
RICINUS OIL	70°	C	B	B	B	A	A	A	A	A	A	A	A	A	A
SAL AMMONIAC	150°	A	A	A	A	A	A	A	A	A	A	B	A	A	A
SAL CHALYBIS	150°	A	A	A	A	A	A	A	A	A	-	B	A	A	A
SALICYLIC ACID		A	B	A	A	A	-	-	-	-	-	-	A	A	-
SALTPETER	150°	A	A	A	A	A	A	A	A	A	A	A	A	A	A
SALT WATER		A	A	A	A	A	-	A	-	A	-	-	A	A	-
SEA WATER	70°	A	A	A	A	A	-	A	-	A	-	-	A	A	-
SEED OIL		U	U	C	A	A	A	B	-	B	A	A	A	A	A
SEWAGE	70°	C	C	C	B	A	-	A	-	A	U	B	A	A	U
SILICATE ESTERS		U	U	U	U	B	-	A	-	A	A	U	A	A	-
SILICATE OF SODA	150°	A	A	A	A	A	-	A	-	A	-	-	-	A	-
SILICONE GREASES		A	A	A	A	A	A	A	-	A	A	C	A	A	A
SILICONE OILS		A	A	A	A	A	A	A	-	A	A	C	A	A	A
SILVER NITRATE		A	A	A	A	B	-	A	-	A	A	A	A	A	A
SLAKED LIME	70°	A	A	A	A	A	A	A	A	A	A	A	A	A	U
SOAP SOLUTIONS		B	B	A	A	A	A	A	-	A	A	A	A	A	U
SODA ASH	150°	A	A	A	A	A	A	A	A	A	-	A	A	A	U
SODA CAUSTIC	150°	B	B	A	A	B	B	B	A	B	B	C	B	B	U
SODA LIME	150°	A	B	A	-	B	-	-	-	B	-	-	-	C	-
SODA NITER	150°	B	B	A	A	B	A	A	A	A	-	U	-	A	-
SODIUM ACETATE	70°	A	C	A	A	B	B	B	-	B	U	U	U	U	U
SODIUM ACID SULFITE	150°	A	B	A	A	A	A	A	A	A	-	A	A	A	U



Data

SODIUM ALUMINATE	70°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
SODIUM BICARBONATE		A	A	A	A	A	A	A	-	A	-	A	A	A	-
SODIUM BICHROMATE	150°	-	-	A	-	-	-	-	A	C	-	-	-	-	-
SODIUM BISULFATE	150°	A	A	A	A	A	-	A	-	A	-	A	A	A	U
SODIUM BISULFITE	150°	A	B	A	A	A	A	A	A	A	-	A	A	A	U
SODIUM BORATE, ANHYDROUS	70°	B	B	A	A	B	A	A	-	A	A	B	B	A	B
SODIUM CARBONATE	150°	A	A	A	A	A	A	A	A	A	-	A	A	A	U
SODIUM CHLORIDE	150°	A	A	A	A	A	A	A	A	A	A	A	A	A	-
SODIUM CHROMATE	150°	-	-	A	-	-	-	-	A	C	-	-	-	-	-
SODIUM CYANIDE	70°	A	A	A	A	A	A	A	-	A	-	A	A	A	-
SODIUM DICHROMATE	150°	-	-	A	-	-	-	-	A	C	-	-	-	-	-
SODIUM DIOXIDE	70°	B	B	A	A	B	-	B	-	B	U	U	B	A	U
SODIUM HYDRATE	150°	B	B	A	A	B	B	B	A	B	B	C	B	B	U
SODIUM HYDROGEN SULFITE	150°	A	B	A	A	A	A	A	A	A	-	A	A	A	U
SODIUM HYDROXIDE	150°	B	B	A	A	B	B	B	A	B	B	C	B	B	U
SODIUM HYPOCHLORITE	70°	U	U	B	B	U	B	C	-	B	U	B	B	A	U
SODIUM HYPOSULFITE	150°	B	B	A	A	B	-	A	-	A	A	A	A	A	U
SODIUM METABORATE PEROXYHYDRATE	70°	B	B	A	A	B	-	B	-	B	-	B	A	A	-
SODIUM METAPHOSPHATE	70°	A	A	A	A	A	-	B	-	B	-	-	A	A	-
SODIUM NITRATE	150°	B	B	A	A	B	A	A	A	A	-	U	-	A	-
SODIUM PERBORATE	70°	B	B	A	A	B	-	B	-	B	-	B	A	A	-
SODIUM PEROXIDE	70°	B	B	A	A	B	-	B	-	B	U	U	B	A	U
SODIUM PHOSPHATE	70°	A	A	A	A	A	-	B	A	A	A	U	A	A	A
SODIUM PHOSPHATE, DIBASIC	70°	A	A	A	A	A	-	B	A	A	A	U	A	A	A
SODIUM PHOSPHATE, TRIBASIC	150°	A	A	A	A	A	-	A	-	A	-	-	-	A	-
SODIUM SILICATE	150°	A	A	A	A	A	-	A	-	A	-	-	-	A	-
SODIUM SULFATE, ANHYDROUS	150°	B	B	A	A	A	A	A	-	A	A	A	A	A	U
SODIUM SULFATE DECAHYDRATE		-	U	B	B	-	-	-	-	-	-	-	A	A	U
SODIUM SULFATE EXSICCATED	150°	B	B	A	A	A	A	A	-	A	A	A	A	A	U
SODIUM SULFIDE	150°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
SODIUM SULFITE	150°	A	A	A	-	A	-	A	-	A	-	-	-	A	-
SODIUM SULFURET	150°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
SODIUM SUPEROXIDE	70°	B	B	A	A	B	-	B	-	B	U	U	B	A	U
SODIUM THIOSULFATE	150°	B	B	A	A	B	-	A	-	A	A	A	A	A	U
SOYA BEAN OIL	70+B1290	U	U	B	B	A	A	B	-	B	B	A	A	A	A
SOYBEAN OIL	70°	U	U	B	B	A	A	B	-	B	B	A	A	A	A
SOY OIL	70°	U	U	B	B	A	A	B	-	B	B	A	A	A	A
STANNIC CHLORIDE	150°	A	A	B	B	A	-	A	-	A	-	B	A	A	-
STANNIC SULFIDE	150°	A	A	A	-	A	-	-	-	A	-	-	-	-	-
STANNOUS CHLORIDE	150°	A	A	A	-	A	-	-	-	A	-	-	-	-	-
STANNOUS SULFIDE	150°	A	A	A	-	A	-	-	-	A	-	-	-	-	-
STARCH SYRUP		A	A	A	A	A	A	A	-	A	A	A	A	A	-
STEAM UNDER 300 F		U	U	A	A	U	-	C	-	U	U	U	U	U	U
STEAM OVER 300 F		U	U	C	B	U	U	U	-	U	U	U	U	U	U
STEARIC ACID	70°	U	U	B	B	B	B	B	-	U	A	A	-	-	-
STODDARD SOLVENT	70°	U	U	U	U	A	A	C	-	C	A	U	A	A	A
STYRENE	70°	U	U	U	U	U	-	U	-	U	-	U	C	B	-
SUCROSE SOLUTION	70°	A	A	A	A	A	-	A	-	A	-	-	-	-	-
SUGAR OF LEAD	70°	A	C	A	A	B	B	B	A	B	U	U	U	U	U
SULFAMIC ACID	70°	B	B	A	A	B	-	B	-	B	-	-	-	-	-
SULFITE LIQUOR	70°	B	B	B	B	B	B	B	-	B	-	U	B	A	U
SULFOCARBOLIC ACID	70°	U	U	C	-	U	-	-	-	U	-	-	-	U	-

Data

SULFONIC ACID	70°	U	U	U	-	U	-	-	-	C	-	-	-	U	-
SULFUR	250°	U	U	A	A	U	C	A	-	A	U	A	A	A	U
SULFUR CHLORIDE	70°	U	U	U	U	C	-	C	-	B	-	-	A	A	-
SULFUR DIOXIDE		C	C	B	A	U	-	C	-	C	-	A	B	A	U
SULFURETTED HYDROGEN	150°	U	U	A	A	U	B	B	-	C	-	C	C	U	U
SULFUR FLOUR	250°	U	U	A	A	U	C	A	-	A	U	A	A	A	U
SULFUR FLOWERS	250°	U	U	A	A	U	C	A	-	A	U	A	A	A	U
SULFURIC ACID, FUMING	70°	U	U	U	U	U	U	U	U	U	U	U	U	B	U
SULFURIC ACID 50-96%	70°	U	U	B	B	U	U	U	U	B	U	U	U	A	U
SULFURIC ACID 35-50%+A1317	100°	C	C	B	B	U	B	B	A	A	B	U	C	A	U
SULFURIC ACID 25% & UNDER	150°	C	C	B	B	U	B	B	-	A	B	U	C	A	U
SULFURIC ANHYDRIDE		B	U	B	B	U	-	U	-	U	-	B	B	A	U
SULFURIC ETHER	70°	U	U	C	C	C	B	U	-	U	B	U	U	U	U
SULFUR MONOCHLORIDE	70°	U	U	U	U	C	-	C	-	B	-	-	A	A	-
SULFUROUS ACID 10-75%	70°	B	B	B	B	B	-	B	-	A	U	U	U	A	U
SULFUROUS ACID 10%	150°	B	B	B	B	B	-	B	-	A	U	U	U	A	U
SULFUROUS ACID ANHYDRIDE		C	C	B	A	U	-	C	-	C	-	A	B	A	U
SULFUROUS OXYCHLORIDE		U	U	U	U	-	-	U	-	-	-	-	-	A	-
SULFUR HEXAFLUORIDE		U	U	A	A	B	A	A	-	B	-	B	B	C	U
SULFUR OXYCHLORIDE		U	U	U	U	-	-	U	-	-	-	-	-	A	-
SULFUR SUBCHLORIDE	70°	U	U	U	U	C	-	C	-	B	-	-	A	A	-
SULFUR TRIOXIDE		B	U	B	B	U	-	U	-	U	-	B	B	A	U
SWEET-BIRCH OIL		-	-	B	B	-	-	U	-	-	-	-	-	-	-
SWEET OIL	70°	U	U	B	B	A	B	B	-	B	A	U	-	A	A
TALL OIL	70°	U	U	U	U	A	-	-	-	U	-	-	-	A	-
TALLOL	70°	U	U	U	U	A	-	-	-	U	-	-	-	A	-
TALLOW	150°	U	U	U	U	A	-	-	-	U	-	-	-	-	-
TANNIC ACID	150°	A	C	B	A	B	-	A	-	A	A	B	A	A	U
TANNIN	150°	A	C	B	A	B	-	A	-	A	A	B	A	A	U
TAR BITUMINOUS	175°	U	U	U	U	B	B	C	-	C	-	B	A	A	U
TAR CAMPHOR	70°	U	U	C	U	U	-	U	-	U	B	U	A	A	-
TAR OIL	70°	U	U	U	U	B	U	C	-	C	B	U	A	A	A
TARTARIC ACID	150°	A	B	B	B	A	B	B	-	A	A	A	A	A	-
TBT		B	B	B	A	B	-	A	-	A	-	-	A	A	-
TCP		U	U	A	A	U	U	C	A	C	C	C	C	B	-
TDI		C	C	A	A	-	-	U	-	U	-	-	-	-	-
TEA	70°	B	B	B	B	B	-	A	-	A	U	-	U	U	U
TERPILENOL		U	U	C	C	B	-	U	A	U	B	-	A	A	-
TERPINEOL		U	U	C	C	B	-	U	A	U	B	-	A	A	-
ALPHA-TERPINEOL		U	U	C	C	B	-	U	A	U	B	-	A	A	-
BETA-TERPINEOL		U	U	C	C	B	-	U	A	U	B	-	A	A	-
GAMMA-TERPINEOL		U	U	C	C	B	-	U	A	U	B	-	A	A	-
TETRABROMOMETHANE		-	-	-	-	U	-	-	-	-	-	-	B	A	-
TETRABUTYL TITANATE		B	B	B	A	B	-	A	-	A	-	-	A	A	-
TETRACHLOROBENZENE	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
TETRACHLORODIFLUOROETHANE		U	-	U	U	B	-	B	-	B	-	-	-	A	-
SYM-TETRACHLOROETHANE	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
TETRACHLOROETHYLENE	70°	U	U	U	U	C	B	U	C	U	U	B	B	A	-
TETRACHLOROMETHANE	70°	U	U	U	U	C	B	U	C	U	C	U	A	A	-
TETRACHLORONAPHTHALENE	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
TETRADECANOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	C	-
TETRAETHYLENE GLYCOL	150°	A	A	A	-	A	-	-	-	A	-	-	-	A	-

Data

TETRAETHYL LEAD		U	U	U	U	B	-	C	-	C	-	-	B	A	-
TETRAETHYLORTHOSILICATE	70°	C	C	A	-	A	-	A	A	-	-	-	-	-	-
TETRAHYDROFURAN		U	U	B	B	-	-	-	C	C	-	-	B	U	-
TETRAHYDRONAPHTHALENE		U	U	U	U	U	-	U	-	U	-	-	A	A	-
TETRALIN		U	U	U	U	U	-	U	-	U	-	-	A	A	-
THF		U	U	B	B	-	-	-	C	C	-	-	B	U	-
THIONYL CHLORIDE		U	U	U	U	-	-	U	-	-	-	-	-	A	-
TIN BISULFIDE	150°	A	A	A	-	A	-	-	-	A	-	-	-	-	-
TINCAL	70°	B	B	A	A	B	A	A	-	A	A	B	B	A	B
TIN CHLORIDE	150°	A	A	B	B	A	-	A	-	A	-	B	A	A	-
TIN CRYSTALS	150°	A	A	A	-	A	-	-	-	A	-	-	-	-	-
TIN DICHLORIDE	150°	A	A	A	-	A	-	-	-	A	-	-	-	-	-
TIN DISULFIDE	150°	A	A	A	-	A	-	-	-	A	-	-	-	-	-
TIN MONOSULFIDE	150°	A	A	A	-	A	-	-	-	A	-	-	-	-	-
TIN PROTOCHLORIDE	150°	A	A	A	-	A	-	-	-	A	-	-	-	-	-
TIN PROTOSULFIDE	150°	A	A	A	-	A	-	-	-	A	-	-	-	-	-
TIN SALT	150°	A	A	A	-	A	-	-	-	A	-	-	-	-	-
TIN SULFIDE	150°	A	A	A	-	A	-	-	-	A	-	-	-	-	-
TIN TETRACHLORIDE	150°	A	A	B	B	A	-	A	-	A	-	B	A	A	-
TITANIC CHLORIDE		U	U	U	U	C	-	U	-	U	-	-	B	A	-
TITANIUM BUTYLATE		B	B	B	A	B	-	A	-	A	-	-	A	A	-
TITANIUM TETRACHLORIDE		U	U	U	U	C	-	U	-	U	-	-	B	A	-
TNT		U	U	U	U	U	-	B	-	B	-	-	B	B	-
TOLUENE	70°	U	U	U	U	U	U	U	U	U	C	U	B	A	-
TOLUENE-2,4-DIISOCYANATE		C	C	A	A	-	-	U	-	U	-	-	-	-	-
TOLUOL	70°	U	U	U	U	U	U	U	U	U	C	U	B	A	-
META TOLYLENE DIISOCYANATE		C	C	A	A	-	-	U	-	U	-	-	-	-	-
2,4-TOLYLENE DIISOCYANATE		C	C	A	A	-	-	U	-	U	-	-	-	-	-
TRANSFORMER OIL		U	U	U	U	A	A	B	A	B	A	B	A	A	A
TRANSMISSION FLUID, TYPE A	150°	U	U	U	U	A	A	B	A	B	A	A	A	A	A
TRIACETIN		B	C	A	A	B	-	B	-	B	U	-	U	U	U
TRIARYL PHOSPHATE		U	U	A	A	U	-	C	-	C	B	C	B	A	U
TRIBUTOXY ETHYL PHOSPHATE		B	B	A	A	U	-	U	-	U	U	-	B	A	-
TRIBUTYL AMINE	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-
TRIBUTYL MERCAPTAN		U	U	U	U	U	-	U	-	U	-	-	-	A	-
TRIBUTYL PHOSPHATE	70°	U	U	A	A	U	-	U	-	C	U	-	U	U	U
TRICALCIUM ALUMINATE	70°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
TRICHLOROACETIC ACID	70°	C	B	B	B	B	-	B	-	B	-	-	-	C	U
TRICHLOROBENZENE	70°	U	U	U	-	U	-	-	-	U	U	-	-	B	-
TRICHLOROETHANE	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
1,1,2-TRICHLOROETHANE	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
TRICHLOROETHYLENE	70°	U	U	U	U	U	U	U	U	U	U	U	U	A	-
TRICHLOROFLUOROMETHANE		U	U	U	U	A	-	C	-	U	U	U	B	A	-
TRICHLOROMETHANE	70°	U	U	U	U	U	-	U	U	U	-	U	B	A	-
TRICHLOROPROPANE	70°	U	U	U	-	U	-	-	-	U	-	-	-	B	-
TRICHLOROTRIFLUOROETHANE		C	B	U	U	A	A	A	-	A	B	U	U	B	-
TRICRESYLPHOSPHATE	70°	U	U	A	A	U	U	C	A	C	C	C	C	B	-
TRIDECANOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
TRIDECYL ALCOHOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	A	-
TRI-ETHANE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
TRIETHANOLAMINE	70°	B	B	B	B	B	-	A	-	A	U	-	U	U	U
TRIETHYLALUMINUM		-	-	-	-	-	-	-	-	-	-	-	-	B	-

Data

TRIETHYLAMINE	70°	B	B	A	-	B	-	-	-	C	-	-	-	-	-
TRIETHYLBORANE		-	-	-	-	-	-	-	-	-	-	-	-	A	-
TRIETHYLBORINE		-	-	-	-	-	-	-	-	-	-	-	-	A	-
TRIETHYLENE GLYCOL	150°	A	A	A	-	A	-	-	A	A	-	-	-	A	-
3,4,5-TRIHYDROXYBENZOIC ACID	70°	A	B	B	B	B	-	C	A	B	U	-	A	A	U
TRI-2-HYDROXYETHYL AMINE	70°	B	B	B	B	B	-	A	-	A	U	-	U	U	U
TRIIODOMETHANE	70°	-	-	A	A	-	-	-	-	-	-	-	-	-	-
TRIMETHYL CARBINOL		B	B	B	B	B	-	B	-	B	U	B	B	A	U
3,5,5-TRIMETHYL-2-CYCLOHEXEN-1-ONE		-	-	A	A	U	-	-	-	-	B	-	-	U	-
TRIMETHYLMETHANE	70°	U	U	U	-	A	-	-	-	U	-	-	-	A	-
2,2,4-TRIMETHYLPENTANE	70°	U	U	U	U	A	A	C	A	B	B	U	A	A	A
2,4,6-TRIMETHYL-1,3,5-TRIOXANE	70°	C	-	A	-	U	-	-	-	-	-	-	-	U	-
TRINIDAD PITCH	175°	U	U	U	U	B	A	B	-	C	B	U	B	A	B
TRINITROPHENOL		B	B	B	B	B	-	A	-	B	B	U	B	A	-
TRINITROTOLUENE		U	U	U	U	U	-	B	-	B	-	-	B	B	-
TRIOCTYL PHOSPHATE		U	U	A	A	U	-	U	-	U	-	C	B	B	U
TRIPHENYL PHOSPHATE	70°	U	U	A	-	U	-	-	-	C	-	-	-	-	-
TRI SODIUM PHOSPHATE	150°	A	A	A	A	A	-	A	-	A	-	-	-	A	-
TRITOLYL PHOSPHATE		U	U	A	A	U	U	C	A	C	C	C	C	B	-
TUNG OIL	100°	U	U	C	U	A	-	B	-	B	B	U	B	A	-
TURBINE OIL		U	U	U	U	B	A	B	-	B	-	-	B	A	B
TURPENTINE		U	U	U	U	A	A	U	-	U	U	U	B	A	A
UDMH		-	-	A	A	B	-	B	-	A	-	U	U	U	-
UNDECANOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	B	-
UNDECYL ALCOHOL	70°	A	A	A	-	A	-	-	-	A	-	-	-	B	-
UNSYMM+A1437ETRICAL DIMETHYL HYDRAZINE		-	-	A	A	B	-	B	-	A	-	U	U	U	-
UREA		-	-	A	-	C	-	A	-	-	-	-	-	-	-
URNER'S LIQUID	70°	B	U	C	-	U	-	-	-	U	-	-	-	U	-
VARNISH		U	U	U	U	B	-	C	-	C	-	-	B	A	-
VEGETABLE OILS		U	U	A	A	A	A	B	-	B	-	A	A	A	A
VERDIGRIS, CRYSTALLIZED	70°	-	-	A	A	B	-	B	-	B	-	-	-	-	-
VERSILUBE		A	A	A	A	A	A	A	-	A	-	C	A	A	A
VINEGAR		B	B	A	A	B	-	A	-	A	-	A	-	A	U
VINEGAR ACID	150°	C	C	A	A	C	C	B	A	B	C	A	B	C	U
VINEGAR NAPHTHA	70°	U	U	B	B	U	-	C	B	U	-	B	U	U	-
VINEGAR SALTS	70°	A	B	A	A	B	-	B	A	B	-	-	U	U	-
VINYL ACETATE	70°	U	U	B	-	U	-	-	-	U	-	-	-	U	-
VINYLACETYLENE		B	B	A	A	A	-	B	-	B	-	B	-	A	-
VINYL BENZENE	70°	U	U	U	U	U	-	U	-	U	-	U	C	B	-
VINYL CHLORIDE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
VINYL CYANIDE	70°	U	U	C	C	U	-	C	A	C	-	U	U	U	-
VINYL ETHER	70°	U	U	B	-	U	-	-	-	U	-	-	-	-	-
VINYLISTYRENE	70°	U	U	U	-	U	-	-	U	U	-	-	-	A	-
VINYL TOLUENE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
VINYL TRICHLORIDE	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-
VM & P NAPHTHA		U	U	U	U	A	-	C	-	U	-	C	U	U	U
WAGNER 21-B FLUID		-	A	B	A	C	-	A	-	B	-	C	U	U	U
WATER		A	A	A	A	A	B	A	A	A	A	A	A	A	U
WATER GLASS	150°	A	A	A	A	A	-	A	-	A	-	-	-	A	-
WHISKEY		A	A	A	A	A	-	A	-	A	A	A	A	A	U
WHITE COPPERAS	150°	B	B	A	A	A	-	A	-	A	-	A	A	A	U
WHITE MINERAL OIL		U	U	U	U	A	A	B	A	B	A	B	A	A	A

Data

WHITE OIL		U	U	U	U	A	A	B	A	B	A	B	A	A	A	A
WHITE PINE OIL		U	U	U	U	B	-	U	-	U	-	-	-	A	A	-
WHITE VITRIOL		B	B	A	A	A	-	A	-	A	-	-	-	A	A	U
WINES		A	A	A	A	A	-	A	-	A	A	A	A	A	A	U
WINTERGREEN OIL		-	-	B	B	-	U	-	-	-	-	-	-	-	A	-
WINTHER'S ACID		U	U	B	B	C	-	C	-	-	-	-	-	B	A	-
WOOD ALCOHOL	70°	A	A	A	A	A	B	A	A	A	U	A	A	C	U	
WOOD ETHER	70°	U	U	C	-	B	-	-	-	U	-	-	-	-	-	
WOOD OIL	100°	U	U	C	U	A	-	B	-	B	B	U	B	A	-	
WOOD VINEGAR		-	-	B	B	-	-	B	-	B	-	-	-	-	-	
XYLENE	70°	U	U	U	U	U	U	U	U	U	U	U	B	A	-	
META-XYLENE		U	U	U	U	U	U	U	U	U	U	U	B	A	-	
ORTHO-XYLENE		U	U	U	U	U	U	U	U	U	U	U	B	A	-	
PARA-XYLENE		U	U	U	U	U	U	U	U	U	U	U	B	A	-	
XYLENOL	70°	U	U	U	-	U	-	-	-	U	-	-	-	A	-	
XYLIDINE	70°	U	U	U	U	C	-	U	-	U	-	U	U	U	-	
XYLOL	70°	U	U	U	U	U	U	U	U	U	U	U	B	A	-	
ZEOLITES		A	A	A	A	A	-	A	-	A	-	-	A	A	-	
ZINC ACETATE		A	C	A	A	B	-	B	-	B	-	U	U	U	U	
ZINC CARBONATE	150°	A	A	A	-	A	-	-	-	A	-	-	-	A	-	
ZINC CHLORIDE	150°	A	A	A	A	A	-	A	-	A	-	-	A	A	U	
ZINC CHROMATE	150°	-	-	A	-	-	-	-	-	C	-	-	-	-	-	
ZINC SULFATE	150°	B	B	A	A	A	-	A	-	A	-	A	A	A	U	
ZINC VITRIOL		B	B	A	A	A	-	A	-	A	-	A	A	A	U	
MIL-L-2104C		U	U	U	U	A	A	A	-	A	A	C	A	A	A	
MIL-L-2105C-1		U	U	U	U	A	A	A	-	A	A	C	A	A	A	
MIL-L-3150B-2		U	U	U	U	A	A	A	-	A	A	C	A	A	A	
MIL-C-4339C		-	-	-	-	A	A	A	-	A	A	C	A	A	A	
MIL-G-4343C		U	U	U	U	B	-	B	-	B	A	U	B	A	A	
MIL-L-5020B		U	U	U	U	A	A	B	-	C	B	U	A	A	B	
MIL-J-5161F		U	U	U	U	A	A	C	-	C	C	U	A	A	-	
MIL-C-5545B-1		U	U	U	U	B	B	B	-	C	C	U	A	A	B	
MIL-H-5559A-2		B	A	A	A	A	A	B	-	B	C	B	B	B	C	
MIL-H-5606D-1		U	U	U	U	A	B	B	-	B	B	U	A	A	A	
MIL-T-5624L-GRADE JP-4		U	U	U	U	A	A	C	-	C	C	U	A	A	B	
MIL-T-5624L GRADE JP-5		U	U	U	U	A	A	C	-	C	C	U	A	A	B	
MIL-O-6081C-2		U	U	U	U	A	A	B	-	B	B	C	A	A	A	
MIL-L-6082D		U	U	U	U	A	A	A	-	A	A	C	A	A	A	
MIL-H-6083D-2		U	U	U	U	A	A	B	-	B	B	C	A	A	A	
MIL-L-6085A-2		U	U	U	U	A	B	C	-	C	C	C	A	A	C	
MIL-L-6086C		U	U	U	U	A	A	A	-	A	A	C	A	A	A	
MIL-C-6529C-2		U	U	U	U	B	B	B	-	C	C	U	A	A	B	
MIL-C-7024C-1		U	U	U	U	A	A	B	-	C	B	U	A	A	B	
MIL-L-7808H		U	U	U	U	A	B	C	-	C	C	C	A	A	C	
MIL-L-7870A		U	U	U	U	B	A	B	-	B	B	C	A	A	A	
MIL-C-8188C		U	U	U	U	A	B	C	-	C	C	C	A	A	C	
MIL-A-8+A1525243B-4		B	A	A	A	A	B	B	-	B	C	B	B	B	C	
MIL-L-8383C-1		U	U	U	U	A	A	A	-	A	A	C	A	A	A	
MIL-H-8446B		U	U	U	U	B	C	B	-	-	-	U	A	A	C	
MIL-L-9000G-3		U	U	U	U	A	A	B	-	C	C	U	A	A	B	
MIL-G-10924C		U	U	U	U	A	A	B	-	B	B	C	A	A	A	
MIL-L-11734C		U	U	C	U	A	B	C	-	C	C	C	A	A	C	

Data

MIL-H-13910B	B	A	B	A	B	B	B	-	B	C	U	B	A	B
MIL-L-14107C	U	U	U	U	C	-	A	-	-	-	U	A	A	-
MIL-L-15019C	U	U	U	U	A	A	A	-	A	A	C	A	A	A
MIL-L-15719A-3	C	B	B	B	B	B	B	-	B	U	U	B	A	B
MIL-L-16958B	U	U	U	U	A	A	B	-	B	B	C	A	A	A
MIL-L-17111A-1	U	U	U	U	A	A	B	-	B	B	C	A	A	A
MIL-L-17331G-1	U	U	U	U	A	A	A	-	A	A	C	A	A	A
MIL-H-17672C	U	U	U	U	A	A	A	-	A	A	C	A	A	A
MIL-L-18486B	U	U	U	U	A	A	A	-	A	A	C	A	A	A
MIL-G-18709A-3	U	U	U	U	A	A	A	-	A	A	C	A	A	A
MIL-H-19457B-2	U	U	A	A	U	U	U	-	U	U	U	C	U	U
MIL-L-19701A	U	U	C	U	A	B	C	-	C	C	C	A	A	C
MIL-L-21260B-1	U	U	U	U	A	A	A	-	A	A	C	A	A	A
MIL-H-22072B-1	B	A	A	A	A	B	B	-	B	C	B	B	B	C
MIL-L-23699C	U	U	C	U	A	B	C	-	C	C	C	A	A	C
MIL-G-23827A-1	U	U	C	U	A	B	C	-	C	C	C	A	A	C
MIL-G-25013D	B	A	A	A	A	A	B	-	B	C	U	B	A	B
MIL-F-25558C	U	U	U	U	A	A	B	-	B	B	C	A	A	A
MIL-P-25576C-1	U	U	U	U	A	A	C	-	C	C	U	A	A	-
MIL-L-25681D	B	A	A	A	A	A	B	-	B	C	U	B	A	B
MIL-L-26087A	U	U	U	U	A	A	A	-	A	A	C	A	A	A
MIL-H-27601A	U	U	U	U	B	B	B	-	C	C	U	A	A	B
MIL-G-27617C	-	B	A	A	U	-	-	-	-	-	U	A	A	-
MIL-I-27686E-2	B	A	A	A	A	B	B	-	B	C	B	B	B	C
MIL-L-27694A	A	A	A	A	A	A	A	-	A	A	U	A	A	-
MIL-L-46000B	U	U	C	U	A	B	C	-	C	C	C	A	A	C
MIL-H-46001B-2	U	U	U	U	A	A	A	-	A	A	C	A	A	A
MIL-P-46002A	U	U	U	U	A	A	A	-	A	A	C	A	A	-
MIL-H-46004-1	U	U	U	U	A	A	B	-	B	A	C	A	A	A
MIL-S-81087B	A	A	A	A	A	A	A	-	A	A	U	B	A	-
TT-N-95B	U	U	U	U	A	A	C	-	C	C	U	A	A	-
TT-N-97C	U	U	U	U	B	B	C	-	C	C	U	B	A	C
TT-S-735 TYPE I	U	U	U	U	A	A	B	-	C	B	U	A	A	B
TT-S-735 TYPE II	U	U	U	U	A	A	C	-	C	C	U	A	A	-
TT-S-735 TYPE III	U	U	U	U	A	A	C	-	C	C	U	A	A	-
TT-S-735 TYPE IV	U	U	U	U	A	A	A	-	A	A	C	A	A	A
TT-S-735 TYPE V	U	U	U	U	A	A	B	-	B	B	C	A	A	A
TT-S-735 TYPE VI	U	U	U	U	A	A	B	-	B	B	C	A	A	A
TT-S-735 TYPE VII	U	U	U	U	A	A	C	-	C	C	U	A	A	-
TT-T-656 B	U	U	A	A	U	U	C	A	C	C	C	C	B	U
VV-B-680B	B	A	B	A	B	B	B	-	B	C	U	B	A	B
VV-G-632A-1	U	U	U	U	A	A	A	-	A	A	C	A	A	A
VV-G-671E	U	U	U	U	A	A	A	-	A	A	C	A	A	A
VV-I-530A	U	U	U	U	A	A	B	A	B	A	B	A	A	A
VV-K-211D	U	U	U	U	A	A	B	A	C	B	U	A	A	A
VV-K-220A-1	U	U	U	U	A	A	B	A	C	B	U	A	A	A
VV-L-751C-1	U	U	U	U	B	B	B	-	B	B	C	A	A	A
VV-L-800A	U	U	U	U	A	A	B	-	B	B	C	A	A	A
VV-L-820C	U	U	U	U	A	A	B	-	B	B	C	A	A	A
VV-L-825A TYPE I	U	U	U	U	A	A	A	-	A	A	C	A	A	A
VV-L-825A TYPE II	U	U	U	U	A	A	A	-	A	A	C	A	A	A
VV-L-825A TYPE III	U	U	U	U	B	B	B	-	C	C	U	A	A	B

Data

VV-P-216B	U	U	U	U	A	A	B	-	B	B	C	A	A	A
VV-P-236	U	U	U	U	A	A	B	A	B	A	B	A	A	A
F.R. -HYDRAULIC FLUIDS	-	-	-	-	-	-	-	-	-	-	-	-	-	-
AEROSHELL FLUID NO. 4	-	-	-	-	-	-	-	-	-	-	-	-	A	-
AMOCO FLUID WO	-	-	-	-	-	-	-	-	-	-	-	-	-	-
AMCO FLUID WG20	-	-	-	-	-	-	-	-	-	-	-	-	-	-
AMOCO FLUID PE 15	-	-	-	-	-	-	-	-	-	-	-	-	-	-
AMOCO FLUID PE 22	-	-	-	-	-	-	-	-	-	-	-	-	-	-
AMOCO FLUID PE 30	-	-	-	-	-	-	-	-	-	-	-	-	-	-
AMOCO FLUID PE 55	-	-	-	-	-	-	-	-	-	-	-	-	-	-
AROCLOR 1248	U	U	B	B	C	-	U	-	U	U	B	B	A	U
AROCLOR 1254	U	U	B	B	C	-	B	-	U	U	B	B	A	U
AROCLOR 1260	U	U	U	-	U	-	U	-	U	-	C	B	A	U
CHEM-TREND FR-20 (WATER-GLYCOL)	-	-	A	A	A	-	B	-	-	U	A	A	A	-
ASTROL NO. 587	-	-	-	-	-	-	-	-	-	-	-	-	-	-
AQUALUBE	-	-	-	-	-	-	-	-	-	-	-	-	-	-
CHEVRON FR FLUID 8	U	U	A	A	U	-	U	-	U	U	B	B	A	U
CHEVRON FR FLUID 10	U	U	A	A	U	-	U	-	U	U	B	B	A	U
CHEVRON FR FLUID 13	U	U	A	A	U	-	U	-	U	U	B	B	A	U
CHEVRON FR FLUID 20	U	U	A	A	U	-	U	-	U	U	B	B	A	U
CITGO PACEMAKER GYLCOL	-	-	-	-	-	-	-	-	-	-	-	-	-	-
CITGO PACEMAKER FR-15	-	-	A	A	A	-	A	-	-	U	U	-	-	-
CITGO PACEMAKER FR-20	-	-	A	A	A	-	A	-	-	U	U	-	-	-
CITGO PACEMAKER FR-25	-	-	A	A	A	-	A	-	-	U	U	-	-	-
CITGO PACEMAKER SYNTHETIC	-	-	-	-	-	-	-	-	-	-	-	-	-	-
CITGO PACEMAKER SYNTHETIC FR-15	-	-	C	C	U	-	U	-	-	U	C	-	-	-
CITGO PACEMAKER SYNTHETIC FR-30	-	-	C	C	U	-	U	-	-	U	C	-	-	-
CITGO PACEMAKER SYNTHETIC FR-50	-	-	C	C	U	-	U	-	-	U	C	-	-	-
CITGO PACEMAKER INVERT-FR-FLUID	-	-	U	U	A	-	C	-	-	C	U	-	-	-
DASCO 1FR	-	-	-	-	-	-	-	-	-	-	-	-	-	-
DASCO FR 150	-	-	-	-	-	-	-	-	-	-	-	-	-	-
DASCO FR 200	-	-	-	-	-	-	-	-	-	-	-	-	-	-
DASCO FR 200B	-	-	-	-	-	-	-	-	-	-	-	-	-	-
DASCO FR 300	-	-	-	-	-	-	-	-	-	-	-	-	-	-
DASCO FR 310	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FYRE-SAFE W/O	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FYRE-SAFE 225	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FYRGUARD 150	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FYRGUARD 150M	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FYRGUARD 200	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FYRQUEL 90	U	U	A	A	U	-	U	-	U	U	B	B	A	U
FYRQUEL 150	U	U	A	A	U	-	U	-	U	U	B	B	A	U
FYRQUEL 220	U	U	A	A	U	-	U	-	U	U	B	B	A	U
FYRQUEL 290	U	U	A	A	U	-	U	-	U	U	B	B	A	U
FYRQUEL 300	U	U	A	A	U	-	U	-	U	U	B	B	A	U
FYRQUEL 550	U	U	A	A	U	-	U	-	U	U	B	B	A	U
FYRQUEL 1000	U	U	A	A	U	-	U	-	U	U	B	B	A	U
FYRTEK 290	-	-	-	-	-	-	-	-	-	-	-	-	-	-
FYRTEK MINING FLUID	-	-	-	-	-	-	-	-	-	-	-	-	-	-
GULF FR FLUID	-	-	-	-	-	-	-	-	-	-	-	-	-	-
GULF FR FLUID G-150	-	-	-	-	-	-	-	-	-	-	-	-	-	-
GULF FR FLUID G-200	-	-	-	-	-	-	-	-	-	-	-	-	-	-

Data

GULF FR FLUID G-250	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
GULF FR FLUID P-37	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
GULF FR FLUID P-40	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
GULF FR FLUID P-43	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
GULF FR FLUID P-45	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
GULF FR FLUID P-47	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
HF-18	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
HOUGHTO-SAFE 271	-	A	B	A	A	-	B	-	-	U	B	B	A	U						
HOUGHTO-SAFE 416	B	B	B	B	A	A	A	-	A	A	B	B	B	B						
HOUGHTO-SAFE 520	B	B	B	B	A	A	A	-	A	A	B	B	B	B						
HOUGHTO-SAFE 525	B	B	B	B	A	A	A	-	A	A	B	B	B	B						
HOUGHTO-SAFE 616	B	B	B	B	A	A	A	-	A	A	B	B	B	B						
HOUGHTO-SAFE 620	B	B	B	B	A	A	A	-	A	A	B	B	B	B						
HOUGHTO-SAFE 640	B	B	B	B	A	A	A	-	A	A	B	B	B	B						
HOUGHTO-SAFE 1010	U	U	A	A	U	-	U	-	U	U	C	B	A	U						
HOUGHTO-SAFE 1015	U	U	A	A	U	-	U	-	U	U	C	B	A	U						
HOUGHTO-SAFE 1055	U	U	A	A	U	-	U	-	U	U	C	B	A	U						
HOUGHTO-SAFE 1120	U	U	A	A	U	-	U	-	U	U	C	B	A	U						
HOUGHTO-SAFE 1130	U	U	A	A	U	-	U	-	U	U	C	B	A	U						
HOUGHTO-SAFE 5040	U	U	U	U	A	-	B	-	-	-	-	B	A	-						
HOUGHTO-SAFE 5046W	U	U	U	U	A	A	B	-	B	A	B	B	A	B						
HOUGHTO-VITAL FLUID	U	U	U	U	U	U	U	-	U	U	C	B	A	U						
HUL-E-MUL	-	-	-	-	-	-	-	-	-	-	-	-	-	-						
HULSAFE 500	-	-	-	-	-	-	-	-	-	-	-	-	-	-						
HYPIN AF-1	-	-	-	-	-	-	-	-	-	-	-	-	-	-						
HYPIN AF-2	-	-	-	-	-	-	-	-	-	-	-	-	-	-						
HYPIN AF-3	-	-	-	-	-	-	-	-	-	-	-	-	-	-						
HYPIN FR	-	-	-	-	-	-	-	-	-	-	-	-	-	-						
HYPIN FR LIGHT	-	-	-	-	-	-	-	-	-	-	-	-	-	-						
HYDRA SAFE 620	-	-	-	-	-	-	-	-	-	-	-	-	-	-						
HUMBLE IMOL																				
HUMBLE IMOL S-150	U	U	A	A	U	-	U	-	-	U	C	C	A	U						
HUMBLE IMOL S-220	U	U	A	A	U	-	U	-	-	U	C	C	A	U						
HUMBLE IMOL S-300	U	U	A	A	U	-	U	-	-	U	C	C	A	U						
HUMBLE IMOL S-550	U	U	A	A	U	-	U	-	-	U	C	C	A	U						
LINDOL HYD FLUID	U	U	A	A	U	-	U	-	U	U	C	C	B	U						
MANSOL FR FLUID	-	-	-	-	-	-	-	-	-	-	-	-	-	-						
MELTRAN FR-900	-	-	-	-	-	-	-	-	-	-	-	-	-	-						
MELSYN 200	-	-	-	-	-	-	-	-	-	-	-	-	-	-						
MELSYN GLYCOL FR	-	-	-	-	-	-	-	-	-	-	-	-	-	-						
MIL-H-8446 & MLO 8515	U	U	U	U	B	C	B	-	-	-	U	A	A	-						
MINESAFE SUNOCO 3XF	U	U	U	U	A	-	B	-	B	U	-	A	A	U						
MLO-7277	U	U	U	U	C	-	U	-	U	C	U	C	A	C						
MLO-8200	U	U	U	U	B	-	A	-	U	A	U	A	A	-						
MOBIL NYVAC FR FLUID	-	-	-	-	-	-	-	-	-	-	-	-	-	-						
MOBIL NYVAC FR-200 FLUID	-	-	-	-	-	-	-	-	-	-	-	-	-	-						
MOBIL PYROGARD CED	U	U	U	U	A	-	B	-	U	A	B	B	A	U						
MOBIL PYROGARD 42	U	U	A	A	U	-	U	-	U	U	U	U	A	U						
MOBIL PYROGARD 43	U	U	A	A	U	-	U	-	U	U	U	U	A	U						
MOBIL PYROGARD 51	U	U	A	A	U	-	U	-	U	U	U	U	A	U						
MOBIL PYROGARD 53	U	U	A	A	U	-	U	-	U	U	U	U	A	U						
MOBIL PYROGARD 55	U	U	A	A	U	-	U	-	U	U	U	U	A	U						



Data

ORONITE 8200	U	U	U	U	B	-	A	-	U	A	U	A	A	-
ORONITE 8515	U	U	U	U	B	-	A	-	U	A	U	A	A	-
OS-45 TYPE III	U	U	U	U	B	-	A	-	B	U	U	B	A	-
OS-45 TYPE IV	U	U	U	U	B	-	A	-	B	U	U	B	A	-
OS-70	U	U	U	U	B	-	A	-	B	U	U	B	A	-
PARK WATER GLYCOL	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PARK HYDRAULIC FLUID	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PENN DRAKE HYDRAQUA FLUID	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PENNZOIL MAXMUL FR	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PENNZOIL FLUID FR-2X	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PURO FR FLUID	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PYDRAUL 10E	U	-	A	A	U	-	U	-	-	-	C	-	U	-
PYDRAUL 29ELT	U	-	A	A	U	-	U	-	-	-	A	-	A	-
PYDRAUL 30E	U	-	A	A	U	-	U	-	-	-	A	-	A	-
PYDRAUL 50E	U	-	A	A	U	-	U	-	-	-	A	-	A	-
PYDRAUL 90E	U	-	A	A	U	-	U	-	-	-	A	-	A	-
PYDRAUL 115E	U	-	A	A	U	-	U	-	-	-	A	-	A	-
PYDRAUL 230C	U	-	C	C	U	-	U	-	-	-	A	-	A	-
PYDRAUL 312C	U	-	C	C	U	-	U	-	-	-	A	-	A	-
PYDRAUL 540C	U	-	C	C	U	-	U	-	-	-	A	-	A	-
QUINTOLUBE 958	-	-	-	-	-	-	-	-	-	-	-	-	-	-
QUINTOLUBE 958-HL	-	-	-	-	-	-	-	-	-	-	-	-	-	-
QUINTOLUBE 958-LV	-	-	-	-	-	-	-	-	-	-	-	-	-	-
QUINTOLUBE 958-LVW	-	-	-	-	-	-	-	-	-	-	-	-	-	-
QUINTOLUBE 958DC	-	-	-	-	-	-	-	-	-	-	-	-	-	-
QUINTOLUBE 610	-	-	-	-	-	-	-	-	-	-	-	-	-	-
QUINTOLUBE 700	-	-	-	-	-	-	-	-	-	-	-	-	-	-
QUINTOLUBE 700RD	-	-	-	-	-	-	-	-	-	-	-	-	-	-
QUINTOLUBE 702	-	-	-	-	-	-	-	-	-	-	-	-	-	-
QUINTOLUBE 702-RD	-	-	-	-	-	-	-	-	-	-	-	-	-	-
REGENT HYDROLUBE #670	-	-	-	-	-	-	-	-	-	-	-	-	-	-
SAFOIL HYDRAULIC FLUID	C	C	U	-	A	-	B	-	-	-	B	-	A	A
SANTOSAFE 300	U	U	C	C	U	-	U	-	-	-	A	A	A	U
SANTOSAFE W/G 15	A	A	A	A	A	-	A	-	-	-	-	-	A	-
SANTOSAFE W/G 20	A	A	A	A	A	-	A	-	-	-	-	-	A	-
SANTOSAFE W/G 30	A	A	A	A	A	-	A	-	-	-	-	-	A	-
SHELL FRM FLUID	-	-	-	-	-	-	-	-	-	-	-	-	-	-
SHELL IRIS 902	U	U	U	U	A	-	B	-	U	A	U	A	A	A
SHELL IRIS 905	-	-	-	-	-	-	-	-	-	-	-	-	-	-
SHELL 3XF MINE FLUID	U	U	U	U	A	-	B	-	B	U	-	A	A	U
SHELL TELLUS #27 (PET BASE)	U	U	U	U	A	-	B	-	U	A	U	A	A	A
SHELL TELLUS #33	U	U	U	U	A	-	B	-	U	A	U	A	A	A
SINCLAIR DURO FR-HD	-	-	-	-	-	-	-	-	-	-	-	-	-	-
SKYDROL 500 A & B	U	U	B	A	U	U	U	-	U	U	U	C	U	U
SKYDROL 7000	U	U	A	A	U	U	U	-	U	U	U	C	B	U
STANDARD GLYCOL FR 15	-	-	-	-	-	-	-	-	-	-	-	-	-	-
STANDARD GLYCOL FR 20	-	-	-	-	-	-	-	-	-	-	-	-	-	-
STANDARD GL+A1701YCOL FR 25	-	-	-	-	-	-	-	-	-	-	-	-	-	-
STAYSOL FR	-	-	-	-	-	-	-	-	-	-	-	-	-	-
SUNSAFE	U	U	U	U	A	-	B	-	B	U	-	A	A	U
TEXACO 760 FD HYDRAFLUID	-	-	-	-	-	-	-	-	-	-	-	-	-	-
TEXACO 763 HYD. SAFETY FLUID	-	-	-	-	-	-	-	-	-	-	-	-	-	-

Data

TEXACO 766 HYD. SAFETY FLUID 200	-	-	-	-	-	-	-	-	-	-	-	-	-	-
UCON HYDROLUBE 150CP	A	A	A	A	A	-	A	-	-	-	-	-	A	-
UCON HYDROLUBE 200CP	A	A	A	A	A	-	A	-	-	-	-	-	A	-
UCON HYDROLUBE 275CP	A	A	A	A	A	-	A	-	-	-	-	-	A	-
UCON HYDROLUBE 300CP	A	A	A	A	A	-	A	-	-	-	-	-	A	-
UCON HYDROLUBE 550CP	A	A	A	A	A	-	A	-	-	-	-	-	A	-
UCON HYDROLUBE 900CP	A	A	A	A	A	-	A	-	-	-	-	-	A	-
UCON HYDROLUBE 150DB	-	-	-	-	-	-	-	-	-	-	-	-	-	-
UCON HYDROLUBE 275DB	-	-	-	-	-	-	-	-	-	-	-	-	-	-
UCON HYDROLUBE 150LT	A	A	A	A	A	-	A	-	-	-	-	-	A	-
UCON HYDROLUBE 200LT	A	A	A	A	A	-	A	-	-	-	-	-	A	-
UCON HYDROLUBE 275LT	A	A	A	A	A	-	A	-	-	-	-	-	A	-
UCON HYDROLUBE 300LT	A	A	A	A	A	-	A	-	-	-	-	-	A	-
UCON HYDROLUBE 200NM	-	-	-	-	-	-	-	-	-	-	-	-	-	-
UCON HYDROLUBE 300NM	-	-	-	-	-	-	-	-	-	-	-	-	-	-
UCON LUBRICANT LB-65	B	B	A	A	A	-	B	-	B	-	A	A	A	-
UCON LUBRICANT LB-135	A	A	A	A	A	-	A	-	A	-	A	A	A	-
UCON LUBRICANT LB-285	A	A	A	A	A	-	A	-	A	-	A	A	A	-
UCON LUBRICANT LB-300X	A	A	A	A	A	-	A	-	A	-	A	A	A	-
UCON LUBRICANT LB-625	A	A	A	A	A	-	A	-	A	-	A	A	A	-
UCON LUBRICANT LB-1145	A	A	A	A	A	-	A	-	A	-	A	A	A	-
UCON LUBRICANT 50-HB-55	A	A	A	A	A	-	A	-	A	-	A	A	A	-
UCON LUBRICANT 50-HB-100	A	A	A	A	A	-	A	-	A	-	A	A	A	-
UCON LUBRICANT 50-HB-260	A	A	A	A	A	-	A	-	A	-	A	A	A	-
UCON LUBRICANT 50-HB-660	A	A	A	A	A	-	A	-	A	-	A	A	A	-
UCON LUBRICANT 50-HB-5100	A	A	A	A	A	-	A	-	A	-	A	A	A	-
UCON M-1	-	-	-	-	-	-	-	-	-	-	-	-	-	-
UCON OIL LB-385	A	A	A	A	A	-	A	-	A	-	A	A	A	-
UCON OIL LB-400X	A	A	A	A	A	-	A	-	A	-	A	A	A	-
UCON OIL 50-HB-280X	A	A	A	A	A	-	A	-	A	-	A	A	A	-
UNIVIS 40	U	U	U	U	A	-	B	-	B	A	U	A	A	A
UNIVIS J-43	U	U	U	U	A	-	B	-	B	A	U	A	A	A
VEEDEL AUBURN FRH	-	-	-	-	-	-	-	-	-	-	-	-	-	-
VEEDEL AUBURN FRH-CONCENTRATE	-	-	-	-	-	-	-	-	-	-	-	-	-	-
VERSILUBE F-50	A	A	A	A	A	-	A	-	A	A	C	A	A	A

Chrysotile Asbestos	Crocidolite Asbestos	Glass Fiber	Polytetrafluoroethylene	Graphite and Carbon Fiber	Cellulose Fiber	Acrylic Fiber	Aramid Fiber
A	A	A	A	A	A	-	-
A	A	A	A	A	-	A	A
A	A	A	A	A	-	-	-
A	A	A	A	A	A	-	-
A	A	A	A	A	A	A	A
U	A	-	A	A	U	-	U
U	A	-	A	A	U	A	U
A	A	A	A	A	A	-	-
A	A	A	A	A	A	-	-
U	A	-	A	A	-	U	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
U	A	-	A	A	-	U	-
-	A	-	A	A	-	-	A
A	A	A	A	A	A	A	A
-	A	-	A	A	-	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
U	-	-	A	-	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
U	A	-	A	A	-	U	-
A	A	A	A	A	-	-	-
A	A	A	A	A	-	-	-
A	A	A	A	A	-	-	-
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
-	-	-	A	A	-	A	A
-	A	-	A	A	-	-	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	-	-
-	A	A	A	A	A	A	A

-	A	-	A	A	-	A	A
-	A	-	A	-	U	A	A
A	A	-	A	A	-	A	A
-	A	-	A	A	-	A	A
-	A	-	A	A	-	-	-
U	-	-	A	A	-	-	-
-	A	-	A	A	-	-	-
A	A	A	A	A	A	A	A
U	A	-	A	-	U	A	A
-	A	-	A	-	U	A	A
-	A	-	A	-	U	A	A
-	A	-	A	A	-	-	-
A	A	A	A	A	A	A	A
A	A	-	A	A	A	-	-
A	A	A	A	A	-	A	A
A	A	-	A	A	A	-	-
A	A	A	A	A	-	-	-
A	A	A	A	A	-	A	A
A	A	-	A	A	-	A	A
A	A	-	A	A	-	-	-
A	A	-	A	A	-	-	A
A	A	-	A	A	-	-	-
A	A	-	A	A	A	-	-
A	A	A	A	A	A	A	A
A	A	-	A	A	-	-	A
A	-	-	A	A	-	-	A
A	-	-	A	A	-	-	A
-	-	-	A	A	-	A	A
U	A	-	A	A	-	A	A
U	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A
U	A	-	A	-	-	-	-
U	A	-	A	-	-	A	A
U	-	-	A	-	-	-	-
-	A	-	A	A	-	A	A
-	-	-	A	A	-	A	A
U	A	-	A	A	-	A	A
-	A	-	A	A	-	A	A
-	A	-	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	-	A	A	-	-	A
-	A	-	A	-	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A
-	A	-	A	-	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A

Data

-	A	-	A	-	-	A	A
A	A	A	A	A	A	A	A
-	-	-	A	A	-	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A
A	A	-	A	A	A	-	-
-	A	-	A	A	-	-	-
A	A	A	A	A	A	A	A
-	A	-	A	A	-	-	-
A	A	-	A	A	A	-	-
-	A	-	A	A	-	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
-	-	-	A	-	-	-	-
-	-	-	A	-	-	-	-
A	A	A	A	A	-	-	-
A	A	A	A	A	A	A	A
U	A	U	A	U	U	U	U
A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A
-	A	-	A	A	-	A	A
-	A	-	A	A	-	-	-
-	A	-	A	A	-	-	-
-	A	-	A	A	-	-	-
-	A	-	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A
U	A	-	A	-	-	-	U
U	A	-	A	-	-	-	U
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	-
A	A	A	A	A	-	-	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A

# Data

A	A	A	A	A	-	A	A
-	A	-	A	-	-	-	-
-	A	-	A	A	-	-	-
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
U	A	-	A	-	U	-	U
-	A	-	A	-	-	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	-	A
A	A	A	A	A	A	A	A
A	A	-	A	B	U	U	U
A	A	A	A	A	U	A	A
-	A	-	A	-	-	-	U
-	A	-	A	-	-	-	U
-	A	-	A	A	-	A	A
-	A	-	A	A	-	A	A
-	A	-	A	A	-	A	A
-	A	-	A	A	-	-	A
-	A	-	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	-	A	-	A	A
-	A	-	A	A	-	A	A
A	A	A	A	-	-	A	A
A	A	A	A	A	A	A	A
-	A	-	A	-	-	-	-
-	-	-	U	-	-	-	-
A	A	A	A	-	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	-	-
A	A	A	A	A	-	-	-
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A
-	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A

-	A	-	A	A	-	-	A
-	A	-	A	A	-	-	A
A	A	A	A	A	-	-	-
A	A	A	A	A	-	-	-
A	A	A	A	A	A	A	A
-	A	-	A	A	-	U	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	-	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	-	-
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
-	-	-	A	-	-	-	-
A	A	A	A	A	-	-	-
-	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
-	A	-	A	-	U	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
-	A	-	A	-	-	-	-
-	A	-	A	-	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	-
A	A	A	A	A	A	A	A
-	A	-	A	-	-	-	-
-	A	-	A	-	-	A	A





Data

```

- A - A A - - U
A A A A A - A A
A A A A A - A A
A A A A A - A A
- A - A A - - -
U A - A A - - U
- A A A U U - U
U - - U U U - U
U A - A A - - U
A A A A A A A A
U A U A U U U U
A A A A A - A A
A A A A A - A A
A A A A A A A A
A A A A A A A A
A A A A A A A A
A A A A A A A A
A A A A A A A A
A A A A A - A -
A A A A A A A A
- - - A A - A A
A A A A A A A A
A A A A A A A A
A A A A A A A A
A A A A A A A A
- - - - - A -
U A U A U U U U
A A A A A A A A
A A A A A - A A
A A A A A - - -
A A A A A A A A
A A A A A A A A
A A A A A A A A
A A A A A A A A
- A - A A - A A
- A - A A - A A
A A - A - - - -
U A - A - - - -
A A A A A A A A
A A A A A A A A
A A A A A A A A
A A A A A A A A
U A U A - - - -
U A - A U U - U
U A - A U U - U
U A - A U U - U
A A A A A A A A
A A A A A A A A
A A - A A - A A
A A A A A - A A
A A A A A A A A
A A A A A - A A

```

A	A	A	A	A	-	A	A
-	A	-	A	A	-	A	A
-	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A
A	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	-	A	A	-	A	A
-	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	-
A	A	-	A	A	-	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
U	A	-	A	-	U	A	-
U	A	-	A	-	U	A	A
U	A	-	A	-	U	A	A
-	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	-
A	A	A	A	A	-	A	-
A	A	-	A	A	-	-	-
A	A	-	A	A	-	-	-
A	A	A	A	A	-	-	-
A	A	A	A	A	-	-	-
A	A	A	A	A	-	-	-
A	A	A	A	A	-	A	A
A	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	-
A	A	-	A	A	-	-	-
U	A	-	A	-	U	A	-
U	A	-	A	-	-	A	A
-	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A

A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	A	-	-
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	-	A	A	A	A	A
A	A	-	A	A	-	A	A
-	A	-	A	A	-	-	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
U	A	-	A	A	-	-	-
A	A	-	A	A	-	A	-
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	-	A	A	-	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	-	A	A	-	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
-	A	-	A	A	A	A	A
U	A	-	A	-	U	-	U
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A







A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
-	A	-	A	A	U	-	-
A	A	A	A	A	A	A	A
-	-	-	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	-	A
A	A	A	A	A	-	-	A
-	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	-
-	A	-	A	A	-	-	U
U	A	-	A	-	U	-	-
-	A	-	A	A	-	-	U
-	A	-	A	A	-	A	A
-	A	-	A	A	-	A	-
-	A	-	A	A	-	-	U
A	A	A	A	A	A	A	A
-	A	-	A	A	-	-	U
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A
A	A	A	A	A	-	A	A
-	A	-	A	-	U	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	-	-	A	A
-	-	-	A	A	-	-	-
A	A	A	A	A	A	-	-
U	A	-	U	-	-	-	-
U	-	-	U	-	-	-	-
A	A	A	A	A	A	-	-
-	-	-	A	A	-	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
-	A	-	A	A	-	-	-
-	A	-	A	A	-	-	-
A	A	A	A	A	A	-	-
A	A	A	A	A	A	-	-
-	A	-	A	A	A	-	A
A	A	A	A	A	A	-	-
-	A	-	A	A	-	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A







-	A	-	A	A	-	-	U
U	A	-	A	A	-	-	U
U	A	-	A	A	-	-	U
-	A	-	A	A	-	-	-
U	U	U	A	A	-	-	U
U	U	U	A	A	-	-	U
U	U	U	A	A	-	-	U
-	A	U	A	A	-	-	-
-	A	U	A	A	-	-	-
-	A	-	A	A	-	-	U
-	A	-	A	A	A	-	A
-	A	-	A	A	-	-	-
A	A	A	A	-	U	A	A
A	A	A	A	U	U	-	U
U	U	U	A	A	-	-	U
A	A	A	A	A	A	A	A
A	A	A	A	-	U	A	A
A	A	A	A	U	U	U	U
-	A	-	A	A	-	A	A
-	A	-	A	A	-	A	A
A	A	A	A	A	A	A	-
A	A	-	A	A	-	-	-
-	A	-	A	A	-	A	A
A	A	-	A	A	-	-	-
A	A	-	A	A	-	A	A
A	A	-	A	A	-	-	-
-	A	-	A	A	-	-	-
A	A	A	A	A	A	A	A
A	A	-	A	A	-	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A
-	A	-	A	A	-	A	A
-	A	-	A	A	-	-	U
-	A	-	A	A	-	-	U
A	A	A	A	A	A	A	A
U	S	-	A	-	U	-	-
-	A	-	A	A	-	-	U
-	A	-	A	A	-	-	U
-	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
-	A	-	A	A	-	-	U
-	A	-	A	A	-	A	A

Data

A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	-	-	-	-
A	A	-	A	A	-	-	-	-
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	-	-	-	-
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A	A
A	A	A	A	A	-	A	A	A
A	A	A	A	A	-	A	A	A
A	A	A	A	A	-	A	A	A
A	A	A	A	A	-	A	A	A
A	A	A	A	A	-	A	A	A
A	A	A	A	A	-	A	A	A
A	A	A	A	A	-	A	A	A
A	A	A	A	A	-	A	A	A
A	A	A	A	A	-	A	A	A
A	A	-	A	A	-	A	A	A
-	A	-	A	-	-	A	A	A
-	A	-	A	A	-	-	-	-
-	A	-	A	A	-	A	A	A
-	A	-	A	A	-	-	-	A
A	A	A	A	A	A	A	A	A
-	A	-	A	-	-	-	-	U





A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A	A
-	A	-	A	A	-	-	-	-
-	A	-	A	A	-	-	-	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A	A
A	A	A	A	A	A	A	A	A
A	A	-	A	A	-	-	-	-
A	A	A	A	A	A	A	A	A
U	A	-	A	A	-	-	-	U
A	A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A	A
A	A	A	A	A	A	A	A	A
A	A	-	A	A	-	A	A	A
A	A	A	A	A	-	-	-	-
A	A	-	A	A	-	-	-	-
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A	A
-	A	-	A	A	-	-	-	U
-	A	-	A	A	-	A	-	-
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A	A
-	A	-	A	A	-	-	-	-
A	A	-	A	A	-	A	A	A
-	A	-	A	A	-	A	A	A
U	A	-	A	-	U	-	-	-
-	A	-	A	A	-	A	A	A
U	A	-	A	-	U	-	-	-
-	A	-	A	A	-	A	A	A
-	A	-	A	A	-	A	A	A
U	A	-	A	-	U	-	-	-
-	A	-	A	A	-	A	A	A
U	A	U	A	U	U	U	U	U
U	A	-	A	U	U	U	U	U
U	A	-	A	U	U	U	U	U
U	A	-	A	U	U	U	U	U

Data

A	A	A	A	A	-	-	A
A	A	A	A	A	A	-	-
U	A	-	A	U	U	-	-
A	A	A	A	A	-	-	-
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	U	U	U	U
U	A	U	A	U	U	U	U
A	A	A	A	A	-	-	-
U	A	U	A	U	U	U	U
A	A	A	A	A	A	A	A
-	A	-	A	A	-	-	-
-	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A
U	A	-	A	U	U	-	-
U	A	-	A	-	-	-	-
U	A	-	A	U	U	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A
-	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A
U	A	-	A	-	-	U	U
-	A	-	A	A	-	-	-
-	A	-	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A

-	A	-	A	A	-	-	U
A	A	A	A	A	A	A	A
A	A	A	A	-	-	U	A
A	A	A	A	U	-	U	-
A	A	A	A	A	A	-	-
A	A	A	A	U	U	U	-
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A
-	A	-	A	A	U	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	-	-
-	A	-	A	-	U	A	A
-	A	-	A	-	U	A	A
A	A	-	A	A	A	A	-
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	-	A	A	-	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	-	A	A	-	-	-
U	A	-	A	-	-	U	U
A	A	-	A	A	A	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	-	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	A	-	-
U	A	-	A	A	-	-	-
A	A	A	A	A	A	A	A



U	A	-	A	-	-	-	U
A	A	A	A	A	A	A	A
U	A	U	A	A	-	A	U
U	A	U	A	A	-	-	U
-	A	-	A	-	-	-	-
-	A	-	A	-	-	-	-
-	A	-	A	-	U	A	A
U	-	-	A	-	-	-	-
-	A	-	A	A	-	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	-	A	A	-	-	-
U	A	-	A	-	U	-	-
-	A	-	A	-	-	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	-	A	A	A	A	-
-	A	-	A	A	-	A	A
A	A	-	A	A	-	A	A
-	A	-	A	A	-	A	A
-	A	-	A	A	-	A	A
-	A	-	A	U	U	-	-
-	A	-	A	A	-	A	A
-	A	-	A	A	-	A	A
A	A	-	A	A	A	A	-
-	A	-	A	A	-	A	A
-	A	-	A	-	-	-	-
-	A	-	A	-	-	-	-
-	A	-	A	U	U	-	-
-	A	-	A	-	-	-	-
A	A	-	A	A	-	-	-
A	A	-	A	A	-	-	-
A	A	-	A	A	-	-	-
-	A	-	A	U	U	-	-
-	A	-	A	A	-	U	U
-	A	-	A	A	-	A	A
-	A	-	A	A	-	U	U
-	A	-	A	A	-	A	A
U	A	-	A	-	U	-	-
A	A	-	A	A	-	A	A
-	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
-	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A

Data

A	A	A	A	A	-	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	-	-
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	-	A	A	-	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A
-	A	-	A	U	U	-	-
-	A	-	A	A	-	-	-
A	A	A	A	A	-	A	A
A	A	-	A	A	-	-	-
U	A	-	A	A	-	-	-
A	A	A	A	A	-	-	-
A	A	-	A	A	-	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
U	A	-	A	A	-	A	A
-	A	-	A	A	-	A	A
-	A	-	A	A	-	A	A
U	A	-	A	-	U	-	-
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A







Data

A	A	-	A	A	-	-	-
-	A	A	A	-	-	-	-
-	A	A	A	-	-	-	-
A	A	A	A	A	A	A	A
-	A	-	A	A	-	A	A
A	A	-	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	-	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	-	-
A	A	A	A	A	-	A	A
-	A	-	A	A	-	-	-
-	-	-	A	-	-	U	-
A	A	A	A	A	-	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
U	A	-	-	-	-	-	-
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
U	A	-	A	-	-	-	-
A	A	A	A	A	A	A	A
U	A	-	A	-	U	-	U
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
-	A	A	A	A	U	A	A
U	A	-	A	A	U	-	U
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	-	A	A	-	A	A
A	A	A	A	A	A	A	A
-	A	A	A	A	-	A	A
A	A	A	A	A	A	A	A







Data

A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	-	-	A	A
A	A	A	A	-	-	A	A
A	A	A	A	-	-	A	A
A	A	A	A	-	-	A	A
A	A	A	A	-	-	A	A
A	A	A	A	-	-	A	A
A	A	A	A	-	-	A	A
A	A	A	A	-	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	-	A	A
A	A	A	A	-	-	A	A
A	A	A	A	-	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	-	-	A	A
A	A	A	A	-	-	-	-
A	A	A	A	-	-	-	A
A	A	A	A	-	-	-	A
A	A	A	A	-	-	-	A





Data

A	A	A	A	-	-	A	A
A	A	A	A	-	U	A	A
A	A	A	A	-	U	A	A
A	A	A	A	-	U	A	A
A	A	A	A	-	U	A	A
A	A	A	A	-	U	A	A
A	A	A	A	-	U	A	A
A	A	A	A	-	-	A	A
A	A	A	A	-	-	A	A
A	A	A	A	-	U	A	A
A	A	A	A	-	U	A	A
A	A	A	A	-	U	A	A
A	A	A	A	-	-	A	A
A	A	A	A	-	-	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	A	A	A	A
A	A	A	A	-	-	-	-
A	A	A	A	-	-	-	-
A	A	A	A	A	A	A	A

Data

X