



## Garlock BLACK GYLON® 3530

### MATERIAL PROPERTIES\*

<b>Color:</b>	Black
<b>Composition:</b>	PTFE with graphite
<b>Temperature<sup>2</sup>, °F (°C)</b>	
Minimum:	-450 (-268)
Continuous Max:	+500 (+260)
<b>Pressure<sup>2</sup>, Maximum, psig (bar):</b>	1200 (83)
<b>P x T (max.)<sup>2</sup>, psig x °F (bar x °C)</b>	
1/32 and 1/16":	350,000 (12,000)
1/8":	250,000 (8,600)
<b>Flammability:</b>	Will Not Burn
<b>Bacterial Growth:</b>	Will Not Support

### TYPICAL PHYSICAL PROPERTIES\*

<b>ASTM F36</b>	<b>Compressibility, %:</b>	7-17
<b>ASTM F36</b>	<b>Recovery, %:</b>	40
<b>ASTM F38</b>	<b>Creep Relaxation, %:</b>	29
<b>ASTM F152</b>	<b>Tensile, Across Grain, psi (N/mm<sup>2</sup>):</b>	3000 (21)
<b>ASTM D792</b>	<b>Specific Gravity:</b>	2.16
<b>ASTM D1708</b>	<b>Modulus @ 100% Elongation, psi (N/mm<sup>2</sup>):</b>	2000 (13.8)
<b>ASTM D149</b>	<b>Dielectric Properties, range, volts/mil.</b>	
	Sample conditioning	<u>1/16" &amp; Under</u> <u>1/8"</u>
	None	<2                      -
	96 hours at 100% Relative Humidity	-                              -
<b>ASTM F586</b>	<b>Design Factors</b>	<u>1/16"</u> <u>1/8"</u>
	"m" factor:	2.8                              2.0
	"y" factor, psi (N/mm <sup>2</sup> ):	1650 (11.4)              1650 (11.4)

### SEALING CHARACTERISTICS\*

	<b>ASTM F37B Fuel A</b>	<b>DIN 3535- 4 Gas Permeability</b>
<b>Gasket Load, psi (N/mm<sup>2</sup>):</b>	1000 (7)	4640 (32)
<b>Internal Pressure, psig (bar):</b>	9.8 (0.7)	580 (40)
<b>Leakage</b>	<b>0.02 ml/hr.</b>	<b>&lt;0.015 cc/min</b>

#### Notes:

This is a general guide and should not be the sole means of selecting or rejecting this material. ASTM test results in accordance with ASTM F-104; properties based on 1/32" (0.8mm) sheet thickness unless otherwise mentioned.

\* Values do not constitute specification Limits

<sup>2</sup> Based on ANSI RF flanges at our preferred torque. When approaching maximum pressure, continuous operating temperature, minimum temperature or 50% of maximum PxT, consult Garlock Applications Engineering.