

Thomson THERMAPAC® 9950

Inorganic Fiber / Nitrile Binder / Graphite



FEATURES / BENEFITS

- Exceptional sheet material with unsurpassed temperature and pressure capability.
- Good chemical compatibility.
- Superior load retention in thermal cycling conditions.
- Passes API 607 Fire Safe Gasket Test.

TYPICAL APPLICATIONS

- Steam and superheated steam applications to 825°F continuous.
- Moderate chemical service including ethanol, liquid petroleum and petroleum derivatives.

“M & Y” FACTORS

Thickness		“m”	“y”
in	mm	(no units)	psi
1/16	1.6	2.6	4500
1/8	3.2	6.1	4500

SPECIFICATIONS

Construction:

Inorganic Fiber / Nitrile Binder / Graphite

Temperatures:

Minimum: -40°F (-40°C)

Intermittent: +1020°F (+549°C)

Continuous: +825°F (+440°C)

Pressures:

Maximum: 2150 psi

Continuous: 1480 psi

Color: Black with Orange branding.

See reverse for technical data.

TECHNICAL DATA - THERMAPAC® 9950

Physical Properties		
TEST METHOD	TYPICAL PHYSICAL PROPERTIES	
ASTM F36	Compressibility: range, %	12–22
DIN 52913	Recovery: %	40
ASTM F38	Torque retention: 1/32" thick, MPa	43
ASTM F152	Tensile across grain: psi	1305
ASTM F1315	Density: lbs/ft ³ (grams/cm ³)	91 (1.46)
ASTM F586	Design Factors:	1/16" 1/8"
	"m" factor	2.6 6.1
	"y" factor, psi	4500 4500
Immersion Properties* - ASTM F146 Fluid Resistance After Five Hours		
	ASTM IRM #903 300°F (150°C)	ASTM FUEL B 70–85°F (20–30°C)
Thickness increase: %	15	15
Weight increase: %	30	20
Sealing Characteristics		
	DIN 3535 NITROGEN	
Leakage: ml/hr	1.8	

NOTES

This is a general guide and should not be the sole means of selecting or rejecting this material. ASTM test results in accordance with ASTM F-104; properties based on 1/16" (1.5 mm) sheet thickness unless otherwise mentioned.

*Values do not constitute specification Limits.

¹When approaching maximum operating temperature or pressure limits, consult A.R. Thomson Group.

AUTHORIZED DISTRIBUTOR

Limitation of liability: actual performance may vary and is determined by factors unique to a given application. It is recommended that care be taken in the selection and application of materials for hazardous services and controlled testing be undertaken to determine suitability for a specific application. A.R. Thomson Group does not make or imply any warranty of suitability for a particular purpose and is not liable for any damages arising from the use of the information in this sheet.



Locations across Canada to serve you. For your nearest branch, please visit www.arthomson.com
Copyright © A.R. Thomson Group - All rights reserved. v2.0