

# Thomson FLUOROLON™ 7545

Microcellular PTFE with high compressibility for non-metallic flanges and where reduced bolt load is available.



## FEATURES / BENEFITS

- Soft, compressible outer microcellular layer conforms to flange irregularities.
- Solid PTFE inner core provides rigidity and stability under load.
- Easy to handle and cut.
- Chemically inert providing excellent application versatility.
- Lower gas permeability than Glass-filled PTFE materials resulting in greater sealability.
- FDA Compliant: complies with FDA regulation 21CFR177.1550.

## TYPICAL APPLICATIONS

- Service in strong caustics, moderate acids, chlorine, hydrocarbons and cryogenics.
- Non-metallic flanges such as FRP and glass lined piping.
- Pulp and Paper, Food Processing, Pharmaceutical, Chemical Process industries.

## “M & Y” FACTORS

Thickness		“m”	“y”
in	mm	(no units)	psi
1/16	1.6	1.4	1595
1/8	3.2	2	1600

## SPECIFICATIONS

### Construction:

Microcellular PTFE / Rigid PTFE core.

### Temperatures:

Minimum: -450°F (-268°C)

Maximum: +500°F (+260°C)

**Pressure, max:** 1200 psi (83 bar)

**Tensile Strength:** 1235 psi

**Color:** White with Grey branding.

**pH Range:** 0–14

Not compatible with elemental fluorine and molten alkali metals. For specific media fluid compatibility please contact A.R. Thomson Group Engineering Department.

See reverse for technical data.

## TECHNICAL DATA - FLUOROLON™ 7545

Physical Properties		
TEST METHOD	TYPICAL PHYSICAL PROPERTIES	
ASTM F36	<b>Compressibility:</b> %	55
ASTM F36	<b>Recovery:</b> %	24
ASTM F38	<b>Creep relaxation:</b> %	< 54
ASTM F152	<b>Tensile strength:</b> psi	1235
ASTM F586	<b>Design factors:</b>	<b>1/16"</b> <b>1/8"</b>
	"m" factor	1.4                              2
	"y" factor, psi	1595                          1600
Sealing Characteristics		
	<b>DIN 3535-6 NITROGEN</b>	
<b>Sealability:</b> ml/min	.01	

### NOTES

ASTM properties based on 1/32" (0.8 mm) sheet thickness unless otherwise noted. This is a general guide and should not be the sole means of selecting or rejecting this material. Based on ANSI RF flanges at our preferred torque - when approaching maximum pressure, continuous operating temperature, minimum temperature or 50% of maximum PxT, consult A.R. Thomson Group. The data listed here falls within the normal range of product properties but should not be used to establish specification limits nor used alone as the basis of design.

### AUTHORIZED DISTRIBUTOR

**Limitation of liability:** actual performance may vary and is determined by factors unique to a given application. It is recommended that care be taken in the selection and application of materials for hazardous services and controlled testing be undertaken to determine suitability for a specific application. A.R. Thomson Group does not make or imply any warranty of suitability for a particular purpose and is not liable for any damages arising from the use of the information in this sheet.



Locations across Canada to serve you. For your nearest branch, please visit [www.arthomson.com](http://www.arthomson.com)

Copyright © A.R. Thomson Group - All rights reserved. v2.4