

STRESS SAVER[®] Chemical Resistance Chart

Key:

- A = Recommended
- B = Depends on operating conditions
- C = Unsuitable
- = No data or insufficient evidence

Ratings are based on ambient temperature (70°F) unless otherwise specified.
For elevated temperature services, please consult Applications Engineering.

Medium	STRESS SAVER [®] XP		
	STRESS SAVER [®] 370	STRESS SAVER [®] 6800	
Abietic Acid	A	-	-
Acetaldehyde	C	A	A
Acetamide	A	A	A
Acetic Acid (Crude, Glacial, Pure)	C	B	C
Acetic Anhydride	C	A	B
Acetone	C	A	A
Acetonitrile	C	A	A
Acetophenone	C	A	A
2-Acetylaminofluorene	-	-	-
Acetylene	A	A	A
Acrolein	C	A	A
Acrylamide	-	-	-
Acrylic Acid	C	-	-
Acrylic Anhydride	-	-	-
Acrylonitrile	C	C	C
Air (<200°F)	A	A	A
Allyl Acetate	-	-	-
Allyl Chloride	-	B	C
Allyl Methacrylate	-	-	-
Aluminum Chloride	A	A	A
Aluminum Fluoride	A	A	A
Aluminum Hydroxide	A	A	A
Aluminum Nitrate	A	A	A
Aluminum Sulfate	A	A	A
Alums	A	A	A
4-Aminodiphenyl	-	-	-
Ammonia, Gas, 150°F and below	C	A	A
Gas, Above 150°F	C	A	B
Liquid, Anhydrous	C	A	A
Ammonium Chloride	A	A	A
Ammonium Hydroxide	A	A	A
Ammonium Nitrate	A	A	A
Ammonium Phosphate, Monobasic	A	A	A
Dibasic	A	A	A
Tribasic	A	A	A
Ammonium Sulfate	A	A	A
Amyl Acetate	C	A	A
Amyl Alcohol	A	A	A
Aniline, Aniline Oil	B	A	B
Aniline Dyes	A	A	B
o-Anisidine	-	A	-
Aqua Regia	A	B	C
Aroclors	A	B	C
Asphalt	A	B	C
Aviation Gasoline	-	B	C
Barium Chloride	A	A	A
Barium Hydroxide	A	A	A
Barium Sulfide	A	A	A
Baygon	-	-	-
Beer	A	A	A
Benzaldehyde	C	-	-
Benzene, Benzol	A	B	C
Benzidine	-	-	-
Benzoic Acid	A	B	C
Benzonitrile	-	-	-
Benzotrichloride	-	-	-
Benzoyl Chloride	A	B	C
Benzyl Alcohol	A	B	C
Benzyl Chloride	A	B	C
Biphenyl (Diphenyl)	A	B	C
Bis(2-chloroethyl)ether	-	-	-

MONOMER!!
MONOMER!!
MONOMER!!
MONOMER!!

Is FDA compliance required?

STRESS SAVER® Chemical Resistance Chart

Key:

- A = Recommended
- B = Depends on operating conditions
- C = Unsuitable
- = No data or insufficient evidence

Ratings are based on ambient temperature (70°F) unless otherwise specified.
For elevated temperature services, please consult Applications Engineering.

Medium	STRESS SAVER®		
	XP	370	680U
Bis(chloromethyl)ether	-	-	-
Bis(2-ethylhexyl)phthalate	-	-	-
Black Liquor	A	A	A
Blast Furnace Gas	A	B	C
Bleach (Sodium Hypochlorite)	A	A	B
Boiler Feed Water	-	A	A
Borax	A	A	A
Boric Acid	A	A	A
Brine (Sodium Chloride)	A	A	A
Bromine	A	B	C
Bromine Trifluoride	C	C	C
Bromoform	-	-	-
Bromomethane	A	B	C
Butadiene	A	B	C
Butane	A	B	C
2-Butanone	-	A	A
Butyl Acetate	C	B	C
Butyl Alcohol, Butanol	A	A	B
n-Butyl Amine	C	B	C
tert-Butyl Amine	C	B	C
Butyl Methacrylate	C	-	-
Butyric Acid	B	A	B
Calcium Bisulfite	A	B	C
Calcium Chloride	A	A	A
Calcium Cyanamide	-	-	-
Calcium Hydroxide	A	A	A
Calcium Hypochlorite	A	A	A
Calcium Nitrate	A	A	A
Calflo AF	-	-	-
Calflo FG	-	-	-
Calflo HTF	-	-	-
Calflo LT	-	-	-
Cane Sugar Liquors	A	-	-
Caprolactam	C	-	-
Captan	-	-	-
Carbaryl	-	-	-
Carbolic Acid, Phenol	A	B	C
Carbon Dioxide, Dry	A	A	B
Wet	A	A	B
Carbon Disulfide	A	B	C
Carbon Monoxide	A	A	A
Carbon Tetrachloride	A	B	C
Carbonic Acid	A	A	A
Carbonyl Sulfide	-	-	-
Castor Oil	A	A	B
Catechol	-	-	-
Caustic Soda	B	A	A
Cetane (Hexadecane)	A	B	C
China Wood Oil	A	B	C
Chloramben	-	-	-
Chlorazotic Acid (Aqua Regia)	C	B	C
Chlordane	A	B	C
Chlorinated Solvents, Dry	A	B	C
Wet	A	B	C
Chlorine, Dry	A	B	C
Wet	A	B	C
Chlorine Dioxide	A	B	C
Chlorine Trifluoride	C	C	C
Chloroacetic Acid	C	A	B
2-Chloroacetophenone	-	-	-
Chloroazotic Acid (Aqua Regia)	-	B	C

MONOMER!!

MONOMER!!

Check concentration of caustic

STRESS SAVER[®] Chemical Resistance Chart

Key:

- A = Recommended
- B = Depends on operating conditions
- C = Unsuitable
- = No data or insufficient evidence

Ratings are based on ambient temperature (70°F) unless otherwise specified.
For elevated temperature services, please consult Applications Engineering.

Medium	STRESS SAVER [®] XP		
	STRESS SAVER [®] 370	STRESS SAVER [®] 6800	
	A	B	C
Chlorobenzene	A	B	C
Chlorobenzilate	-	-	-
Chloroethane	A	A	A
Chloroethylene	-	-	-
Chloroform	A	B	C
Chloromethyl Methyl Ether	-	-	-
Chloronitrous Acid (Aqua Regia)	C	B	C
Chloroprene	A	B	C
Chlorosulfonic Acid	C	B	C
Chrome Plating Solutions	A	B	C
Chromic Acid	A	B	C
Chromic Anhydride	-	-	-
Chromium Trioxide	-	-	-
Citric Acid	A	A	A
Coke Oven Gas	A	B	C
Copper Chloride	A	A	A
Copper Sulfate	A	A	A
Corn Oil	A	B	C
Cotton Seed Oil	A	B	C
Creosote	A	B	C
Cresols, Cresylic Acid	A	B	C
Crotonic Acid	A	-	-
Crude Oil	A	B	C
Cumene	A	B	C
Cyclohexane	A	B	C
Cyclohexanone	C	B	C
2,4-D, Salts and Esters	-	-	-
Detergent Solutions	A	A	A
Diazomethane	-	-	-
Dibenzofuran	-	-	-
Dibenzylether	A	B	C
1,2-Dibromo-3-chloropropane	-	-	-
Dibromoethane	-	-	-
Dibutyl Phthalate	A	A	A
Dibutyl Sebacate	A	A	B
o-Dichlorobenzene	A	B	C
1,4-Dichlorobenzene	A	B	C
3,3-Dichlorobenzidine	A	-	-
Dichloroethane (1,1 or 1,2)	A	B	C
1,1-Dichloroethylene	A	B ¹	C
Dichloroethyl Ether	-	-	-
Dichloromethane	A	B	C
1,2-Dichloropropane	A	B	C
1,3-Dichloropropene	A	B	C
Dichlorvos	-	-	-
Diesel Oil	A	B	C
Diethanolamine	-	A	A
N,N-Diethylaniline	C	A	A
Diethyl Carbonate	A	B	C
Diethyl Sulfate	-	A	A
3,3-Dimethoxybenzidine	-	-	-
Dimethylaminoazobenzene	-	-	-
N,N-Dimethyl Aniline	-	-	-
3,3-Dimethylbenzidine	-	-	-
Dimethyl Carbamoyl Chloride	-	-	-
Dimethyl Ether	C	A	B
Dimethylformamide	C	A	B
Dimethyl Hydrazine, Unsymmetrical	-	-	-
Dimethyl Phthalate	A	A	B
Dimethyl Sulfate	-	-	-
4,6-Dinitro-o-Cresol and Salts	-	-	-

Is FDA compliance required?
Is FDA compliance required?

MONOMER!!

STRESS SAVER® Chemical Resistance Chart

Key:

- A = Recommended
- B = Depends on operating conditions
- C = Unsuitable
- = No data or insufficient evidence

Ratings are based on ambient temperature (70°F) unless otherwise specified.
For elevated temperature services, please consult Applications Engineering.

Medium	STRESS SAVER®		
	XP	370	6800
2,4-Dinitrophenol	-	-	-
2,4-Dinitrotoluene	C	B	C
Dioxane	C	A	B
1,2-Diphenylhydrazine	-	A	-
Diphyl DT	-	A	-
Dowfrost	-	A	-
Dowfrost HD	-	A	-
Dowtherm 4000	-	B	C
Dowtherm A	A	B	C
Dowtherm E	A	B	C
Dowtherm G	-	B	C
Dowtherm HT	-	B	C
Dowtherm J	-	B	C
Dowtherm Q	-	B	C
Dowtherm SR-1	-	B	C
Epichlorohydrin	C	B	C
1,2-Epoxybutane	-	-	-
Ethane	A	B	C
Ethers	C	B	C
Ethyl Acetate	C	A	A
Ethyl Acrylate	C	A ¹	B
Ethyl Alcohol	A	A	A
Ethylbenzene	A	B	C
Ethyl Carbamate	-	-	-
Ethyl Cellulose	C	A	B
Ethyl Chloride	A	A	A
Ethyl Ether	C	B	C
Ethyl Hexoate	-	-	-
Ethylene	A	B	C
Ethylene Bromide	-	B	C
Ethylene Dibromide	A	B	C
Ethylene Dichloride	A	B	C
Ethylene Glycol	A	A	A
Ethyleneimine	-	-	-
Ethylene Oxide	C	B ¹	C
Ethylene Thiourea	-	-	-
Ethylidene Chloride	-	B	C
Ferric Chloride	A	A	A
Ferric Phosphate	-	-	-
Ferric Sulfate	A	A	A
Fluorine, Gas	B	C	C
Fluorine, Liquid	B	C	C
Fluorine Dioxide	-	C	-
Formaldehyde	C	A	B
Formic Acid	C	A	A
Fuel Oil #1	A	B	C
Fuel Oil, Acid	-	B	C
Furfural	C	A	B
Gasoline, Refined	A	B	C
Sour	-	B	C
Gelatin	A	A	A
Glucose	A	A	A
Glue, Protein Base	A	A	A
Glycerine, Glycerol	A	A	A
Glycol	A	A	A
Grain Alcohol	A	A	A
Grease, Petroleum Base	A	B	C
Green Sulfate Liquor	A	A	A
Heptachlor	A	B	C
Heptane	A	B	C
Hexachlorobenzene	-	-	-

MONOMER!!
Is FDA compliance required?

MONOMER!!

Is FDA compliance required?

STRESS SAVER[®] Chemical Resistance Chart

Key:

- A = Recommended
- B = Depends on operating conditions
- C = Unsuitable
- = No data or insufficient evidence

Ratings are based on ambient temperature (70°F) unless otherwise specified.
For elevated temperature services, please consult Applications Engineering.

Medium	STRESS SAVER [®] XP	STRESS SAVER [®] 370	STRESS SAVER [®] 680U
Hexachlorobutadiene	-	-	-
Hexachlorocyclopentadiene	-	-	-
Hexachloroethane	A	-	-
Hexadecane	A	-	-
Hexamethylene Diisocyanate	-	-	-
Hexamethylphosphoramide	-	-	-
Hexane	A	B	C
Hexone	C	A	B
Hydraulic Oil, Mineral	A	B	C
Synthetic	B	B	C
Hydrazine	C	A	A
Hydrobromic Acid	A	A	A
Hydrochloric Acid	A	A	B
Hydrocyanic Acid	A	A	A
Hydrofluoric Acid, up to Anhydrous, 150°F & below	C	B	C
Less than 65%, Above 150°F	C	B	C
65% to Anhydrous, Above 150°F	C	B	C
Anhydrous	C	B	C
Hydrofluorosilicic Acid	-	-	-
Hydrofluosilicic Acid	A	A	A
Hydrogen	A	A	A
Hydrogen Bromide	-	A	A
Hydrogen Fluoride	C	A	B
Hydrogen Peroxide, 10%	A	B	C
10-90%	A	B	C
Hydrogen Sulfide, Dry or Wet	C	A	B
Hydroquinone	A	B	C
Iodine Pentafluoride	C	-	C
Iodomethane	-	-	-
Isobutane	A	B	C
Isooctane	A	B	C
Isophorone	C	A	A
Isopropyl Alcohol	A	A	A
Jet Fuels (JP Types)	A	B	C
Kerosene	A	B	C
Lacquer Solvents	C	B	C
Lacquers	C	B	C
Lactic Acid, (COLD)	A	A	A
(HOT)	A	A	B
Lime Salt peter (Calcium Nitrates)	A	A	A
Lindane	-	-	-
Linseed Oil	A	B	C
Lithium Bromide	A	A	B
Lithium, Elemental	-	C	-
Lubricating Oils, Mineral or Petroleum Types	A	B	C
Refined	-	B	C
Sour	-	B	C
Lye	A	A ¹¹	A
Magnesium Chloride	A	A	A
Magnesium Hydroxide	A	A	A
Magnesium Sulfate	A	A	A
Maleic Acid	A	A	A
Maleic Anhydride	C	B	C
Mercuric Chloride	A	A	A
Mercury	A	A	A
Methane	A	B	C
Methanol, Methyl Alcohol	A	A	A
Methoxychlor	-	-	-
Methylacrylic Acid	-	B	C
Methyl Alcohol	A	A	A
2-Methylaziridine	-	-	-

Check concentration of caustic

STRESS SAVER® Chemical Resistance Chart

Key:

- A = Recommended
- B = Depends on operating conditions
- C = Unsuitable
- = No data or insufficient evidence

Ratings are based on ambient temperature (70°F) unless otherwise specified.
For elevated temperature services, please consult Applications Engineering.

Medium	STRESS SAVER®		
	XP	370	6800
Methyl Bromide	A	B	C
Methyl Chloride	A	B	C
Methyl Chloroform	A	B	C
4,4 Methylene Bis(2-chloroaniline)	-	-	-
Methylene Chloride	B	B	C
4,4-Methylene Dianiline	-	-	-
Methylene Diphenyldiisocyanate	-	-	-
Methyl Ethyl Ketone	C	A	A
Methyl Hydrazine	-	-	-
Methyl Iodide	-	A	A
Methyl Isobutyl Ketone (MIBK)	C	-	-
Methyl Isocyanate	B	-	-
Methyl Methacrylate	C	B	C
N-Methyl-2-Pyrrolidone	-	-	-
Methyl Tert. Butyl Ether (MTBE)	C	B	C
Milk	A	A	A
Mineral Oils	A	B	C
Mobiltherm 600	A	B	C
Mobiltherm 603	-	B	C
Mobiltherm 605	-	B	C
Mobiltherm Light	-	B	C
Molten Alkali Metals	-	C	C
Monomethylamine	-	A	A
MultiTherm 100	-	-	-
MultiTherm 503	-	-	-
MultiTherm IG-2	-	-	-
MultiTherm PG-1	-	-	-
Muriatic Acid	-	A	B
Naphtha	A	B	C
Naphthalene	A	B	C
Naphthols	-	-	-
Natural Gas	A	B	C
Nickel Chloride	A	A	A
Nickel Sulfate	A	A	A
Nitric Acid, Less than 30%	A	B	C
Above 30%	A	B	C
Crude	A	B	C
Red Fuming	A	B	C
Nitrobenzene	A	A	B
4-Nitrophenyl	-	-	-
2-Nitro-Butanol	-	-	-
Nitrocalcite (Calcium Nitrate)	A	A	A
Nitrogen	A	A	A
Nitrogen Tetroxide	C	B	C
Nitrohydrochloric Acid (Aqua Regia)	C	B	C
Nitromethane	C	A	B
2-Nitro-2-Methyl Propanol	-	-	-
Nitromuriatic Acid (Aqua Regia)	-	B	C
4-Nitrophenol	C	-	-
2-Nitropropane	C	A	B
N-Nitrosodimethylamine	-	-	-
N-Nitroso-N-Methylurea	-	-	-
N-Nitrosomorpholine	-	-	-
Norge Niter (Calcium Nitrate)	A	A	A
Norwegian Saltpeter (Calcium Nitrate)	A	A	A
N-Octadecyl Alcohol	-	-	-
Octane	A	B	C
Oil, Petroleum	A	B	C
Oils, Animal and Vegetable	A	B	C
Oleic Acid	A	B	C
Oleum	A	B	C

MONOMER!!

Is FDA compliance required?

Is FDA compliance required?

STRESS SAVER[®] Chemical Resistance Chart

Key:

- A = Recommended
- B = Depends on operating conditions
- C = Unsuitable
- = No data or insufficient evidence

Ratings are based on ambient temperature (70°F) unless otherwise specified.
For elevated temperature services, please consult Applications Engineering.

Medium	STRESS SAVER [®] XP STRESS SAVER [®] 370 STRESS SAVER [®] 6800		
Orthodichlorobenzene	-	B	C
Oxalic Acid	A	A	A
Oxygen, Gas	A	-	-
Ozone	A	A	B
Palmitic Acid	A	A	B
Paraffin	A	B	C
Paratherm HE	A	-	-
Paratherm NF	A	-	-
Parathion	-	-	-
Paraxylene	-	B	C
Pentachloronitrobenzene	-	-	-
Pentachlorophenol	A	B	C
Pentane	A	B	C
Perchloric Acid	A	B	C
Perchloroethylene	A	B	C
Petroleum Oils, Crude	A	B	C
Petroleum Oil <250°F	A	B	C
Petroleum Oil >250°F	B	B	C
Phenol	A	B	C
p-Phenylenediamine	C	-	-
Phosgene	C	B	C
Phosphate Esters	-	A	A
Phosphine	-	-	-
Phosphoric Acid, 20%	A	A	A
Phosphoric Acid, 60%	A	A	A
Phosphoric Acid, 85%	A	A	A
Phosphorus, Elemental	-	-	-
Phosphorus Pentachloride	-	-	-
Phthalic Acid	A	A	A
Phthalic Anhydride	C	A	A
Picric Acid	A	B	C
Pinene	A	B	C
Piperidine	C	B	C
Polyacrylonitrile	-	-	-
Polychlorinated Biphenyls	-	-	-
Potash, Potassium Carbonate	A	A	A
Potassium Acetate	C	A	A
Potassium Bichromate	-	A	A
Potassium Chromate	A	A	A
Potassium Cyanide	A	A	A
Potassium Dichromate	A	A	A
Potassium, Elemental	-	C	-
Potassium Hydroxide	C	A ¹¹	A
Potassium Nitrate	A	A	A
Potassium Permanganate	A	A	A
Potassium Sulfate	A	A	A
Producer Gas	A	B	C
Propane	A	B	C
1,3-Propane Sultone	-	-	-
Beta-Propiolactone	-	-	-
Propionaldehyde	-	-	-
Propoxur (Baygon)	-	-	-
Propyl Nitrate	C	A	B
Propylene	A	B	C
Propylene Dichloride	A	B	C
Propylene Oxide	C	A	B
1,2-Propylenimine	-	-	-
Prussic Acid, Hydrocyanic Acid	-	A	A
Pyridine	C	A	B
Quinoline	A	-	-
Quinone	A	-	-

Consult Engineering!

Check concentration of caustic!

STRESS SAVER[®] Chemical Resistance Chart

Key:

- A = Recommended
- B = Depends on operating conditions
- C = Unsuitable
- = No data or insufficient evidence

Ratings are based on ambient temperature (70°F) unless otherwise specified.
For elevated temperature services, please consult Applications Engineering.

Medium	STRESS SAVER [®] XP		
	STRESS SAVER [®] 370	STRESS SAVER [®] 6800	
Refrigerants			
10	-	B	C
11	B	B	C
12	B	A	A
13	B	A	A
13B1	B	A	A
21	C	B	C
22	C	A	A
23	-	A	A
31	C	A	A
32	C	A	A
112	B	B	C
113	C	B	C
114	B	A	A
114B2	B	B	C
115	B	A	A
123	-	B	C
124	-	A	A
125	-	A	A
134a	-	A	A
141b	-	-	-
142b	C	A	A
143a	B	A	A
152a	C	A	A
218	B	A	A
290	-	B	C
500	-	-	-
502	C	-	-
503	-	A	A
C316	B	A	A
C318	B	A	A
HP62	-	-	-
HP80	-	-	-
HP81	-	-	-
Salt Water	A	A	A
Saltpeter, Potassium Nitrate	A	A	A
2,4-D Salts and Esters	-	-	-
Sewage	A	A	A
Silver Nitrate	A	A	A
Skydrol 500A	C	A	A
Skydrol 500B	C	A	A
Skydrol LD	C	-	-
Skydrol 7000	A	A	A
Soap Solutions	A	A	A
Soda Ash, Sodium Carbonate	A	A	A
Sodium Bicarbonate, Baking Soda	A	A	A
Sodium Bisulfate (Dry)	A	A	A
Sodium Bisulfite	A	A	A
Sodium Chlorate	A	A	A
Sodium Chloride	A	A	A
Sodium Cyanide	A	A	A
Sodium, Elemental	-	C	-
Sodium Hydroxide	A	A ¹¹	B
Sodium Hypochlorite	A	A	B
Sodium Metaborate Peroxyhydrate	-	-	-
Sodium Metaphosphate	A	A	A
Sodium Nitrate	A	A	A
Sodium Perborate	A	A	A
Sodium Peroxide	A	A	A
Sodium Phosphate, Monobasic	A	A	A
Dibasic	A	A	A

Check concentration of caustic!

STRESS SAVER® Chemical Resistance Chart

Key:

- A = Recommended**
- B = Depends on operating conditions**
- C = Unsuitable**
- = No data or insufficient evidence**

**Ratings are based on ambient temperature (70°F) unless otherwise specified.
For elevated temperature services, please consult Applications Engineering.**

Medium	STRESS SAVER®		
	XP	370	6800
Tribasic	A	A	A
Sodium Silicate	A	A	A
Sodium Sulfate	A	A	A
Sodium Sulfide	A	A	A
Sodium Superoxide	-	A	B
Sodium Thiosulfate, "Hypo"	A	-	-
Soybean Oil10	A	B	C
Stannic Chloride	A	A	A
Steam, Saturated (<366°F)	A	A	B
Superheated	C	-	C
Stearic Acid	A	A	B
Stoddard Solvent	A	B	C
Styrene	A	B ¹	C
Styrene Oxide	-	-	-
Sulfur Chloride	A	B	C
Sulfur Dioxide	A	A	A
Sulfur, Molten	A	A	A
Sulfur Trioxide, Dry	A	A	B
Wet	C	B	C
Sulfuric Acid, 20-40%	A	A	B
Sulfuric Acid, 40-98%	A	A	B
Sulfuric Acid, concentrated	A	A	B
Sulfuric Acid, Fuming	A	B	C
Sulfurous Acid	B	A	B
Sulfurous Acid (5% Sulfur Dioxide)	C	A	B
Syltherm 800	-	-	-
Syltherm XLT	-	-	-
Tannic Acid	A	A	A
Tar	A	B	C
Tartaric Acid	A	B	C
2,3,7,8-TCDB-p-Dioxin	-	-	-
Tertiary Butyl Amine	-	-	-
Tetrabromoethane	-	B	C
Tetrachlorethane	A	B	C
Tetrachloroethylene	A	B	C
Tetrahydrofuran, THF	C	B	C
Therminol 44	A	B	C
Therminol 45	A	B	C
Therminol 59	-	B	C
Therminol 60	-	B	C
Therminol 66	-	B	C
Therminol 75	-	B	C
Therminol D12	-	B	C
Therminol LT	-	B	C
Therminol VP-1	-	B	C
Therminol XP	-	B	C
Thionyl Chloride	A	B	C
Titanium Sulfate	-	-	-
Titanium Tetrachloride	A	B	C
Toluene	A	B	C
2,4-Toluenediamine	-	-	-
2,4-Toluenediisocyanate	C	A	B
Toluene Sulfonic Acid	-	-	-
o-Toluidine	C	-	-
Toxaphine	-	-	-
Transformer Oil (Mineral Type)	A	B	C
Transmission Fluid A	A	B	C
Trichloroacetic Acid	B	A	B
1,2,3- Trichlorobenzene	A	-	-
1,1,1-Trichloroethane	A	B	C
Trichloroethylene	A	B	C

MONOMER!!

STRESS SAVER[®] Chemical Resistance Chart

Key:

- A = Recommended
- B = Depends on operating conditions
- C = Unsuitable
- = No data or insufficient evidence

Ratings are based on ambient temperature (70°F) unless otherwise specified.
 For elevated temperature services, please consult Applications Engineering.

Medium	STRESS SAVER [®] XP		
	STRESS SAVER [®] 370	STRESS SAVER [®] 6800	
2,4,5-Trichlorophenol	-	-	-
2,4,6-Trichlorophenol	-	-	-
Tricresylphosphate	A	A	A
Triethanolamine	C	A	A
Triethyl Aluminum	A	-	-
Triethylamine	C	A	A
Trifluralin	-	-	-
2,2,4-Trimethylpentane	A	B	C
Tung Oil	A	B	C
Turpentine	A	B	C
UCON Heat Transfer Fluid 500	-	-	-
UCON Process Fluid WS	-	-	-
Varnish	A	B	C
Vinegar	A	A	A
Vinyl Acetate	C	A ¹	B
Vinyl Bromide	-	A ¹	-
Vinyl Chloride	A	B ¹	C
Vinylidene Chloride	A	B ¹	C
Vinyl Methacrylate	-	-	-
Water, Acid Mine, with Oxidizing Salt	-	-	-
No Oxidizing Salts	-	A	A
Water, Distilled	A	A	A
Return Condensate	A	A	A
Seawater	A	A	A
Tap	A	A	A
Whiskey and Wines	A	A	A
Wood Alcohol	A	A	A
Xceltherm 550	-	-	-
Xceltherm 600	-	-	-
Xceltherm MK1	-	-	-
Xceltherm XT	-	-	-
Xylene	A	B	C
Zinc Chloride	A	A	A
Zinc Sulfate	A	A	A

Is FDA compliance required?
MONOMER!!
MONOMER!!
MONOMER!!
MONOMER!!

Is FDA compliance required?