

Thomson GC 89



General service compression packing for centrifugal pump, rotating equipment agitators/mixers, reciprocating pumps, and valve service.

FEATURES / BENEFITS

- Non-abrasive - long service life.
- General service economizes on one style.
- Non-contaminating - will not affect the media.
- Reduces maintenance costs.

TYPICAL APPLICATIONS

- Centrifugal or reciprocating pumps, valves.
- Medium acids and alkalis, petroleum and synthetic oils, steam, aromatic and aliphatic solvents and dry gas applications. Good chemical resistance.
- Where a clean 'white' non-contaminating packing is preferred.
- Rotating equipment - general service applications, agitators/mixers, pumps and valves.

SPECIFICATIONS

Construction:

Teflon® impregnated, acrylic yarn with unique break-in lubricant. Single yarn encapsulation for superior protection from chemical attack. Square interbraid.

Max Speed:

2500+ fpm (12.7 m/s)

Temperatures:

-170°F (-112°C) to
550°F (288°C)

Max Pressure:

To 500 psi (34.4 bar) rotary

Up to 2500 psi (172 bar) in
valve service

pH range:

0-12

Teflon® is a registered trademark of Dupont. All trademarks remain property of their respective holders and are used only to directly describe the products being provided.

ORDERING INFORMATION - GC 89

Specify Thomson style, size and quantity (lbs) required.

Size	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8	1"
Approx. (ft/lb)	45	26	16	13.1	9.8	7.1	6.3	4.6	2.7	2.3	1.8
Std pkg (lbs)	2	2	2/5	5	5	5/10/25	5	5/10	10/25	10	10/25

Also available in metric sizes, die formed pre-packaged sets, and specialty cut lengths.
Contact A.R. Thomson Group for any special requirements.

SHAFT SPEED CONVERSION CALCULATIONS

Feet per minute (fpm)	Meter per second (m/s)
Shaft / sleeve diameter (in) x RPM x 0.262 = fpm	Shaft / sleeve diameter (in) x RPM x 0.0013299 = m/s
Shaft / sleeve diameter (mm) x RPM x 0.0103 = fpm	Shaft / sleeve diameter (mm) x RPM x 0.0000524 = m/s

AUTHORIZED DISTRIBUTOR



Limitation of liability: actual performance may vary and is determined by factors unique to a given application. It is recommended that care be taken in the selection and application of materials for hazardous services and controlled testing be undertaken to determine suitability for a specific application. A.R. Thomson Group does not make or imply any warranty of suitability for a particular purpose and is not liable for any damages arising from the use of the information in this sheet.

 **A.R. THOMSON GROUP INC.**

Locations across Canada to serve you. For your nearest branch, please visit: www.arthomson.com

Copyright © A.R. Thomson Group - All rights reserved.

arthomson.com