

# Thomson HS-3000M



## TYPICAL APPLICATIONS

- Rotary equipment - high-speed rotary to 4000 fpm, digester-related equipment.
- Molybdenum disulphide lubricant - extremely chemical and thermally stable.

Pure carbon yarn square interbraid construction compression packing for rotary equipment and valves.

## FEATURES / BENEFITS

- Carbon filament - staple fibers conform to the stuffing box, resist extrusion in high-pressure applications and/or worn rotating equipment.
- High-speed applications - molybdenum disulphide break-in lubricant offers a more forgiving start-up.

### All carbon construction:

- Maximizes equipment reliability and performance.
- Provides excellent chemical resistance.
- Energy savings related to less gland load - less friction, reduced gland water required.
- Dissipates heat better than conventional compression packing. Increased MTBR - mean time between repair - less sleeve damage.
- Dimensionally more stable compared to conventional compression packing (less volume loss).

## SPECIFICATIONS

### Construction:

Pure carbon yarn with graphite dispersion lubricant - surface coated with molybdenum disulphide. Square interbraid.

### Pressure:

Valves: to 2500 psi (173 bar)

Pumps: to 500 psi (35 bar)  
rotary

### pH range:

0-14 (except  
strong oxidizers)

### Temperatures:

Min: -328°F (-200°C)

Max. Atmosphere: to 850°F  
(455°C)

Max. Steam: to 1200°F  
(650°C)

### Shaft Speed:

4000 fpm (20 m/s)

## ORDERING INFORMATION - HS-3000M

Specify Thomson style, size and quantity (lbs) required.

Size	1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
Approx. (ft/lb)	140	50	30	21	13	10	8.5	7.0	6.0	4.0	3.4	2.2
Std pkd(lbs)	1	1	5	5	5	5	5	5	5	5/10	10	10

Also available in metric sizes, die formed pre-packaged sets, and specialty cut lengths.  
Contact A.R. Thomson Group for any special requirements.

## SHAFT SPEED CONVERSION CALCULATIONS

Feet per minute (fpm)	Meter per second (m/s)
Shaft / sleeve diameter (in) x RPM x 0.262 = fpm	Shaft / sleeve diameter (in) x RPM x 0.0013299 = m/s
Shaft / sleeve diameter (mm) x RPM x 0.0103 = fpm	Shaft / sleeve diameter (mm) x RPM x 0.0000524 = m/s

## AUTHORIZED DISTRIBUTOR



Limitation of liability: actual performance may vary and is determined by factors unique to a given application. It is recommended that care be taken in the selection and application of materials for hazardous services and controlled testing be undertaken to determine suitability for a specific application. A.R. Thomson Group does not make or imply any warranty of suitability for a particular purpose and is not liable for any damages arising from the use of the information in this sheet.

 **A.R. THOMSON GROUP INC.**

Locations across Canada to serve you. For your nearest branch, please visit: [www.arthomson.com](http://www.arthomson.com)

Copyright © A.R. Thomson Group - All rights reserved.

[arthomson.com](http://arthomson.com)