


Thomson ULTRAGRAF® EF

UltraGraf 'Easy Fab' is the latest technology in Flexible Graphite offering safer handling and easier/faster fabrication.



FEATURES/BENEFITS

- **New 316L Flexmet™ Insert:**
 - Greatly reduced sharp edges.
 - Easier to fabricate.
 - Promotes more even loading and greater load retention during cycling.
- **Thomson Sure-Release® Anti-Stick** treatment makes gasket removal quicker and easier.
- **Updated surface finish:** Results in a more robust, less fragile gasket.
- **Plus all the benefits of Flexible Graphite:**
 - No fillers or binders allowing greater chemical range.
 - Stainless insert reduces creep relaxation.
 - Conforms well to surface irregularities.

TYPICAL APPLICATIONS

- Gaskets in a broad range of chemicals and hydrocarbons as well as high pressure steam.
- Chemical, PetroChemical, Oil Refinery, Pulp and Paper, and Power Generation industries including nuclear power plants.
- Fire Safe.

SPECIFICATIONS

Construction:

Pure Homogeneous Flexible Graphite laminated to a unique acid-resistant 316L Flexmet insert.

Temperatures:

Minimum: -328°F (-200°C)

Maximum: +1200°F (+648°C)

Continuous: +850°F (+454°C)

Pressure, max: 2000 psi

Color: Sea Blue with Black branding.

See reverse for technical data.

AVAILABILITY

- Custom shapes and standard flange gaskets.
- Standard stock items:
 - 1/32", 1/16" & 1/8" thicknesses x 59" x 59"
 - * Other sheet sizes & thicknesses available upon request.

TECHNICAL DATA - ULTRAGRAF® EF

Physical Properties

TYPICAL PHYSICAL PROPERTIES

Oxidation Rate: %	< 5
Oxidation Inhibitor: Y/N	No
Leachable Chloride: ppm	< 50
Sulfur Content: ppm	< 1000
Purity: %	≥ 98
Ash Content: ppm	< 2
Density (Graphite only - without insert): lb/ft ³	65
SS 316L Insert: inch	0.015
Compressibility ASTM F36A: %	35
Recovery ASTM F36A: %	22
Creep Relaxation ASTM F38B: %	12
Stability Under Stress DIN 52913 (572°F): N/mm ²	> 48
Sealability DIN 3535 (0.060"): ml/min	0.5

"M & Y" FACTORS

Thickness		"m"	"y"
in	mm	(no units)	psi
1/16	1.6	4.5	1740
1/8	3.2	5.5	4351

NOTES

Flexible Graphite material is not recommended for Glass or Ceramic flanges. Consult an A.R. Thomson Group representative for temperatures or pressures nearing the maximum rating. When approaching maximum or minimum temperatures, or maximum operating pressure, consult A.R. Thomson Group.

AUTHORIZED DISTRIBUTOR

Limitation of liability: actual performance may vary and is determined by factors unique to a given application. It is recommended that care be taken in the selection and application of materials for hazardous services and controlled testing be undertaken to determine suitability for a specific application. A.R. Thomson Group does not make or imply any warranty of suitability for a particular purpose and is not liable for any damages arising from the use of the information in this sheet.



Locations across Canada to serve you. For your nearest branch, please visit www.arthomson.com

Copyright © A.R. Thomson Group - All rights reserved. v1.4